

**Maya Ardiati. 081211331137, 2016. Sintesis dan Karakterisasi Komposit Polyester Serat Daun Lontar dengan Penambahan Variasi Konsentrasi Kalium Permanganat ( $KMnO_4$ ). Skripsi ini dibawah bimbingan Jan Ady, S.Si, M.Si dan Drs. Djony Izak Rudyardjo, M.Si, Departemen Fisika, Fakultas Sains dan Teknologi, Universitas Airlangga.**

---

## ABSTRAK

Telah dilakukan penelitian tentang Sintesis dan Karakterisasi Komposit Polyester Serat Daun Lontar dengan Penambahan Variasi Konsentrasi Kalium Permanganat ( $KMnO_4$ ). Penelitian ini bertujuan untuk mengetahui pengaruh variasi konsentrasi  $KMnO_4$  terhadap karakteristik densitas, kekuatan tekan dan kekuatan tarik pada komposit serat daun lontar (*Borassus flabellifer*). Bahan komposit polimer yang digunakan dalam penelitian ini adalah resin *Polyester BTQN 157* sebagai matrik dan serat daun lontar sebagai *filler*. Perbandingan komposit yang digunakan adalah 75% untuk matrik dan 25% untuk *filler*. Katalis yang digunakan untuk mempercepat proses pembuatan adalah katalis *Metyl Etyl Keton Peroksida* (MEKPO). pada penelitian ini akan disintesis serat daun lontar (*Borassus flabellifer*) yang direndam dengan larutan alkali  $KMnO_4$ . Perendaman dilakukan dengan variasi konsentrasi  $KMnO_4$  2%, 4%, 6%, 8%, dan 10%. Karakterisasi yang dilakukan adalah uji kerapatan, kuat tekan, kuat tarik dan SEM. Hasil penelitian menunjukkan nilai densitas serat tertinggi pada konsentrasi 2%  $KMnO_4$  yaitu  $0,767 \text{ g/cm}^3$ , densitas komposit polyester tertinggi pada konsentrasi 8%  $KMnO_4$  yaitu  $1,081 \text{ g/cm}^3$ , kuat tekan tertinggi pada konsentrasi 6%  $KMnO_4$  yaitu 66,178 MPa, kuat tarik tertinggi pada konsentrasi 2%  $KMnO_4$  yaitu 54,80 MPa. Dari hasil keseluruhan data menunjukkan bahwa Penambahan Variasi Konsentrasi Kalium Permanganat ( $KMnO_4$ ) mempengaruhi sifat fisis dan mekanik dengan nilai optimum pada penambahan konsentrasi 2%  $KMnO_4$  berdasarkan referensi maupun dari sampel kontrol (tanpa penambahan serat daun lontar) untuk bahan material industri.

Kata kunci : Komposit *Polyester*, serat daun lontar, konsentrasi  $KMnO_4$

**Maya Ardiati. 081211331137, 2016. Synthesis and Characterization of Polyester Composites Fiber Palmyra Leaf with Addition Variation Concentration Potassium Permanganate ( $KMnO_4$ ). This thesis under the guidance of Jan Ady, S.Si, M.Si and Drs. Izak Djony Rudyardjo, M.Si, Department of Physics, Faculty of Science and Technology, University of Airlangga.**

---

## ABSTRACT

Research on synthesis and characterization of polyester composites fiber palmyra leaf with addition variation concentration potassium permanganate ( $KMnO_4$ ). This study aims to determine the effect of variations in the concentration of  $KMnO_4$  on the characteristics of density, compressive strength and tensile strength to the composite fibers of palmyra leaf (*Borassus flabellifer*). Materials polymer composite used in this study was resin polyester BTQN 157 as the matrix and fiber palmyra leaf as filler. Comparison of composites used is 75% to 25% for the matrix and filler. The catalyst used to speed up the manufacturing process is a catalyst Metyl Etyl Ketone Peroxide (MEKPO). This research will be synthesized fibers of palmyra leaf (*Borassus flabellifer*) were soaked with a solution alkali  $KMnO_4$ . Soaking was done by varying the concentration of  $KMnO_4$  2%, 4%, 6%, 8% and 10%. Characterization is done is test the density, compressive strength, tensile strength and SEM. The results showed the highest fiber density value at a concentration of 2%  $KMnO_4$  is  $0.767 \text{ g/cm}^3$ , The highest density polyester composite at a concentration of 8%  $KMnO_4$  is  $1.081 \text{ g/cm}^3$ , The highest compressive strength at a concentration of 6%  $KMnO_4$  is 66.178 MPa, the highest tensile strength at a concentration of 2%  $KMnO_4$  is 54.80 MPa. From the results of the overall data showed that the addition of Variation of Concentration of Potassium Permanganate ( $KMnO_4$ ) affects the physical and mechanical properties with optimum value in the addition of a concentration of 2%  $KMnO_4$  by reference or control sample (without the addition of fibers of palm leaves) for industrial materials.

Keywords: Polyester composite, fiber palmyra leaf, concentration  $KMnO_4$