

TOXICOLOGICAL SCREENING OF ELLAGIC ACID IN POMEGRANATE FRUIT AND HYDROXYAPATITE COMBINATION AS BONE GRAFT MATERIAL ON BHK-21 FIBROBLAST CELL

by Hendrik Setia Budi

Submission date: 13-Jun-2022 07:33AM (UTC+0800)

Submission ID: 1855541215

File name: Dentino_Sinta-3.pdf (154.23K)

Word count: 3352

Character count: 18428

DENTINO
JURNAL KEDOKTERAN GIGI
Vol V. No 1. Maret 2020

1
TOXICOLOGICAL SCREENING OF ELLAGIC ACID IN POMEGRANATE
FRUIT AND HYDROXYAPATITE COMBINATION AS BONE GRAFT
MATERIAL ON BHK-21 FIBROBLAST CELL

Agung Satria Wardhana¹, Isyana Erlita², Intan Nirwana³, Hendrik Setiabudi⁴

4
¹Department of Dental Material, Faculty of Dentistry, Lambung Mangkurat University, Banjarmasin

²Department of Conservative Dentistry, Faculty of Dentistry, Lambung Mangkurat University, Banjarmasin

³Department of Dental Material, Faculty of Dentistry, Airlangga University, Surabaya

⁴Department of Oral Biology, Faculty of Dentistry, Airlangga University, Surabaya

ABSTRACT

Background: Bone graft is an alternative therapy for periodontitis and other bone destructive lesions. Several studies had revealed Ellagic Acid (EA) ability in increasing osteogenesis process. EA contains polyphenols, such as Ellagitannin, Gallotannin, and Anthocyanin, which demonstrate anti-inflammatory and antibacterial activity as well as growth factor stimulating effect. EA combination with bone graft material (hydroxyapatite) is anticipated to enhance bone osteogenesis yet no investigation was performed to identify its toxicity towards fibroblast cell. **Objective:** To analyze EA toxicity on fibroblast cell in vitro. **Methods:** This was a true experimental study using post-test only with control group design. Fibroblast cell was exposed with EA in eight different concentrations: 0.1%, 0.2%, 0.5%, 1%, 2%, 3%, 4% and 5%. Control group comprised of cell control and media group. All groups were exposed to MTT Assay test and measured using Elisa Reader. **Result:** The calculation of cell viability value in EA groups at 0.1%, 0.2%, 0.5%, 1%, 2%, 3%, 4% and 5% concentration were 88.2%, 92.3%, 97.5%, 89.5%, 84.2%, 90.7%, 88.9% and 89.4% respectively. **Conclusion:** All EA and hydroxyapatite combinations are not toxic towards BHK-21 fibroblast cells.

Keywords: Bone graft, ellagic acid, fibroblast cells, hydroxyapatite, MTT assay

Correspondence: Agung Satria Wardhana. Faculty of Dentistry, University of Lambung Mangkurat, Jl. Veteran 128B. Banjarmasin, South Borneo, email: agung.drg@gmail.com

INTRODUCTION

Bone destruction and periodontal problems are the highest disease prevalence in Indonesia with annual increase in the current decade. Based on Basic Health Research conducted by Ministry of Health Indonesia, this disease prevalence reached 23.4% in 2007 and increased to 57.6% in 2018.¹⁻³ Newman *et al* (2012) mentioned that 50% of adult population in the United States suffered from bone and periodontal tissue destruction², while National Household Health Survey Ministry of Health Indonesia in 2011 reported that bone and periodontal problems constituted 60% of oral and dental diseases within the country.

Conventional therapy, in extensive bone destruction specifically, is by utilizing graft or bone transplant from various types such as autograft, allograft, xenograft or synthetic graft.⁴

Autograft is bone transplant method originated from individual's body. This type of transplant demonstrates excellent osteogenic and osteoconductive activity. Notwithstanding, autograft results in several drawbacks such as painful sensation at donor site, blood loss, infection, donor tissues death, and limited number of organ available.⁵ So does allograft obtained from cadavers or donor from similar species or xenograft (from animal or different

species) that are presented with countable disadvantages like less osteogenic activity as well as risk of cross infection and immunological rejection.⁶⁻⁸ As the gold standard of therapeutic material for bone destruction, the three types of graft exhibit limitation in material quantity. This leads to the disproportion between material availability and higher demand of graft material therefore synthetic substances are being developed consequently. Synthetic graft is considered as the solution for limited supply of adequate material because it may be produced without being dependent on donors like other types while providing good osteoinductive activity.^{5,9,10}

Main component of bone graft material is hydroxyapatite. It is an inorganic compound identified in the structure of human bone and teeth.¹¹ Hydroxyapatite in the form of graft or scaffold is used as a therapy for bone defect by presenting good biocompatibility, bio-affinity, bioactivity, osteoinductive, osteoconductive and osteointegrative properties.^{6,12} The occurrence of bone destruction will stimulate bone healing process initiated with inflammatory process. Inflammatory process induces the increase of osteoclast activity for bone resorption. By diminishing inflammatory reaction, the activity of osteoclast will decrease thus accelerating new bone formation.¹³ Hydroxyapatite material has no activity as anti-inflammation so that anti-inflammatory effect in bone graft material may be furnished by the addition of ellagic acid (EA). EA is a compound mostly found in pomegranate together with other polyphenols such as gallotannin, anthocyanin and others.¹⁴ A number of researchers revealed that phenolic compound is the major bioactive substance required for bone health. Ellagic acid has been proven to possess anti-inflammatory, antioxidant, free radical scavenging, antiapoptotic, antimutagenic, and antiviral effect in addition to antifibrotic activity. Further to previous study, EA is also confirmed to accelerate bone healing process in rats after tooth extraction.^{15,13,16,17}

EA combination with hydroxyapatite is anticipated to enhance anti-inflammatory activity which may reduce bone resorption and accelerate new bone remodeling. Combination of this material should be identified to be safe

with no disadvantageous effect for tissues in human body.^{18,19} To corroborate this aspect, cytotoxic screening should be performed using BHK-21 fibroblast cell culture originated from hamster kidney. BHK-21 fibroblast cell is used as it is the common cell lines deployed for investigating drug and material toxicity in dental field.²⁰ Toxicological screening in this study exerts *methylthiazol tetrazolium* (MTT) assay method. This method is reported as a valid screening with rapid process. The result of MTT assay will display purplish color in cell culture well after given the reagent. This result is measured by observing the absorbance using spectrophotometer to obtain OD (optical density) value. The value of OD is equivalent to the number of living cell in cell culture well.^{23,24} Toxicological screening of hydroxyapatite combination with EA on BHK-21 fibroblast cell has yet been conducted. Henceforth, a study about the toxicity of hydroxyapatite combination with EA upon fibroblast cell is needed.

5 MATERIALS AND METHODS

This research had been approved by Ethics Committee Faculty of Dentistry Universitas Lambung Mangkurat No. 190/KEPKH-FKGULM/EC/V/2019. This was a true experimental study with post-test only and control group design. Samples were selected randomly and divided into 11 groups comprised of 8 treatment groups and 2 control groups. Eight treatment groups comprised of hydroxyapatite combination with EA at 0.1%, 0.2%, 0.5%, 1%, 2%, 3%, 4% and 5% concentration while two control groups comprised of positive control using hydroxyapatite, cell control and media control. Replication was performed five times per group based on Federer formula. Population in this study was BHK-21 fibroblast cell obtained from LPPT Gajah Mada University.

Bone graft material applied in this study was synthetic hydroxyapatite from *Batan*. Ellagic Acid (EA) used was a pure EA (96%) from pomegranate fruit of *Xi'an Biof Bio-Technology Co., Ltd. China*. EA and hydroxyapatite (HA) were combined based on weight ratio of each material using digital

analytic balance. Combination of material was executed until eight compositions were obtained: (i) 99.9% HA + 0.1%, (ii) 99.8% HA + 0.2% EA, (iii) 99.5% HA + 0.5% EA, (iv) 99% HA + 1% EA, (v) 98% HA + 2% EA, (vi) 97% HA + 3% EA, (vii) 96% HA + 4% EA and (viii) 95% HA + 5% EA.

Fibroblast culture cell in the form of cell line was planted in a bottle. After confluent, culture was collected using *trypsin versene*. The result of collection was taken a little and replanted in eagle media containing 10% bovine serum albumin and incubated for 24 hours. Soon the cell was transferred to a small bottle at 2×10^5 cell/ml solidity; cell was prepared for sample testing. 96-well cell culture plates were deployed for cell viability testing on acrylic resin. The testing was performed based on standardized protocol for MTT assay. In each well, 200 μ l media containing cell at 2×10^5 cell/ml solidity was inserted. Prior to the testing, cell was sterilized using ultraviolet for 15 minutes and subsequently inserted in well plate. Well plate was later incubated for 20 hours at 37°C. Following the incubation, each well was inserted with 20 μ l MTT solved in PBS to be incubated further for 5 hours at 37°C temperature. The sample was collected from each well and each well was added with 200 μ l DMSO using vertical up-down pipetting motion to dissolve formulated crystalline. Well plates were incubated for 5 minutes at 37°C. Further, well plate was measured using spectrophotometer at 620 nm wavelength. The result was obtained in the form of optical density (absorbent). The value of absorbent from each well represents the number of cell viability in media culture.²⁵ Measurement of cell viability was performed using Optical Density formula as follows:^{23,24}

$$\text{Cell viability (\%)} = \frac{\text{OD treatment} - \text{OD media control}}{\text{OD cell control} - \text{OD media control}} \times 100\%$$

Notes:

Cell viability (%): Percentage of living cell after treatment

OD treatment : Optical Density of fibroblast cell in each sample

OD media control : Optical Density of fibroblast cell in media control

OD cell control : Optical Density of cell control without any additional treatment

A material is categorized as non-toxic when the number of living cell or cell viability results greater than 60%.

RESULTS

The result of MTT assay for the toxicological screening of hydroxyapatite combination with EA demonstrates the presence of purplish color in cell culture. Deeper colour demonstrates higher viability of fibroblast cell in the well. Dark purplish colour was observed in positive control group treated with hydroxyapatite only while well-distributed purplish color was observed in all treatment groups.




Figure 1. a. Material with 0.1% EA concentration (61, 6B, 6C, 6D, 6E); b. Material with 0.2% EA concentration (6F, 6G, 6H, 7A, 7B); c. Material with 0.5% EA concentration (7C, 7D, 7E, 7F, 7G); d. Material with 1% EA concentration (7H, 8A, 8B, 8C, 8D); e. Material with 2% EA concentration (8E, 8F, 8G, 8H, 9A); f. Material with 3% EA concentration (9B, 9C, 9D, 9E, 9F); g. Material with 4% EA concentration (9G, 9H, 10A, 10B, 10C); h. Material with 5% EA concentration (10D, 10E, 10F, 10G, 10H); i. Hydroxyapatite as positive control (11A, 11B, 11C, 11D, 11E); j.

Fibroblast as cell control (12A, 12B, 12C, 12D, 12E); k. Media control (11F, 11G, 11H, 12F, 12G, 12H)

Table 1. Viability of BHK-21 fibroblast cell after treatment (%)

Concentration	Fibroblast cell viability (%)
Ellagic Acid 0,1%	88,21
Ellagic Acid 0,2%	92,33
Ellagic Acid 0,5%	97,58
Ellagic Acid 1%	89,56
Ellagic Acid 2%	84,24
Ellagic Acid 3%	90,77
Ellagic Acid 4%	88,92
Ellagic Acid 5%	89,42

Cell viability measurement in table 1 reveals that OD value in all treatment groups were greater than 60%. This may be clarified that all treatment groups exhibit no toxicity.

DISCUSSION

Toxicological screening for bone graft material combination of hydroxyapatite and ellagic acid from pomegranate fruit resulted in non-toxic effect upon fibroblast cell culture after treated with ellagic acid at 0.1%, 0.2%, 0.3%, 0.5%, 1%, 2%, 3%, 4% and 5% concentration. It is based on cell viability value which was scored more than 60% in all groups. The highest viability was observed in 0.5% ellagic acid concentration group with 97.59% OD value while the lowest viability was prevailed in 2% ellagic acid concentration group with 84.24% OD value. This result is in accordance with previous study mentioning that 40% standardized pomegranate fruit extract possessed ideal concentration between 2.5% to 7.5% while topical application of pure ellagic acid (98-100%) on wound healing of rats showed the best result at 1% concentration. Ellagic acid at 1-3% concentration in several studies also demonstrates antitumor, anti-inflammatory and anticancer activity on lung, prostate and brain cancer cells.^{16,26-28}

Previous study claimed that EA exposure on fibroblast and osteoblast cell at viability testing may increase the proliferation of osteoblast and fibroblast cell *in vitro*.²⁹ Other studies also revealed non-toxic property of EA towards RAW264.7 cells which is a progenitor for bone and fibroblast formation.^{30,31} In this study, cell viability was less than 100% showing the presence of cell death that yet to be classified as toxic. This occurs as the result of cytotoxic effect from EA material as it initiates changes in the permeability of fibroblast cell membrane.¹⁹ Damage on cell membrane may cause the cell to be viable and develop into cell death. In non-viable cell, membrane cell shall be penetrated by *trypsine blue* that is hardly occurs in viable cell. The higher the number of non-viable cell, the higher the percentage of cell death. Percent cell death is demonstrated by formazan optical density value where higher formazan optical density value indicates higher number of living cell. This means that BHK-21 fibroblast cell is able to maintain membrane integrity so that cell death may not occur.²³ Percent of cell death in this study is classified in low category inferring that EA is non-toxic towards fibroblast cell.

Low percentage of cell death in this study is generated by EA content which may stimulate the proliferation of fibroblast cell. Ellagic acid contains polyphenols that are largely composed by punicalagin. Punicalagin phenolic compound is reported to improve non-specific immunity through cell activity that regulates immune response. This phenolic compound is also proven to stimulate pulp cell proliferation and accelerate wound healing process.^{19,32} Punicalagin also act as pro-oxidant that increase oxidative stress activity thus initiating apoptosis in carcinoma cell whilst excluding normal cell.^{26,27} Ellagitanin compound at particular level may operate as antioxidant, antibacterial and anti-inflammatory agent. This compound is evinced to be safe for normal cell in limited amount of dosage and intensify wound healing process.^{14,33} From this study, it may be concluded that no toxicity was observed from ellagic acid in pomegranate fruit at 0.1%, 0.2%, 0.5%, 1%, 2%, 3%, 4% and 5% concentration

with hydroxyapatite combination towards BHK-21 fibroblast cells.

REFERENCES

- Riset Kesehatan Dasar (Riskesdas). Badan Penelitian dan Pengembangan. Kementerian Kesehatan Republik Indonesia. Jakarta. 2007. Hal. 112
- Riset Kesehatan Dasar (Riskesdas). Badan Penelitian dan Pengembangan. Kementerian Kesehatan Republik Indonesia. Jakarta. 2013. Hal. 111
- Riset Kesehatan Dasar (Riskesdas). Badan Penelitian dan Pengembangan. Kementerian Kesehatan Republik Indonesia. Jakarta. 2018. Hal. 101-102
- Lan Levegood S, Zhang M. Chitosan-based scaffolds for bone tissue engineering. *Journal Material Chemistry Biomaterial and Biology Med.* 2015; 2(21): 3161–3184.
- Lovati AB, Lopa S, Recordati C, Talò G, Turrisi C, Bottagisio M, et al. In Vivo Bone Formation Within Engineered Hydroxyapatite Scaffolds in a Sheep Model. *Calcified Tissue International Journal.* 2016; 99(2): 209–223.
- Kattimani VS, Kondaka S, Lingamaneni KP. Hydroxyapatite-Past, Present, and Future in Bone Regeneration. *Bone and Tissue Regeneration Insights.* 2016; 7: 9-19
- Polo-Corrales L, Latorre-Esteves M, Ramirez-Vick JE. Scaffold design for bone regeneration. *Journal Nanoscience and Nanotechnology.* 2014;14(1):15–56.
- Hashemi ZS. Tissue Engineering Scaffolds: History, Types and Construction Methods. *Journal of Iran- Iran Anat. Science.* 2011; 9(35): 145–168.
- De Witte T, Fratila-apachitei LE, Zadpoor AA, Peppas NA. Bone tissue engineering via growth factor delivery: from scaffolds to complex matrices. *Regenerative Biomaterial Journal.* 2018; 5(4): 197-211.
- Matsuura A, Kubo T, Doi K, Hayashi K, Morita K, Yokota R. Bone formation ability of carbonate apatite-collagen scaffolds with different carbonate contents. *Dental Material Journal.* 2009; 28(2): 234–42.
- Medina S, Salazar L, Mejía C, Moreno F. In vitro behavior of the dentin and enamel calcium hydroxyapatite in human premolars subjected to high temperatures. *Dyna Journal Universidad Nacional Colombia.* 2016; 83 (195): 34–41.
- Dewi AH, Ana ID. The use of hydroxyapatite bone substitute grafting for alveolar ridge preservation, sinus augmentation, and periodontal bone defect: A systematic review. *Heliyon Journal.* 2018; 4(10): 1-30.
- McKee MD, Pedraza CE, Kaartinen MT. Osteopontin and wound healing in bone. *Cells Tissues Organs Journal.* 2011; 194 (2–4): 313–319.
- Primarizky H, Yuniarti WM, Lukiswanto BS. Ellagic Acid Activity in Healing Process of Incision Wound on Male Albino Rats (*Rattus norvegicus*). *Veterinary Medicine International Journal.* 2018;3(6):224.
- Al-Obaidi MMJ, Al-Bayaty FH, Al Batran R, Hassandarvish P, Rouhollahi E. Protective effect of ellagic acid on healing alveolar bone after tooth extraction in rat - A histological and immunohistochemical study. *Archeve of Oral Biology Journal.* 2014; 59(9): 987–99.
- Yuniarti WM, Primarizky H, Lukiswanto BS. The activity of pomegranate extract standardized 40% ellagic acid during the healing process of incision wounds in albino rats (*Rattus norvegicus*). *Veterinary World Journal.* 2018; 11(3) : 321–326.
- Primarizky H, Yuniarti WM, Lukiswanto BS. Ellagic Acid Activity in Healing Process of Incision Wound on Male Albino Rats (*Rattus norvegicus*). *Veterinary Medicine International Conference KnE life Science.* 2017; 3(6): 224–233.
- Siswadi, Saragih GS. Uji Toksisitas Akut Ekstrak Etanol Kulit Batang Faloak (*Sterculia quadrifida R. Br*) Pada Tikus Sprague-Dawley. *Traditional Medicine Journal.* 2018; 23: 127–134.
- Emilda Y, Budipramana E, Kuntari S. Uji toksisitas ekstrak bawang putih (*Allium Sativum*) terhadap kultur sel fibroblast (*Garlic (Allium Sativum) extract toxicity test on fibroblast cell culture*). 2014; 47(4): 215–219.
- Apriasari ML, Adhani R, Savitri D. Uji Sitotoksitas Ekstrak Metanol Batang Pisang Mauli (*Musa Sp.*) Terhadap Sel Fibroblas Bhk (Baby Hamster Kidney) 21. *Dentino Journal.* 2014; II(2): 214–218.
- Bahuguna A, Khan I, Bajpai VK, Kang SC. MTT assay to evaluate the cytotoxic potential of a drug. *Bangladesh Journal of Pharmacology.* 2017; 12(2): 8.
- Vajrabhaya L, Korsuwannawong S. Cytotoxicity evaluation of a Thai herb using tetrazolium (MTT) and

- sulforhodamine B (SRB) assays. *Journal of Analytic Science and Technology*. 2018; 9(15): 2-6.
23. Freshney RI. *Cytotoxicity: Culture Animal Cells a Manual of Basic Technique*. John Willey and Sons, inc. USA. 2010; 5(10): 359-73.
24. Aslantürk ÖS. In Vitro Cytotoxicity and Cell Viability Assays: Principles, Advantages, and Disadvantages. *Intech Open Journal*. 2018; 1(1): 1-17.
25. Yuliati A. Viabilitas sel fibroblas BHK-21 pada permukaan resin akrilik rapid heat cured (Viability of fibroblast BHK-21 cells to the surface of rapid heat cured acrylic). *Dental Journal (Majalah Kedokteran Gigi)*. 2005; 38(2): 68-72.
26. Li J, Wang G, Hou C, Li J, Luo Y, Li B. Punicalagin and ellagic acid from pomegranate peel induce apoptosis and inhibits proliferation in human HepG2 hepatoma cells through targeting mitochondria. *Food Agric Immunology Journal*. 2019; 30(1): 898-913.
27. Weisburg JH, Schuck AG, Reiss SE, Wolf BJ, Fertel SR, Zuckerbraun HL, et al. Ellagic Acid, a Dietary Polyphenol, Selectively Cytotoxic to HSC-2 Oral Carcinoma Cells. *Anticancer Research Journal*. 2013; 33: 1829-1836.
28. Hussein-al-ali SH, Al-qubaisi M, Rasedee A, Hussein MZ. Evaluation of the Cytotoxic Effect of Ellagic Acid Nanocomposite in Lung Cancer A549 Cell Line and RAW 264.9 Cells. *Journal of Bionanoscience*. 2017;11: 578-83.
29. Al-Obaidi MMJ, Al-Bayaty FH, Batran R Al, Hussaini J, Khor GH. Impact of Ellagic Acid in Bone Formation after Tooth extraction: An Experimental Study on Diabetic Rats. *Scientific World Journal*. 2014; Article no 908098: 1-14.
30. Setiadhi R, Sufiawati I, Zakiawati D, Nur'aeny N, Hidayat W, Firman DR. Evaluation of antibacterial activity and acute toxicity of pomegranate (*punica granatum l.*) seed ethanolic extracts in swiss webster mice. *Journal Dentomaxillofacial Science*. 2017;2(2):119.
31. BenSaad LA, Kim KH, Quah CC, Kim WR, Shahimi M. Anti-inflammatory potential of ellagic acid, gallic acid and punicalagin A&B isolated from *Punica granatum*. *BMC Complementary and Alternative Medicine*. 2017;17(1):1-10.
32. Saldanha E, Joseph N, Ravi R, Kumar A, Shetty V, Fayad R, et al. Polyphenols in the Prevention of Acute Pancreatitis. *Polyphenols in Human Health and Disease Journal*; 2014; 1: 427-433.
33. Usta C, Ozdemir S, Schiariti M, Puddu PE. The pharmacological use of ellagic acid-rich pomegranate fruit. *International Journal of Food Science and Nutrition*. 2013;64(7). p.907-13.

TOXICOLOGICAL SCREENING OF ELLAGIC ACID IN POMEGRANATE FRUIT AND HYDROXYAPATITE COMBINATION AS BONE GRAFT MATERIAL ON BHK-21 FIBROBLAST CELL

ORIGINALITY REPORT

7%

SIMILARITY INDEX

6%

INTERNET SOURCES

4%

PUBLICATIONS

%

STUDENT PAPERS

PRIMARY SOURCES

1	www.semanticscholar.org Internet Source	2%
2	www.thieme-connect.com Internet Source	1%
3	garuda.kemdikbud.go.id Internet Source	1%
4	Deby Kania Tri Putri, Fadel Amirda, Hilman Muzadi, Amy Nindia Carabelly, Isyana Erlita, Rahmiati. " The Antibacterial Activity of Actinomycetes Against the Growth of and ", BIO Web of Conferences, 2020 Publication	1%
5	medic.upm.edu.my Internet Source	1%
6	Sauli Ari Widjaja, Yoshimune Hiratsuka, Koichi Ono, Ima Yustiarini, Nurwasis Nurwasis, Akira Murakami. "Ocular Trauma Trends in Indonesia: Poor Initial Uncorrected Visual	<1%

Acuity Associated with Mechanism of Injury", Open Access Macedonian Journal of Medical Sciences, 2021

Publication

Exclude quotes Off

Exclude matches < 10 words

Exclude bibliography On

TOXICOLOGICAL SCREENING OF ELLAGIC ACID IN POMEGRANATE FRUIT AND HYDROXYAPATITE COMBINATION AS BONE GRAFT MATERIAL ON BHK-21 FIBROBLAST CELL

GRADEMARK REPORT

FINAL GRADE

GENERAL COMMENTS

/0

Instructor

PAGE 1

PAGE 2

PAGE 3

PAGE 4

PAGE 5

PAGE 6
