

Antibacterial power effectiveness of calcium hydroxide and propolis mixture on *Fusobacterium nucleatum* bacteria

by Turnitin Official

Submission date: 08-Apr-2023 11:17PM (UTC+0800)

Submission ID: 2059034976

File name: nal_Skripsi_Agnes_Melinda_Wong_021511133078_English_1-4_b_1.pdf (504.06K)

Word count: 3227

Character count: 16313

Research Report

16

Antibacterial power effectiveness of calcium hydroxide and propolis mixture on *Fusobacterium nucleatum* bacteriaIra Widjiastuti¹, Sukaton¹, Agnes Melinda Wong², Nanik Zubaidah¹¹ Department of Conservative Dentistry, Faculty of Dental Medicine Faculty, Universitas Airlangga, Surabaya, Indonesia² Undergraduate Student of Dental Medicine Faculty, Universitas Airlangga, Surabaya, Indonesia**ABSTRACT**

Background: Calcium hydroxide is a root canal dressing material that is widely used in dentistry because of its ability to regenerate hard tissue and eliminate bacteria. According to Ferreira et al. (2015), *Fusobacterium nucleatum* was found in 90% of teeth that had a root canal treatment done using calcium hydroxide as an intracanal medication. Due to this shortcoming of the antibacterial power of calcium hydroxide, additional research on alternative ingredients that can be combined with calcium hydroxide to improve its antibacterial power is necessary. Propolis is a natural material that has high antibacterial power and has long been used in dentistry. The addition of propolis to calcium hydroxide is expected to improve the antibacterial power of calcium hydroxide without eliminating its function in terms of regenerating hard tissue. **Purpose:** To find out how effective is the antibacterial power of a combination of calcium hydroxide and propolis against *Fusobacterium nucleatum*. **Methods:** The research was carried out using 4 treatment groups consisting of 6 samples for each group. Group 1 is given a combination of calcium hydroxide and propolis with a ratio of 1:1, group 2 with a ratio of 1:1.5, group 3 with a ratio of 1:2, and group 4 is a positive control of calcium hydroxide and sterile aquadest suspension. Each sample was put into a test tube containing BHIB and a suspension of *Fusobacterium nucleatum*, incubated at 37°C for 24 hours, and vortexed for 1 minute. A total of 0.1 ml of bacterial inoculum was taken from each sample and then put into the MHA and grown for 24 hours. The number of *Fusobacterium nucleatum* colonies grown on MHA was calculated and expressed using the Colony Forming Unit (CFU). **Results:** There were fewer colonies of *Fusobacterium nucleatum* in the treatment group compared to the control group. **Conclusion:** The combination of calcium hydroxide and propolis has an effective antibacterial power against *Fusobacterium nucleatum* which the ratio of 1:2 is more effective than ratio of 1:1.5 and 1:1.

Key words: calcium hydroxide, propolis, *Fusobacterium nucleatum*.

Correspondence: Dr. Ira Widjiastuti, drg., M.Kes., Sp.KG (K), Dental Medicine Faculty, Airlangga University, Surabaya – Indonesia, +6287854573451, ira-w@fkg.unair.ac.id

INTRODUCTION

Dental caries is recognized as the main problem of oral health and the main cause of tooth loss¹. Based on the data of Riset Kesehatan Dasar (Riskesdas) in 2013, the prevalence of active caries in the Indonesian population showed a significant percentage of 53.2%. Dental caries refers to local damage of dental hard tissue by acid products as a result of bacterial fermentation of carbohydrate diets, which generally start from enamel to dentine. It is not uncommon for caries on the enamel and dentine to continue to cause pulp necrosis and dental root canal infection as a result of continuous bacterial invasion².

For teeth with pulp necrosis, dental root canal treatment (RCT) is needed which aims to maintain the presence of teeth in the oral cavity with one of the treatment procedures is root canal sterilization with the application of dressing³. The use of dressing material on RCT aims to reduce the number of bacteria and prevent bacterial regrowth, reduce pain, induce hard tissue

regeneration, and reduce tooth apex resorption.³ From many various types of RCT dressing materials, calcium hydroxide is one of the materials widely used in dentistry nowadays².

Calcium hydroxide with the formula $\text{Ca}(\text{OH})_2$ is a strong base with a pH of 12.5-12.8 after contact with solvent media and dissociates into calcium (Ca^{2+}) and hydroxyl ions (OH^-). As a RCT dressing material, Ca^{2+} from $\text{Ca}(\text{OH})_2$ acts to induce the formation of dentine, while OH^- plays a role in increasing pH to be a strong base that can cause bacterial death by damaging its cell wall. These things placed $\text{Ca}(\text{OH})_2$ as the ideal RCT dressing material because it has two main functions that are important for the treated dental root canal, which are regeneration of dental hard tissue and elimination of bacteria⁴. However, the antibacterial power of $\text{Ca}(\text{OH})_2$ was declared weakened as the pH decreased which occurred some time after $\text{Ca}(\text{OH})_2$ was dissociated⁵. The weakness of the antibacterial power of $\text{Ca}(\text{OH})_2$ is proven through research conducted by Ferreira et al. (2015) which showed that *Fusobacterium nucleatum* was

found with a percentage of 90% in teeth with RCT with $\text{Ca}(\text{OH})_2$ as an intracanal medication⁷.

Fusobacterium nucleatum is a rod-shaped or spindle Gram-negative bacterium, anaerobic, non-motile, has little fimbriae or pili, does not form spores⁸. *F. nucleatum* was found as one of the Gram-negative bacteria found in teeth with pulp necrosis and root canal infection, supported by studies conducted by Fabris et al. (2014) which showed that *F. nucleatum* was found in as many as 25% in 88 of 103 dental samples that had pulp necrosis. This species has been shown to be able to survive even after the root canal of the tooth is permanently filled with sealers and gutta percha⁹.

The weakness of the antibacterial power of $\text{Ca}(\text{OH})_2$ requires research related to other material that can be combined with $\text{Ca}(\text{OH})_2$ to increase its antibacterial power without reducing the ability to regenerate dental hard tissue. Propolis is a natural substance which can be combined with $\text{Ca}(\text{OH})_2$ without causing toxicity. Propolis is a resin substrate, collected by bees from leaf buds and plant bark mixed with enzymes and wax from honeycomb. Various contents of propolis include vitamins (A, B, and C), minerals (Ca, Mg, Na, Fe, Mn, Cu, and Zn), succinate dehydrogenase enzymes, as well as various active substances namely polyphenols (flavonoids, phenolic acids, and esters), terpenoids, steroids, and amino acids¹⁰. Biological and pharmacological activities of broad-spectrum propolis with their role as antibacterial, antiviral, antioxidant, anti-inflammatory, antifungal, antiprotozoal, anesthetic, antitoxic, immuno-stimulator, anti-tumor and healing¹¹.

Various advantages of propolis are expected to be able to improve the lack of $\text{Ca}(\text{OH})_2$ antibacterial power so that the research is conducted to determine the effectiveness of the antibacterial combination of calcium hydroxide and propolis against the *Fusobacterium nucleatum* bacteria.

MATERIALS AND METHODS

This study was a laboratory experimental study using *Fusobacterium nucleatum* ATCC 25586 as the study sample. The number of samples is determined by calculating the Federer formula so that this study uses 6 samples for each treatment.

The study was initiated by creating a culture of *Fusobacterium nucleatum* ATCC 25586, started by taking a bacterial culture using osseous wire and put it into a test tube containing 5 ml of Brain Heart Infusion Broth (BHIB) then incubating it in an anaerobic jar at 37°C for 24 hours. The *F. nucleatum* culture that had grown on BHIB was then standardized with 0.5 Mc Farland.

Besides preparing bacterial samples, a combination of $\text{Ca}(\text{OH})_2$ and propolis prepared with a ratio of 1:1 which consist of 0.125 g of $\text{Ca}(\text{OH})_2$ powder and 0.125

ml of propolis extract, a ratio of 1:1.5 consist of 0.125 g of $\text{Ca}(\text{OH})_2$ powder and 0.1875 ml of propolis extract, a ratio of 1:2 consist of 0.125 g of $\text{Ca}(\text{OH})_2$ powder and 0.25 ml of propolis extract, and as a control group which is the mixture of $\text{Ca}(\text{OH})_2$ powder with sterile distilled water.

After preparing the research material, four test tubes were provided; the first tube contains 5 ml BHIB + 0.1 ml of *Fusobacterium nucleatum* ATCC 25586 + combination of $\text{Ca}(\text{OH})_2$ and propolis 1:1; the second tube contains 5 ml BHIB + 0.1 ml of *Fusobacterium nucleatum* ATCC 25586 + combination of $\text{Ca}(\text{OH})_2$ and propolis 1:1.5; the third tube contains 5 ml BHIB + 0.1 ml of *Fusobacterium nucleatum* ATCC 25586 + combination of $\text{Ca}(\text{OH})_2$ and propolis 1:2; and the fourth tube as a positive control containing 5 ml BHIB + 0.1 ml of *Fusobacterium nucleatum* ATCC 25586 + $\text{Ca}(\text{OH})_2$ suspension. The four tubes were incubated in anaerobic jar at 37°C for 24 hours, then vortexed for 1 minute. The cultures of *Fusobacterium nucleatum* ATCC 25586 in the four tubes were taken as much as 0.1 ml of bacterial inoculum using a micropipette, then flattened on a petridisk containing Muller Hinton Agar (MHA) media by spreading. The petridisk is then incubated in anaerobic jar at 37°C for 24 hours. After incubation, an observation of the number of colonies grown on MHA was carried out and calculations with the Colony Forming Unit (CFU). The results data were then analyzed by the Kolmogorov-Smirnov Test, Levene's Test, One Way ANOVA, and Tukey HSD Post-Hoc Test.

RESULTS

The results of the study in the form of the number of *Fusobacterium nucleatum* bacteria colonies in MHA shown in Table 1.

Table 1. Mean values and standard deviations for the number of colonies of *Fusobacterium nucleatum* bacteria

Groups	N	Mean (colony)	Std. Deviation
Positive Control	6	105,50 CFU/ml	3,728
I	6	54,00 CFU/ml	2,280
II	6	28,17 CFU/ml	1,472
III	6	14,17 CFU/ml	1,472

Table description:

- Positive control = $\text{Ca}(\text{OH})_2$ - aquadest sterile
- Group I = combination of $\text{Ca}(\text{OH})_2$ - propolis 1:1
- Group II = combination of $\text{Ca}(\text{OH})_2$ - propolis 1:1.5
- Group III = combination of $\text{Ca}(\text{OH})_2$ - propolis 1:2

Based on the results of the study, it was found that the average number of *F. nucleatum* colonies in the treatment group was lower than the control group. The number of *F. nucleatum* colonies decreased along with the increasing composition of propolis extract in its

combination with $\text{Ca}(\text{OH})_2$, as seen that the mean quantity of *F. nucleatum* colonies in group III was 14.17 CFU/ml counted lower than group II which was 28.17 CFU/ml; the mean quantity of *F. nucleatum* colonies in group II was 28.17 CFU/ml counted lower than group I which was 54.00 CFU/ml; and colonies in group I amounted to 54.00 CFU/ml counted lower than the control group which was 105.50 CFU/ml. This means that the decrease in the number of *F. nucleatum* colonies is inversely proportional to the increase of propolis extract composition in its combination with $\text{Ca}(\text{OH})_2$. The lowest number of *F. nucleatum* colonies among the three treatment groups was in group III with a combination of $\text{Ca}(\text{OH})_2$ and propolis 1: 2.




Figure 1. One of the six sample results

Normality tests were carried out in each research group using the Kolmogorov-Smirnov Test to see data distribution. The results of the normality test show a value of $p>0.05$ in all study groups which means that the data obtained from the results of the study are normally distributed. Next, the data variance homogeneity test was carried out in each study group using Levene's Test. Based on the results of the homogeneity test, obtained $p>0.05$ which is $p=0.138$ which means that the data variance is homogeneous.

After the normality and homogeneity of the data are met, the One Way ANOVA test is carried out to determine the difference in the calculated average across all sample groups. From the existing data, the results obtained $p<0.05$, namely $p=0.000$, which means that each treatment group has a significant difference.

Table 2. Data on the results of the Tukey HSD test

	Positive Control	I	II	III
Positive Control	-	$p = 0.000^*$	$p = 0.000^*$	$p = 0.000^*$

I		-	$p = 0,000^*$	$p = 0,000^*$
II			-	$p = 0,000^*$
III				-

Table description :

- Positive control = $\text{Ca}(\text{OH})_2$ - sterile distilled water
 - Group I = combination of $\text{Ca}(\text{OH})_2$ - propolis 1:1
 - Group II = combination of $\text{Ca}(\text{OH})_2$ - propolis 1:1.5
 - Group III = combination of $\text{Ca}(\text{OH})_2$ - propolis 1:2
- * significant difference (for $p<0.05$)

Data analysis was ended by looking at a comparison between samples using the Honestly Significant Difference (Tukey HSD) Test to determine whether or not there were significant differences between sample groups, as shown in Table 2.

DISCUSSION

The results showed that the addition of propolis to $\text{Ca}(\text{OH})_2$ was able to kill and inhibit colonization of *F. nucleatum* better than $\text{Ca}(\text{OH})_2$ without propolis. It was evident that the number of colonization of *F. nucleatum* in the control group was greater than in the three treatment groups of the combination of $\text{Ca}(\text{OH})_2$ and propolis. In addition, it was proven that the number of *F. nucleatum* colonies was inversely proportional to propolis extract composition in its combination with $\text{Ca}(\text{OH})_2$. These results can occur because in the combination of $\text{Ca}(\text{OH})_2$ and propolis, calcium salt compounds are formed with its active compounds derived from propolis extracts such as flavonoids, terpenoids and tannins (Leo, 2017). In the combination of $\text{Ca}(\text{OH})_2$ and propolis 1:2, there are more flavonoids, terpenoids and tannins than the combination of 1:1.5; as well as the combination of $\text{Ca}(\text{OH})_2$ and propolis 1:1.5 which contains more flavonoids, terpenoids and tannins when compared with a 1:1 combination as tested through phytochemical tests that were first carried out. Each active compound such as flavonoids, terpenoids and tannins has antibacterial power so that the more active content of the compound means the higher the antibacterial power, the less the number of colonies of bacteria formed¹²⁻¹⁴.

According to Cushnie and Lamb (2005), flavonoids show antibacterial action through three main mechanisms, namely by inhibiting nucleic acid synthesis, function of cytoplasmic membranes and bacterial energy metabolism¹². Kumar and Pandey (2013) also explained that flavonoids work as antibacterial through several cellular targets, more than one specific action. Molecular actions of flavonoids include forming complexes with bacterial cell proteins through nonspecific forces such as hydrogen bonds and hydrophobic effects, and by the formation of covalent bonds. The main performance of flavonoids is seen through ring B on flavonoids which

play a role in hydrogen bonds with nucleic acid base structures in bacteria so that bacterial DNA and RNA synthesis is inhibited. The bond between flavonoids and bacterial cells will then deactivate the properties of microbial adhesin, enzymes, cell transport proteins, and so on related to the living needs of bacterial cells which will further inhibit their development to result in bacterial cell death¹⁵.

Terpenoids through sesquiterpenoid tt-farnesol work by increasing proton permeability in bacterial cell membranes which results in damage to the bacterial barrier membrane function. Damage to the function of bacterial membranes causes the diffusion of excess fluid into bacterial cells until the cell undergoes lysis¹³.

In addition to flavonoids and terpenoids, tannins also have antibacterial power through the action of catechins that are able to penetrate and interact with lipid bilayers, causing fusion of bacterial cell membranes, a process that results in material leakage and cell intramembrane aggregation which will further cause bacterial cell death¹⁴.

Various performance of propolis active compounds shows that propolis has good antibacterial power, in addition to its role as a carrier of Ca²⁺ and OH ions resulted from the dissociation of Ca(OH)₂ when both are combined. The antibacterial power of propolis combined with Ca(OH)₂ was proven to be valid for *F. nucleatum* bacteria as seen through the results of research that showed that the treatment group with a combination of Ca(OH)₂ and propolis left fewer *F. nucleatum* bacteria colonies compared to the control group namely Ca(OH)₂ without propolis.

Based on the results of this research, concluded that the combination of Ca(OH)₂ and propolis has an effective antibacterial effect on *F. nucleatum* with a ratio of 1:2 is more effective compared to 1:1.5 and 1:1. Therefore, a combination of Ca(OH)₂ and propolis in a ratio of 1:2 can be further developed to be used later as an intracanal medication, in this case the dental root canal dressing, so that more optimal bacterial elimination occurs which simultaneously stimulates the regeneration of dental hard tissue.

REFERENCES

1. Yadav K, Prakash S. Dental caries: A Review. *Asian J Biomed Pharm Sci.* 2016; 6(53):01-07. doi:10.15272/ajbps.v6i53.773
2. Torabinejad M, Walton RE. *Endodontics Principles and Practice*. 4th ed. (Saunders, ed.). Missouri: Elsevier Ltd; 2009.
3. Löst C. Quality guidelines for endodontic treatment: Consensus report of the European Society of Endodontontology. *Int Endod J.* 2006; 39(12):921-930. doi:10.1111/j.1365-2591.2006.01180.x
4. Kim D, Kim E. Antimicrobial effect of calcium hydroxide as an intracanal medicament in root canal treatment: a literature review - Part I. In vitro studies. *Restor Dent Endod.* 2014; 39(4):241. doi:10.5395/rde.2014.39.4.241
5. Siqueira JF, Lopes HP. Mechanisms of antimicrobial activity of calcium hydroxide: A critical review. *Int Endod J.* 2009; 32(5):361-369. doi:10.1046/j.1365-2591.1999.00275.x
6. Ferreira NS, Martinho Frederico C, Cardoso FG, Nascimento GG, Carvalho CA., Valera MC. Microbiological Profile Resistant to Different Intracanal Medications in Primary Endodontic Infections. *Am Assoc Endodontists.* 2015; 41(6):824-830. doi:10.1016/j.ijhydene.2015.04.002
7. Ferreira NS, Martinho FC, Cardoso FGR, Nascimento GG, Carvalho AT, Valera MC. Microbiological Profile Resistant to Different Intracanal Medications in Primary Endodontic Infections. 2015; 41(6). doi:10.1016/j.joen.2015.10.031
8. He Z, Huang Z, Zhou W, Tang Z, Ma R, Liang J. Antibiofilm Activities from Resveratrol against: Fusobacterium nucleatum. *Front Microbiol.* 2016; 7(JUL):1-9. doi:10.3389/fmicb.2016.01065
9. Fabris AS, Nakano V, Avila-Campos MJ. Bacteriological analysis of necrotic pulp and fistulae in primary teeth. *J Appl Oral Sci.* 2014; 22(2):118-124. doi:10.1590/1678-775720130358
10. Halim E, Hardinsyah, Sutandyo N, Sulaeman A, Artika M, Harahap Y. Kajian Bioaktif dan Zat Gizi Propolis Indonesia dan Brasil. *J Gizi dan Pangan.* 2012; 7(1):1-6.
11. Piana T, Gesteira MDFM, Carvalho E dos S, et al. Evaluation of the antimicrobial effect of calcium hydroxide combined to different vehicles. *Rev Odonto Ciência.* 2016; 31(2):89-94.
12. Cushnie TPT, Lamb AJ. Antimicrobial activity of flavonoids. *Int J Antimicrob Agents.* 2005; 26(5):343-356. doi:10.1016/j.ijantimicag.2005.09.002
13. Jeon J, Pandit S, Xiao J, et al. Influences of trans-trans farnesol, a membrane-targeting sesquiterpenoid, on *Streptococcus mutans* physiology and survival within mixed-species oral biofilms. *Int J Oral Sci.* 2011; 3(2):98-106. doi:10.4248/IJOS11038
14. Slobodníková L, Fialová S, Rendeková K, Kováč J, Mučaiji P. Antibiofilm Activity of Plant Polyphenols. *Molecules.* 2016; 21(12):1-15. doi:10.3390/molecules21121717
15. Kumar S, Pandey AK. Chemistry and Biological Activities of Flavonoids: An Overview. 2013; 2013(February 2014):1-16. doi:10.1155/2013/162750

Antibacterial power effectiveness of calcium hydroxide and propolis mixture on *Fusobacterium nucleatum* bacteria

ORIGINALITY REPORT



PRIMARY SOURCES

- | | | |
|---|---|----|
| 1 | www.ncbi.nlm.nih.gov
Internet Source | 3% |
| 2 | Retno Pudji Rahayu, Nirawati Pribadi, Ira Widjiastuti, Nur Ariska Nugrahani.
"Combinations of propolis and Ca(OH)2 in dental pulp capping treatment for the stimulation of reparative dentin formation in a rat model", F1000Research, 2020
Publication | 2% |
| 3 | scitepress.org
Internet Source | 2% |
| 4 | Ainun Fitriani. "Pengaruh Model Brain Based Learning Ditinjau dari Kemampuan Berpikir Kritis Siswa", JURNAL PENDIDIKAN MIPA, 2019
Publication | 1% |
| 5 | Submitted to Universitas Airlangga
Student Paper | 1% |
| 6 | ijcpd.com
Internet Source | 1% |

- 7 medcraveonline.com 1 %
Internet Source
-
- 8 Cruz, R.M.. "Histologic evaluation of periradicular tissues in dogs treated with calcium hydroxide in combination with HCT20 and camphorated P-chloropheno", Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology and Endodontology, 200510 1 %
Publication
-
- 9 worldwidescience.org 1 %
Internet Source
-
- 10 www.sid.ir 1 %
Internet Source
-
- 11 AlMaha S. AlGazlan, Sayed H. Auda, Hanan Balto, Fahd Alsalleeh. "Antibiofilm Efficacy of Silver Nanoparticles Alone or Mixed with Calcium Hydroxide as Intracanal Medicaments: An Ex-Vivo Analysis", Journal of Endodontics, 2022 1 %
Publication
-
- 12 Lívia Slobodníková, Silvia Fialová, Katarína Rendeková, Ján Kováč, Pavel Mučaji. "Antibiofilm Activity of Plant Polyphenols", Molecules, 2016 1 %
Publication
-
- 13 Wang, C.S.. "Effect of Intracanal Medicament on the Sealing Ability of Root Canals Filled 1 %

with Resilon", Journal of Endodontics, 200606

Publication

14

S H Noer, P Gunowibowo. "Scientific Learning and Its Contributions to Increase the Student's Self Confidence and Learning Outcomes", Journal of Physics: Conference Series, 2019

Publication

1 %

15

Bijaya Chingtham, Langpoklakpam Chaoba Singh, Saraswathi Ramakrishna, Rahul Jain, Anita Gurung. "A Comparative Study on Three Different Combinations of Ketofol for Induction of General Anaesthesia", Journal of Evolution of Medical and Dental Sciences, 2021

Publication

1 %

16

"Abstracts of the ESE Wladimir Adlivankine Research Prize and Original Scientific Posters", International Endodontic Journal, 2014.

Publication

<1 %

17

Paulo W.P. Gomes, Thaiana C.D.L. Pamplona, Kely C. Navegantes-Lima, Lucas B.G. Quadros et al. "Chemical composition and antibacterial action of Stryphnodendron pulcherrimum bark extract, "barbatimão" species: evaluation of its use as a topical agent", Arabian Journal of Chemistry, 2021

Publication

<1 %

18	literatur.thuenen.de Internet Source	<1 %
19	www.frontiersin.org Internet Source	<1 %
20	B. P. F. A. Gomes. "Effectiveness of 2% chlorhexidine gel and calcium hydroxide against Enterococcus faecalis in bovine root dentine in vitro", International Endodontic Journal, 4/2003 Publication	<1 %
21	Basrani, B.. "Efficacy of chlorhexidine- and calcium hydroxide-containing medicaments against Enterococcus faecalis in vitro", Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology and Endodontontology, 200311 Publication	<1 %
22	www.jpda.com.pk Internet Source	<1 %

Exclude quotes Off
Exclude bibliography On

Exclude matches < 10 words

Antibacterial power effectiveness of calcium hydroxide and propolis mixture on *Fusobacterium nucleatum* bacteria

GRADEMARK REPORT

FINAL GRADE

/0

GENERAL COMMENTS

Instructor

PAGE 1

PAGE 2

PAGE 3

PAGE 4
