

BUKTI KORESPONDENSI
Jurnal Internasional Bereputasi

Judul Artikel : Property Test of Phosphate and Hydroxyl Groups from Lates Carcarifer Fish Scale as a Candidate for Synthetic Hydroxyapatite using the FTIR Method.

Penulis : **Dian Agustin Wahjuningrum***, Setyabudi, Anuj Bhardwaj, Syania Edinda Febriyanti, Nadia Liliani Soetjipta, Latief Mooduto

Jurnal : Journal of International Dental and Medical Research
Vol.14 No.2, p. 489-493

Penerbit : Ektodermal Displazi Grubu

1	Manuscript was submitted to Journal “ Journal of International Dental and Medical Research ” (ID: D20_1363)	Received: 03 Desember 2020
	Your manuscript entitled " Property Test Of Phosphate And Hydroxyl Groups From Lates Carcarifer Fish Scale As A Candidate For Synthetic Hydroxyapatite Using The Ftir Method " has been successfully submitted to the JIDMR by e-mail and will be considered for publication in “Journal of International Dental and Medical Research”.	
2	Revision needs (ID: D20_1363)	Received: 31 Desember 2020
	Your article looks well designed which titled " Property Test Of Phosphate And Hydroxyl Groups From Lates Carcarifer Fish Scale As A Candidate For Synthetic Hydroxyapatite Using The Ftir Method ", but it should be revise especially references section according to the JIDMR guideline http://www.jidmr.com/journal/author-guidelines/ .	
5	Decision: Accepted for Publication	10 Januari 2021
6	Published online	23 Februari 2021
7	Published on Journal of International Dental and Medical Research Vol.14 No.2, p. 489-493.	04 Juli 2021

D20_1363_DIAN_AGUSTIN_WAHJUNINGRUM_Indonesia / Submission confirmation

1 pesan

izzet yavuz <izzetyavuz@hotmail.com>

3 Desember 2020 23.37

Kepada: agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>

Dear Prof. Dr. Dian Agustin Wahjuningrum,

Your manuscript entitled " **PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM Lates carcarifer FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYAPATITE USING THE FTIR METHOD** " has been successfully submitted to the JIDMR by e-mail and will be considered for publication in "**Journal of International Dental and Medical Research**".

We are sending your article for a peer-review and when we receive an evaluation we will inform you.

Thank for considering the manuscript for submission to the **Journal of International Dental and Medical Research**.

Please feel free to contact me with any questions or concerns.

Best Regards,

Prof. Dr. Izzet YAVUZ

Editor-in-Chief and General Director

Journal of International Dental and Medical Research ISSN 1309 - 100X

<http://www.jidmr.com/journal/>

MSc, PhD, Professor, Pediatric Dentistry

Dicle University, Faculty of Dentistry

21280 Diyarbakir, TURKEY

E-mail: izzetyavuz@hotmail.com, iyavuz@dicle.edu.tr

ECTODERMAL DYSPLASIA GROUP - TURKEY

<http://www.ektodermaldisplazi.com>

Gönderen: agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>

Gönderildi: 3 Aralık 2020 Perşembe 16:38

Kime: izzet yavuz <izzetyavuz@hotmail.com>

Konu: Submit

Dear Prof Izzet,

I would like to publish in JIDMR. I attach manuscript also transfer of copyright.

Thank you so much for your support

Warm regards

Dian

D20_1363_DIAN_AGUSTIN_WAHJUNINGRUM_Indonesia / Revision needs

4 pesan

izzet yavuz <izzetyavuz@hotmail.com>
Kepada: agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>

31 Desember 2020 03.40

Dear Prof. Dr. DIAN AGUSTIN WAHJUNINGRUM,

Your article looks well designed which titled " **PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM Lates carcarifer FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYAPATITE USING THE FTIR METHOD** ", but it should be revise especially references section according to the JIDMR guideline <http://www.jidmr.com/journal/author-guidelines/> .

Referencess citations should be at the and upside of sentences without brackets as a numerically superscript.

All of the references section should be unique with a same character (Year; volume(No): page number).

Improve to the article with recently published articles, which some of reference samples are below, they are full text open access, at least 15 referencess should has your article which recently published.

It will be welcome if you cite some of them in your article.

After the revisions you can submit your paper.

Sincerely yours.

- 1. Effect of Yellowfin Tuna Bone Derived Hydroxyapatite on Hela and Vero Cell Line Proliferation**
Tetiana Haniastuti, Ananda Mutiara Wening, Firda Arifatul Faqiha, Dian Az Zahra
[Journal of International Dental and Medical Research 2020; 13 \(4\)](#)
Pages 1299-1303
- 2. Enhancement of Osteogenesis Using a Combination of Hydroxyapatite and Stem Cells from Exfoliated Deciduous Teeth**
Chiquita Prahasanti, Agung Krismariono, Rifiana Takanamita, I Komang Evan Wijaksana, Ketut Suardita, Tania Saskianti, Diah Savitri Ernawati
[Journal of International Dental and Medical Research 2020; 13 \(2\)](#)
Pages 508-512
- 3. Fabrication of Chitosan-Chondroitin Sulfate/Hydroxyapatite Composite Scaffold by Freeze Drying Method**
Aminatun, Yunita Indriani, Dyah Hikmawati
[Journal of International Dental and Medical Research 2019; 12 \(4\)](#)
Pages 1355-1362
- 4. Carbonate Hydroxyapatite-Hyaluronic Acid as Bone Healing Accelerator: in-vitro and in-vivo Studies on the Alveolar Bone of Wistar Rats**
Ernie Maduratna Setiawatie, Prihartini Widiyanti, Muhammad Ryan, Muhammad Rubianto
[Journal of International Dental and Medical Research 2019; 12 \(4\)](#)
Pages 1280-1286

D20_1363_DIAN_AGUSTIN_WAHJUNINGRUM_Indonesia / Accept letter

2 pesan

izzet yavuz <izzetyavuz@hotmail.com>

10 Januari 2021 20.00

Kepada: agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>

Subject: Your article has been accepted for Publication. (**DIAN AGUSTIN WAHJUNINGRUM, SETYABUDI, ANUJ BHARDWAJ, SYANIA EDINDA FEBRIYANTI, NADIA LILIANI SOETJIPTA, LATIEF MOODUTO, "PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM Lates carcarifer FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYPATITE USING THE FTIR METHOD"**)

Dear Prof. Dr. DIAN AGUSTIN WAHJUNINGRUM,

It's a great pleasure for me to inform you that your manuscript which titled "**PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM Lates carcarifer FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYPATITE USING THE FTIR METHOD**" has been accepted and will be finalized for **issue 2021; volume 14 number 1** which will be released either late March 2021 or early April 2021.

Send us Transfer of Copyright Agreement) please, it is necessarily before sending manuscript to press <http://www.jidmr.com/journal/>, http://www.ektodermaldisplazi.com/journal/documents/Transfer_of_Copyright_Agreement.doc.

Before sending manuscript to press, I will send to you the press ready copy for your final checking.

Sincerely yours.

Open access and publication process charges for your article is ~~750 US\$~~, **600 US\$**.

Please complete to the publication process for your accepted article.

Sincerely yours.

1- By bank transfer to the my account (as ~~750 US\$~~, **600 US\$).**

Please carefully fill in transaction form and indicate at the "Remittance Information" section over the transaction or swift bill (pay slip) section to the; Full Account Beneficiary Name, Account IBAN number and **your article ID number .**

Please inform JIDMR money order date when you did.

FINANCIAL INSTITUTION Vakıf Bank	BANK CODE/ABA # Vakıf Bank 015
BRANCH Dicle Üniversitesi (Diyarbakir)(S0527)Bağlı Şube	ACCOUNT HOLDER / BENEFICIARY NAME# izzet yavuz
CITY/STATE/ZIP/COUNTRY	SWIFT CODE TVBATR2A BIC CODE XXX
	IBAN / ACCOUNT NUMBER #

5. **Characterization and Degradation of Hydroxyapatite Gypsum Puger (HAGP) Freeze Dried Scaffold as a Graft Material for Preservation of the Alveolar Bone Socket**

Amiyatun Naini, I Ketut Sudiana, Mohamad Rubianto, Ferdiansyah, Nandang Mufti

[Journal of International Dental and Medical Research 2018; 11 \(2\)](#)

Pages 532-536

6. **Potential Proliferation of Stem Cell from Human Exfoliated Deciduous Teeth (SHED) in Carbonate Apatite and Hydroxyapatite Scaffold**

Tania Saskianti, Rianita Ramadhani, Els S Budipramana, Seno Pradopo, Ketut Suardita

[Journal of International Dental and Medical Research 2017; 10 \(2\)](#)

Pages 350-353

7. **The Profile of Crosslinked Bovine Hydroxyapatite Gelatin Chitosan Scaffolds with 0.25% Glutaraldehyde**

Anita Yuliati, Nadia Kartikasari, Elly Munadziroh, Devi Rianti

[Journal of International Dental and Medical Research 2017; 10 \(1\)](#)

Pages 151-155

Prof. Dr. Izzet YAVUZ

Editor-in-Chief and General Director

Journal of International Dental and Medical Research ISSN 1309 - 100X

<http://www.jidmr.com/journal/>

MSc, PhD, Professor, Pediatric Dentistry

Dicle University, Faculty of Dentistry

21280 Diyarbakir, TURKEY

E-mail: izzetyavuz@hotmail.com, iyavuz@dicle.edu.tr

ECTODERMAL DYSPLASIA GROUP - TURKEY

<http://www.ektodermaldisplazi.com>

agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>
Kepada: syaniaef@gmail.com

7 Januari 2021 10.59

[Kutipan teks disembunyikan]

Syania Edinda <syaniaef@gmail.com>
Kepada: agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>

9 Januari 2021 19.28

Berikut saya lampirkan revisi manuscript JIDMR

[Kutipan teks disembunyikan]

 **MANUSCRIPT JIDMR NEW VERSION.docx**
548K

agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>
Kepada: izzet yavuz <izzetyavuz@hotmail.com>

9 Januari 2021 19.43

Dear Prof. Izzet Yavuz

Thank you so much for your support. I already fix and adding references from your suggestion.

Warm regards

Dian

[Kutipan teks disembunyikan]

 **MANUSCRIPT JIDMR NEW VERSION.docx**
548K

D20_1363_DIAN_AGUSTIN_WAHJUNINGRUM_Indonesia

1 pesan

izzet yavuz <izzetyavuz@hotmail.com>

23 Februari 2021 18.36

Kepada: "dian-agustin-w@fkg.unair.ac.id" <dian-agustin-w@fkg.unair.ac.id>

Dear **Prof. Dr. DIAN AGUSTIN WAHJUNINGRUM,**

Thank you very much for complete to the publication process.

Your article "**PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM Lates carcarifer FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYAPATITE USING THE FTIR METHOD**", will be published at the for **issue 2021; volume 14 number 2** which will be released either late June 2021 or early July 2021.

Before sending manuscript to press, I will send to you the press ready copy for your final checking.

Sincerely yours.

Prof. Dr. Izzet YAVUZ

Editor-in-Chief and General Director

Journal of International Dental and Medical Research ISSN 1309 - 100X

<http://www.jidmr.com/journal/>

MSc, PhD, Professor, Pediatric Dentistry

Dicle University, Faculty of Dentistry

21280 Diyarbakir, TURKEY

E-mail: izzetyavuz@hotmail.com, iyavuz@dicle.edu.tr

ECTODERMAL DYSPLASIA GROUP - TURKEY

<http://www.ektodermaldisplazi.com>

2- By Western Union (as an ~~750 US\$,~~ 600 US\$.

Please indicate;_

Please inform me money order date and others which is below when you did.

Under the next day payment

The country the money was sent from:

The name of the sender:

The amount:

Money Transfer Control Number (MTCN):

Prof. Dr. Izzet YAVUZ

Editor-in-Chief and General Director

Journal of International Dental and Medical Research ISSN 1309 - 100X

<http://www.jidmr.com/journal/>

MSc, PhD, Professor, Pediatric Dentistry

Dicle University, Faculty of Dentistry

21280 Diyarbakir, TURKEY

E-mail: izzetyavuz@hotmail.com, iyavuz@dicle.edu.tr

ECTODERMAL DYSPLASIA GROUP - TURKEY

<http://www.ektodermaldisplazi.com>



1235 Accept letter for paper D20_1363_DIAN_AGUSTIN_WAHJUNINGRUM_Indonesia.doc
401K

agustin wahjuningrum Dian <dian-agustin-w@fkg.unair.ac.id>

10 Januari 2021 20.53

Kepada: izzet yavuz <izzetyavuz@hotmail.com>

Dear Prof Izzet Yavuz

Thank you so much... I will processing APC as soon as possible..

Warm regards

Dian

[Kutipan teks disembunyikan]



JIDMR

10 / January / 2021

No: JIDMR / 2021.1235

Subject: Your article has been accepted for Publication. (**DIAN AGUSTIN WAHJUNINGRUM, SETYABUDI, ANUJ BHARDWAJ, SYANIA EDINDA FEBRIYANTI, NADIA LILIANI SOETJIPTA, LATIEF MOODUTO, "PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM Lates carcarifer FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYAPATITE USING THE FTIR METHOD"**)

Dear Prof. Dr. DIAN AGUSTIN WAHJUNINGRUM,

It's a great pleasure for me to inform you that your manuscript which titled **"PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM Lates carcarifer FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYAPATITE USING THE FTIR METHOD"** has been accepted and will be finalized for **issue 2021; volume 14 number 1** which will be released either late March 2021 or early April 2021.

Send us Transfer of Copyright Agreement please, it is necessarily before sending manuscript to press <http://www.jidmr.com/journal/>, http://www.ektodermaldisplazi.com/journal/documents/Transfer_of_Copyright_Agreement.doc.

Before sending manuscript to press, I will send to you the press ready copy for your final checking.

Sincerely yours.

Prof. Dr. Izzet YAVUZ

Editor-in-Chief and General Director of J Int Dent Med Res

J Int Dent Med Res
1309-100X

ISSN

Publisher: Ectodermal Displasia Group-Turkey

Corresponding Adress: Prof. Dr. izzet YAVUZ, Dicle University, Faculty of Dentistry, 21280 Diyarbakir / TURKEY.

Web page: <https://www.jidmr.com/>

E-mail: izzetyavuz@hotmail.com ; iyavuz@dicle.edu.tr

Phone: +90 412 241 10

17 / 3404 , Fax: +90 412 248 81 00

PROPERTY TEST OF PHOSPHATE AND HYDROXYL GROUPS FROM *Lates calcarifer* FISH SCALE AS A CANDIDATE FOR SYNTHETIC HYDROXYAPATITE USING THE FTIR METHOD

DIAN AGUSTIN WAHJUNINGRUM¹, SETYABUDI¹, ANUJ BHARDWAJ^{2,3}, SYANIA EDINDA FEBRIYANTI⁴, NADIA LILIANI SOETJIPTA⁵, LATIEF MOODUTO¹

1 Department of Conservative Dentistry, Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia.

2 Department of Conservative Dentistry and Endodontics, College of Dental Science and hospital, Indore, India

3 Adjunct Professor at Department of Conservative Dentistry, Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia.

4 Undergraduate Student of Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia.

5 Postgraduate Student of Department of Conservative Dentistry, Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia

Corresponding Author: Dian Agustin Wahjuningrum
Lecturer, Department of Conservative Dentistry, Faculty of Dental Medicine, Airlangga University

Dental Medicine Faculty of Airlangga University
St. Mayjen Prof. Dr. Moestopo No. 47, Surabaya, Indonesia
Tel. +62 315-030-255
E-mail: dian-agustin-w@fkg.unair.ac.id

Abstract

Background: In Indonesia, the market price of Synthetic hydroxyapatite, $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ reaches 1.5 million per 5 milligrams and its availability still depends on imported products. To solve this problem, alternative materials can be used, such as *Lates calcarifer* fish scales. Phosphate (PO_4)³⁻ and hydroxyl (-OH) groups are functional groups of synthetic hydroxyapatites. The presence of phosphate (PO_4)³⁻ and hydroxyl (-OH) groups in the sample can indicate the presence of hydroxyapatite. Therefore, phosphate and hydroxyl groups can be used as test parameters for the property test. In this study, the phosphate and hydroxyl characteristics of the *Lates calcarifer* fish scales group were compared with the "ALDRICH" chemical synthetic hydroxyapatite group using the FTIR analysis method. **Objectives:** to explain whether the scales of *Lates calcarifer* fish can be used as a synthetic hydroxyapatite candidate and to analyze the characteristics of the phosphate and hydroxyl groups produced from *Lates calcarifer* fish scales. **Methods:** FTIR or Fourier-transform Infrared Spectroscopy analysis method was used by

comparing the peak image of the phosphate and hydroxyl groups between the *Lates calcarifer* fish scales group and the "ALDRICH" chemical synthetic hydroxyapatite control group on the wave ranges of 1350–1250, 1050–990, 1240–1190/995–850, 1100–1000 for phosphate groups and on the wave ranges of 3650–3600, 3570–3200, 3400–2400 for hydroxyl groups. **Results:** The *Lates calcarifer* fish scales group showed that the peaks of the phosphate (PO_4^{3-}) and hydroxyl (-OH) groups had the same wave range as the synthetic hydroxyapatite control group "ALDRICH", namely in the 850–995 cm^{-1} , 990–1050 cm^{-1} / 1100–1000 cm^{-1} , and 3200–3570 cm^{-1} wave ranges. **Conclusion:** *Lates calcarifer* fish scales can be used as a candidate for synthetic hydroxyapatite.

Keywords: *Lates calcarifer* fish scales, phosphate groups, hydroxyl groups, FTIR.

Introduction

Background

Synthetic hydroxyapatite, $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ is one of the materials that is often used in biomedical applications as a bone substitution therapy or bone graft. Synthetic hydroxyapatite is biocompatible or has the ability to adapt to the body. Hydroxyapatite structure has regular porosity that is similar to natural structure of the bone tissue. The pores have an open structure and biocompatible surface which has ideal condition for cell growth and tissue differentiation. Synthetic hydroxyapatite also has bioactive properties that can bind to bone tissue and provide a specific biological response. these abilities can stimulate osteoblasts to form new bone tissue so that it can help in the process of bone regeneration.^{1,2}

The use of HA as a bone substitute or replacement includes complete or partial bone augmentation, filling bones and teeth or coating in orthopedics and dental implants.³ The use of synthetic chemicals in the hydroxyapatite synthesis process has an impact on the price of hydroxyapatite. In Indonesia, the market price of hydroxyapatite reaches 1.5 million per 5 milligrams and its availability still depends on imported products.⁴ To solve this problem, alternative materials can be used using natural materials by utilizing the richness of Indonesia's marine resources such as the scales of *Lates calcarifer* fish. *Lates calcarifer* fish is a leading marine cultivation commodity in Indonesia, whose market demand continues to increase every year, causing an increase in the residual fish waste such as *Lates calcarifer* scales. This can cause problems with the environmental balance.^{5,6} The utilization of *Lates calcarifer*

fish scales is needed because in addition to reducing *Lates calcarifer* scales waste and as an effort to maintain environmental balance, it can also be utilized in the medical field, namely as a synthetic hydroxyapatite candidate. Phosphate (PO_4)³⁻ and hydroxyl (-OH) groups are functional groups of synthetic hydroxyapatites. The presence of phosphate (PO_4)³⁻ and hydroxyl (-OH) groups in the sample can indicate the presence of hydroxyapatite in the sample. Therefore, the phosphate and hydroxyl groups can be used as test parameters for the property test. ⁷ In this study, the phosphate and hydroxyl characteristics of the *Lates calcarifer* fish scales group were compared with the "ALDRICH" chemical synthetic hydroxyapatite group using the FTIR analysis method.

Objectives

to explain whether the scales of *Lates calcarifer* fish can be used as a synthetic hydroxyapatite candidate and to analyze the characteristics of the phosphate and hydroxyl groups produced from *Lates calcarifer* fish scales.

Materials and Methods

Research Samples

The research sample used was the scales of 6 months old *Lates Calcarifer*, obtained from the Muara Karang Fish Auction, Jakarta.

Research Methods

FTIR or Fourier-transform Infrared Spectroscopy analysis method was used by comparing the peak image of the phosphate and hydroxyl groups between the *Lates calcarifer* fish scales group and the "ALDRICH" chemical synthetic hydroxyapatite (Merck KGaA, Darmstadt, Germany) control group. There were three stages.

1. Sample preparation stage

The fish scales were washed with distilled water for debridement and then soaked in a surfactant solution. Re-washing was carried out using a shaker for 4-6 hours to clean the surface and dry grease, and then the fish scales were soaked in 1N NaOH solution and heated at 120°C for about 30 minutes. The HA sediment was separated from the degraded protein, and the sediment was purified in distilled water. HA was dried in an

oven at 60°C to remove water and moisture from the powder and HA was sterilized by irradiation. After that, the powder sample was mixed with powdered potassium bromide (KBr), then pounded until smooth and mixed in a mortar agate. Then, the mixture was subjected to a high pressure of about 12,000 psi for 1-2 minutes. The ratio between sample powder and KBr is about 1: 100 to form a very homogeneous mixture of KBr. The resulting KBr mixture could be inserted into the FTIR spectroscopy holder.

2. Sample Handling Stage

Infrared light was directed at the sample or solid crystal with a high refractive index, at a certain angle. Then, the infrared rays contacted the ATR crystal and produced some internal reflection, which then created an evanescent wave that extended beyond the surface of the crystal. The sample that contacted the evanescent wave would absorb the wave energy and as a result, the evanescent wave would be attenuated. The attenuated light would be reflected on the crystal, and then went out to the opposite end of the crystal and was directed to the detector in the infrared spectrometer. The detector recorded the attenuated Infrared light as an interferogram signal, which could then be used to generate the Infrared spectrum.

3. FTIR spectrum analysis

FTIR (Fourier Transform Infrared Spectroscopy) is an instrument technique used to identify functional groups present in organic and inorganic compounds by measuring their absorption of infrared radiation in a certain wavelength range.⁸ FTIR analysis is generally used to determine the characterization of the desired compound which is characterized by distinctive pattern bands.⁹ The pattern of the absorption spectrum is like a fingerprint that identifies the molecule, which lends itself to both quantitative and qualitative analysis.¹⁰

FTIR analysis was used to determine the phosphate and hydroxyl functional groups based on the peaks which were displayed on the monitor screen originating from the light captured by the FTIR detector. The peaks were observed for the presence of phosphate groups, which can be analyzed from the sharp peaks in the FTIR spectroscopy pattern in 1350–1250 (Organic phosphates), 1050–990 (Aliphatic phosphates), 1240–1190/995–850 (Aromatic phosphates), and 1100-1000 (phosphate ions) wave ranges. The presence of hydroxyl groups can be analyzed from the sharp peaks in the FTIR spectrum pattern

on 3650-3600 (free alcohols, phenols), 3570-3200 (H-bonded alcohols, H-bonded OH, phenols), and 3400-2400 (carboxylic acid) wave ranges. ^{11, 12}

Statistical methods

The Mann-Whitney comparison test was used to see the significance of the two groups, *Lates Calcarifer* group and the ALDRICH group. Based on the statistical test of the two groups, it was stated that the phosphate group test resulted in $P = 0.27$, and the hydroxyl group test resulted in $P = 1.000$ so that $P > 0.05$. Thus, it can be stated that there was an insignificant difference data in the phosphate and the hydroxyl group between the *Lates Calcarifer* scales and the ALDRICH group.

Results




Figure 1. FTIR Spectrum of *Lates Calcarifer* Fish Scales Group




Figure 2. FTIR Spectrum of the synthetic hydroxyapatite control group "ALDRICH"(Merck KGaA, Darmstadt, Germany)

Table 1. Comparison table of phosphate and hydroxyl peaks between the *Lates Calcarifer* fish scales group and the "ALDRICH" group

GROUP	PHOSPHATE		HYDROXYL	
	λ (cm ⁻¹)	Transmittance Number (%)	λ (cm ⁻¹)	Transmittance Number (%)
<i>Lates Calcarifer</i> Fish Scales	873	66	3407	66
	990	63		
	1050	39		
"Sigma ALDRICH" Synthetic Hydroxyapatite (Merck KGaA, Darmstadt, Germany)	873	50	3352	45
	990	42	3570	50
	1050	23		

In the *Lates calcarifer* scales group, there were peak images of the phosphate (PO_4)³⁻ and hydroxyl (-OH) groups with the same wavelength ranges as the synthetic hydroxyapatite control group "ALDRICH", namely in 850-995 cm^{-1} , 990-1050 cm^{-1} / 1100-1000 cm^{-1} , and 3200-3570 cm^{-1} wavelength ranges. At the wavelength of $\lambda = \sim 873$ cm^{-1} , the transmittance number of *Lates calcarifer* fish scales group was $\sim 66\%$ and in the "ALDRICH" group was $\sim 50\%$. At the wavelength of $\lambda = \sim 990$ cm^{-1} , the transmittance number of *Lates calcarifer* fish scales group was $\sim 63\%$ and the "ALDRICH" group was $\sim 42\%$. At the wavelength of $\lambda = \sim 1050$ cm^{-1} , the transmittance number of *Lates calcarifer* fish scales group was $\sim 39\%$ and the "ALDRICH" group was $\sim 23\%$. On the hydroxyl groups, the *Lates calcarifer* fish scales group had a peak image on the wavelength of $\lambda = \sim 3407$ cm^{-1} , and its transmittance number was $\sim 66\%$. Meanwhile, the "ALDRICH" group had two peaks at the wavelength of $\lambda = \sim 3352$ cm^{-1} with its transmittance number was $\sim 45\%$ and at the wavelength of $\lambda = \sim 3570$ cm^{-1} with its transmittance number was $\sim 50\%$.

Discussion

Synthetic hydroxyapatite is a mineral that can be derived from chemicals or natural materials commonly used for bone therapy or bone graft. Synthetic hydroxyapatite has the properties of osseointegration, osteoconduction, osteoinduction, and osteogenesis. Thus, it is said to meet the criteria as an ideal bone graft candidate. Synthetic hydroxyapatite has the chemical structure of $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$. The phosphate (PO_4)³⁻ and hydroxyl (-OH) contained in synthetic hydroxyapatite have important roles in the process of osteogenesis or bone repair. ¹³ Phosphate (PO_4)³⁻ and hydroxyl (-OH) groups are functional groups of synthetic hydroxyapatites. Therefore, the presence of phosphate (PO_4)³⁻ and hydroxyl (-OH) groups in the sample can indicate the presence of hydroxyapatite in the sample. ⁷

Based on the results of the FTIR spectrum, it is known that the *Lates calcarifer* scales contain phosphate and hydroxyl groups from the wave peaks in the resulting spectrum. The *Lates calcarifer* scales group had peaks present in the wavelength range of phosphate and hydroxyl groups which were the same as the "ALDRICH" control group, namely in the 850-995 cm^{-1} and 990-1050 cm^{-1} / 1100-1000 cm^{-1} wavelength ranges, which indicated the presence of phosphate groups, and in the range of 3200-3570 cm^{-1} , which indicated the presence of a hydroxyl group. In the 850-995 cm^{-1} wavelength range, both the *Lates calcarifer* scales group and the "ALDRICH" control group had peak figures at

$\lambda = \sim 873 \text{ cm}^{-1}$ and $\lambda = \sim 990 \text{ cm}^{-1}$. In the *Lates calcarifer* group, the wavelength peak image was at $\lambda = \sim 873 \text{ cm}^{-1}$ with its transmittance number = $\sim 66\%$ and wavelength peak image at $\lambda = \sim 990 \text{ cm}^{-1}$ with transmittance number = $\sim 63\%$. Meanwhile, the control group "ALDRICH" had a slightly sharper peak image and lower transmittance number, in which at wavelength peak image $\lambda = \sim 873 \text{ cm}^{-1}$ with its transmittance number = $\sim 50\%$ and at $\lambda = \sim 990 \text{ cm}^{-1}$ with its transmittance number = $\sim 42\%$. In the $990\text{-}1050 \text{ cm}^{-1}$ / $1100\text{-}1000 \text{ cm}^{-1}$ wavelength range, both the fish scales group and the "ALDRICH" control group had a peak appearance at $\lambda = \sim 1050 \text{ cm}^{-1}$. In the *Lates calcarifer* group, The wavelength peak image was at $\lambda = \sim 1050 \text{ cm}^{-1}$ with its transmittance number = $\sim 39\%$, while the "ALDRICH" control group had a slightly sharper peak image and lower transmittance number of $\sim 23\%$ compared to the *Lates calcarifer* fish scale group.

The difference in the peak image of the phosphate groups between the two groups was slightly different with insignificant transmittance numbers. The frequency that passes through an organic compound or sample (which is not absorbed) will be measured as a percent of transmittance number. The higher the transmittance number means that the fewer infrared waves are absorbed by the compound or sample. Meanwhile, the lower the transmittance number or the sharper the wavelength peak, the higher the absorption intensity of infrared waves.¹⁴ Thus, indicating that the content of chemical group constituents in a certain wavelength range will increase. Based on the results of the phosphate groups spectrum in the *Lates calcarifer* fish scales, they contained less phosphate than the "ALDRICH" group. The "ALDRICH" group contained $\pm 15\%$ more phosphate content than the *Lates calcarifer* fish scales. According to the Stanciu, et al theory, the sharper the peak of the phosphate group $(\text{PO}_4)^{3-}$, the better the crystallinity growth of hydroxyapatite, which means that the better the hydroxyapatite is obtained.¹⁵ So that based on the image of the phosphate group peaks in the "ALDRICH" group, it can be said to have a slightly better hydroxyapatite content than the *Lates calcarifer* fish scales.

The *Lates calcarifer* fish scales group had peaks present in the wavelength range of the hydroxyl group, which was the same as the control group "ALDRICH", namely in the wavelength range of $3200\text{-}3570 \text{ cm}^{-1}$. The fish scales group had a peak image at $\lambda = \sim 3407 \text{ cm}^{-1}$ with a transmittance number = $\sim 66\%$, while the control group "ALDRICH" had two peak images at $\lambda = \sim 3352 \text{ cm}^{-1}$ with a transmittance number = $\sim 45\%$ and at $\lambda = \sim 3570 \text{ cm}^{-1}$ with a transmittance number = $\sim 50\%$. Based on the results of the hydroxyl groups spectrum between the two groups, the peak image in the "ALDRICH" control group had

a slightly sharper picture and a lower transmittance number compared to the *Lates calcarifer* fish scales. The "ALDRICH" group had two peaks in appearance while the *Lates calcarifer* fish scales group has only one peak. The sharper the peak of the hydroxyl group (-OH) shows a good level of crystallinity, which means that the more and better hydroxyapatite is obtained. ¹⁶So that based on the content and the peak images of the hydroxyl group, the "ALDRICH" group had a better hydroxyapatite content because of more hydroxyl content that the absorption intensity of infrared waves was more than the *Lates calcarifer* fish scales group.

Conclusions

In conclusion, Based on the results of the analysis of the content of phosphate and hydroxyl groups using FTIR, it can be concluded that the *Lates calcarifer* scales can be used as a synthetic hydroxyapatite candidate because it contains hydroxyapatite as indicated by the presence of phosphate groups (PO₄)³⁻ and hydroxyl (-OH) which had the same wave range with synthetic hydroxyapatite "ALDRICH" with a similar amount or less than the control group "ALDRICH", albeit not significant. However, the hydroxyapatite content produced from the "ALDRICH" group was better than that of *Lates calcarifer* scales.

Limitations

This study has a limitation, namely the property test carried out on *Lates calcarifer* scales was only the FTIR method. Therefore, it is advisable to do further research on: The property test of *Lates calcarifer* scales as synthetic hydroxyapatite candidates tested using other methods, such as XRD, TEM, and others, The effectiveness of *Lates calcarifer* scales on the bone or as synthetic hydroxyapatite, The toxicity test of *Lates calcarifer* in the body.

Acknowledgement

The authors are grateful to the Ministry of Research, Technology and Higher Education, Indonesia, for the funding support thus this research could be conducted.

Declaration of interests

The authors declare that there are no conflicts of interest.

Ethical policy and institutional review board statement

Ethical clearance had been obtained from the Ethics Commission of the Faculty of Dental Medicine, Airlangga University, Surabaya (No.279/ HRECC.FODM / VI / 2020) on 11 June, 2020.

References

1. Prahasanti C, Krismariono A, Takanamita R, et al. Enhancement of Osteogenesis Using a Combination of Hydroxyapatite and Stem Cells from Exfoliated Deciduous Teeth Chiquita. *J Int Dent Med Res* ISSN. 2020; 13(2): 508–12.
2. Supangat D, Cahyaningrum SE. Synthesis and Characterization of Hydroxyapatite of Crabs Shell (*Scylla Serrata*) by Wet Application Method. *UNESA J Chem*. 2017; 6(3): 143–9.
3. Szcześ A, Hołysz L, Chibowski E. Synthesis of hydroxyapatite for biomedical applications. *Adv Colloid Interface Sci Journal*. 2017; 249: 321–30.
4. Technology Sector Material : Bioceramic Hydroxyapatite. *Pusat Pelayanan Teknologi Badan Pengkajian dan Penerapan Teknologi*. PUSYANTEK BBPT publication. 2018.
5. Windarto S, Hastuti S, Subandiyono S, Nugroho R, Sarjito S. *Performa Pertumbuhan Ikan Kakap Putih (Lates Calcarifer Bloch, 1790) Yang Dibudidayakan Dengan Sistem Keramba Jaring Apung (KJA)*. *Sains Akuakultur Tropis*. 2019; 3(1): 56-7.
6. Romadhon, Darmanto Y, Kurniasih R. *Karakteristik kolagen dari tulang, kulit, dan sisik ikan nila*. *Jurnal Pengolahan Hasil Perikanan Indonesia*. 2019; 22(2): 403.
7. Harahap A, Helwani Z, Zultiniar, Yelmida. *Sintesis Hidroksiapatit melalui Precipitated Calcium Carbonate (PCC) Cangkang Kerang Darah dengan Metode Hidrotermal pada Variasi pH dan Waktu Reaksi*. *Jom FTEKNIK*. 2015; 2(2): 1-7.
8. Siregar C, Martono S, Rohman A. Application of Fourier transform infrared (FTIR) spectroscopy coupled with multivariate calibration for quantitative analysis of curcuminoid in tablet dosage form. *Journal of Applied Pharmaceutical Science*. 2018; 8(8): 151-6.
9. Causserand, C. & Aimar, P. Analysis of Chemical Composition. In: Causserand, C. & Aimar, P. *Characterization Of Filtration Membranes*. France: Elsevier: 2010: 328-31.
10. Guerrero-Pérez M, Patience G. Experimental methods in chemical engineering: Fourier transform infrared spectroscopy—FTIR. *The Canadian Journal of Chemical Engineering*. 2019; 98(1): 25-6.
11. Nandiyanto A, Oktiani R, Ragadhita R. How to Read and Interpret FTIR Spectroscopy of Organic Material. *Indonesian Journal of Science and Technology*. 2019; 4(1): 103.
12. Mohamed MA, Jaafar J, Ismail AF, Othman MHD, Rahman MA. Fourier Transform Infrared (FTIR) Spectroscopy. In: Hilal N, Ismail A, Matsuura T, Oatley-Radcliffe D. *Membrane Characterization*. 1st ed; 2017: 2-11.
13. Ardhiyanto H. *Stimulasi Osteoblas oleh Hidroksiapatit Sebagai Material Bone Graft Pada Proses Penyembuhan Tulang*. *Jurnal Kedokteran Gigi Universitas Jember*. 2014; 9(3): 162-3.
14. Dachriyanus. *Spektrofotometer Inframerah*. In: Dachriyanus. *Analisis Struktur Senyawa Organik Secara Spektroskopi*. Padang: Lembaga Pengembangan Teknologi Informasi dan Komunikasi (LPTIK) Universitas Andalas; 2004: 22-3.
15. Stanciu G, Sandulescu I, Savu B, et al. Investigation of the Hydroxyapatite Growth on

Bioactive Glass Surface. Journal of Biomedical & Pharmaceutical Engineering. 2007; 1(1): 38.

16. Tua B, Amri A, Zultiniar. *Sintesis dan Karakterisasi Hidroksiapatit dari Cangkang Kerang Darah dengan Proses Hidrotermal Variasi Suhu dan pH*. Jom FTEKNIK. 2016; 3(2): 1-4.

TABLES, FIGURES




Figure 1. FTIR Spectrum of *Lates Calcarifer* Fish Scales Group




Figure 2. FTIR Spectrum of the synthetic hydroxyapatite control group "ALDRICH" (Merck KGaA, Darmstadt, Germany)

Table 1. Comparison table of phosphate and hydroxyl peaks between the *Lates Calcarifer* fish scales group and the "ALDRICH" group

GROUP	PHOSPHATE		HYDROXYL	
	λ (cm ⁻¹)	Transmittance Number (%)	λ (cm ⁻¹)	Transmittance Number (%)
<i>Lates Calcarifer</i> Fish Scales	873	66	3407	66
	990	63		
	1050	39		
"Sigma ALDRICH" Synthetic Hydroxyapatite (Merck KGaA, Darmstadt, Germany)	873	50	3352	45
	990	42	3570	50
	1050	23		

Property Test of Phosphate and Hydroxyl Groups from Lates Carcarifer Fish Scale as a Candidate for Synthetic Hydroxyapatite using the FTIR Method

Dian Agustin Wahjuningrum^{1*}, Setyabudi¹, Anuj Bhardwaj^{2,3}, Syania Edinda Febriyanti⁴,
Nadia Liliani Soetjipta⁵, Latief Mooduto¹

1. Departement of Conservative Dentistry, Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia.
2. Department of Conservative Dentistry and Endodontics, College of Dental Science and hospital, Indore, India.
3. Adjunct Professor at Departement of Conservative Dentistry, Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia.
4. Undergraduate Student of Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia.
5. Postgraduate Student of Departement of Conservative Dentistry, Faculty of Dental Medicine, Airlangga University, Surabaya, Indonesia.

Abstract

In Indonesia, the market price of Synthetic hydroxyapatite, $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ reaches 1.5 million per 5 milligrams and its availability still depends on imported products. To solve this problem, alternative materials can be used, such as Lates calcarifer fish scales. Phosphate (PO_4)₃⁻ and hydroxyl (-OH) groups are functional groups of synthetic hydroxyapatites. The presence of phosphate (PO_4)₃⁻ and hydroxyl (-OH) groups in the sample can indicate the presence of hydroxyapatite. Therefore, phosphate and hydroxyl groups can be used as test parameters for the property test. In this study, the phosphate and hydroxyl characteristics of the Lates calcarifer fish scales group were compared with the "ALDRICH" chemical synthetic hydroxyapatite group using the FTIR analysis method.

Objectives to explain whether the scales of Lates calcarifer fish can be used as a synthetic hydroxyapatite candidate and to analyze the characteristics of the phosphate and hydroxyl groups produced from Lates calcarifer fish scales.

FTIR or Fourier-transform Infrared Spectroscopy analysis method was used by comparing the peak image of the phosphate and hydroxyl groups between the Lates calcarifer fish scales group and the "ALDRICH" chemical synthetic hydroxyapatite control group on the wave ranges of 1350–1250, 1050–990, 1240–1190/995–850, 1100-1000 for phosphate groups and on the wave ranges of 3650-3600, 3570-3200, 3400-2400 for hydroxyl groups.

The Lates calcarifer fish scales group showed that the peaks of the phosphate (PO_4)₃⁻ and hydroxyl (-OH) groups had the same wave range as the synthetic hydroxyapatite control group "ALDRICH", namely in the 850-995 cm⁻¹, 990-1050 cm⁻¹ / 1100-1000 cm⁻¹, and 3200-3570 cm⁻¹ wave ranges.

Lates calcarifer fish scales can be used as a candidate for synthetic hydroxyapatite.

Experimental article (J Int Dent Med Res 2021; 14(2): 489-493)

Keywords: Lates calcarifer fish scales, phosphate groups, hydroxyl groups, FTIR.

Received date: 03 December 2020

Accept date: 10 January 2021

Introduction

Background

Synthetic hydroxyapatite, $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ is one of the materials that is often used in biomedical applications as a bone substitution therapy or bone graft. Synthetic hydroxyapatite is biocompatible or has the ability

to adapt to the body. Hydroxyapatite structure has regular porosity that is similar to natural structure of the bone tissue. The pores have an open structure and biocompatible surface which has ideal condition for cell growth and tissue differentiation. Synthetic hydroxyapatite also has bioactive properties that can bind to bone tissue and provide a specific biological response. these abilities can stimulate osteoblasts to form new bone tissue so that it can help in the process of bone regeneration.^{1,2}

The use of HA as a bone substitute or replacement includes complete or partial bone augmentation, filling bones and teeth or coating in orthopedics and dental implants.³ The use of

*Corresponding author:

Dian Agustin Wahjuningrum,
Dental Medicine Faculty of Airlangga University
St. Mayjen Prof. Dr. Moestopo No. 47, Surabaya, Indonesia.
E-mail: dian-agustin-w@fkg.unair.ac.id

synthetic chemicals in the hydroxyapatite synthesis process has an impact on the price of hydroxyapatite. In Indonesia, the market price of hydroxyapatite reaches 1.5 million per 5 milligrams and its availability still depends on imported products.⁴ To solve this problem, alternative materials can be used using natural materials by utilizing the richness of Indonesia's marine resources such as the scales of *Lates calcarifer* fish. *Lates calcarifer* fish is a leading marine cultivation commodity in Indonesia, whose market demand continues to increase every year, causing an increase in the residual fish waste such as *Lates calcarifer* scales. This can cause problems with the environmental balance.^{5,6} The utilization of *Lates calcarifer* fish scales is needed because in addition to reducing *Lates calcarifer* scales waste and as an effort to maintain environmental balance, it can also be utilized in the medical field, namely as a synthetic hydroxyapatite candidate. Phosphate (PO_4^{3-}) and hydroxyl (-OH) groups are functional groups of synthetic hydroxyapatites. The presence of phosphate (PO_4^{3-}) and hydroxyl (-OH) groups in the sample can indicate the presence of hydroxyapatite in the sample. Therefore, the phosphate and hydroxyl groups can be used as test parameters for the property test.⁷ In this study, the phosphate and hydroxyl characteristics of the *Lates calcarifer* fish scales group were compared with the "ALDRICH" chemical synthetic hydroxyapatite group using the FTIR analysis method.

Objectives to explain whether the scales of *Lates calcarifer* fish can be used as a synthetic hydroxyapatite candidate and to analyze the characteristics of the phosphate and hydroxyl groups produced from *Lates calcarifer* fish scales.

Materials and methods

Research Samples

The research sample used was the scales of 6 months old *Lates Calcarifer*, obtained from the Muara Karang Fish Auction, Jakarta.

Research Methods

FTIR or Fourier-transform Infrared Spectroscopy analysis method was used by comparing the peak image of the phosphate and hydroxyl groups between the *Lates calcarifer* fish scales group and the "ALDRICH" chemical synthetic hydroxyapatite (Merck KGaA,

Darmstadt, Germany) control group. There were three stages.

1. Sample preparation stage

The fish scales were washed with distilled water for debridement and then soaked in a surfactant solution. Re-washing was carried out using a shaker for 4-6 hours to clean the surface and dry grease, and then the fish scales were soaked in 1N NaOH solution and heated at 120°C for about 30 minutes. The HA sediment was separated from the degraded protein, and the sediment was purified in distilled water. HA was dried in an oven at 60°C to remove water and moisture from the powder and HA was sterilized by irradiation. After that, the powder sample was mixed with powdered potassium bromide (KBr), then pounded until smooth and mixed in a mortar agate. Then, the mixture was subjected to a high pressure of about 12,000 psi for 1-2 minutes. The ratio between sample powder and KBr is about 1: 100 to form a very homogeneous mixture of KBr. The resulting KBr mixture could be inserted into the FTIR spectroscopy holder.

2. Sample Handling Stage

Infrared light was directed at the sample or solid crystal with a high refractive index, at a certain angle. Then, the infrared rays contacted the ATR crystal and produced some internal reflection, which then created an evanescent wave that extended beyond the surface of the crystal. The sample that contacted the evanescent wave would absorb the wave energy and as a result, the evanescent wave would be attenuated. The attenuated light would be reflected on the crystal, and then went out to the opposite end of the crystal and was directed to the detector in the infrared spectrometer. The detector recorded the attenuated Infrared light as an interferogram signal, which could then be used to generate the Infrared spectrum.

3. FTIR spectrum analysis

FTIR (Fourier Transform Infrared Spectroscopy) is an instrument technique used to identify functional groups present in organic and inorganic compounds by measuring their absorption of infrared radiation in a certain wavelength range.⁸ FTIR analysis is generally used to determine the characterization of the desired compound which is characterized by distinctive pattern bands.⁹ The pattern of the absorption spectrum is like a fingerprint that identifies the molecule, which lends itself to both quantitative and qualitative analysis.¹⁰

FTIR analysis was used to determine the phosphate and hydroxyl functional groups based on the peaks which were displayed on the monitor screen originating from the light captured by the FTIR detector. The peaks were observed for the presence of phosphate groups, which can be analyzed from the sharp peaks in the FTIR spectroscopy pattern in 1350–1250 (Organic phosphates), 1050–990 (Aliphatic phosphates), 1240–1190/995–850 (Aromatic phosphates), and 1100-1000 (phosphate ions) wave ranges. The presence of hydroxyl groups can be analyzed from the sharp peaks in the FTIR spectrum pattern on 3650-3600 (free alcohols, phenols), 3570-3200 (H-bonded alcohols, H-bonded OH, phenols), and 3400-2400 (carboxylic acid) wave ranges.^{11, 12}

Statistical methods

The Mann-Whitney comparison test was used to see the significance of the two groups, *Lates Calcarifer* group and the ALDRICH group. Based on the statistical test of the two groups, it was stated that the phosphate group test resulted in P = 0.27, and the hydroxyl group test resulted in P = 1.000 so that P > 0.05. Thus, it can be stated that there was an insignificant difference data in the phosphate and the hydroxyl group between the *Lates Calcarifer* scales and the ALDRICH group.

Results

In the *Lates calcarifer* scales group, there were peak images of the phosphate (PO₄)³⁻ and hydroxyl (-OH) groups with the same wavelength ranges as the synthetic hydroxyapatite control group "ALDRICH", namely in 850-995 cm⁻¹, 990-1050 cm⁻¹ / 1100-1000 cm⁻¹, and 3200-3570 cm⁻¹ wavelength ranges. At the wavelength of λ = 873 cm⁻¹, the transmittance number of *Lates calcarifer* fish scales group was ~ 66% and in the "ALDRICH" group was ~ 50%. At the wavelength of λ = ~ 990 cm, the transmittance number of *Lates calcarifer* fish scales group was ~ 63% and the "ALDRICH" group was ~ 42%. At the wavelength of λ = ~ 1050 cm⁻¹, the transmittance number of *Lates calcarifer* fish scales group was ~ 39% and the "ALDRICH" group was ~ 23%. On the hydroxyl groups, the *Lates calcarifer* fish scales group had a peak image on the wavelength of λ = ~ 3407 cm⁻¹, and its transmittance number was ~ 66%. Meanwhile, the "ALDRICH" group had two peaks at the

wavelength of λ = ~ 3352 cm⁻¹ with its transmittance number was ~ 45% and at the wavelength of λ = ~ 3570 cm⁻¹ with its transmittance number was ~ 50%.




Figure 1. FTIR Spectrum of *Lates Calcarifer* Fish Scales Group.




Figure 2. FTIR Spectrum of the synthetic hydroxyapatite control group "ALDRICH"(Merck KGaA, Darmstadt, Germany).

GROUP	PHOSPHATE		HYDROXYL	
	λ (cm ⁻¹)	Transmittance Number (%)	λ (cm ⁻¹)	Transmittance Number (%)
<i>Lates Calcarifer</i> Fish Scales	-873	-66	-3407	-66
	-990	-63		
	-1050	-39		
"Sigma ALDRICH" Synthetic Hydroxyapatite (Merck KGaA, Darmstadt, Germany)	-873	-50	-3352	-45
	-990	-42	-3570	-50
	-1050	-23		

Table 1. Comparison table of phosphate and hydroxyl peaks between the *Lates Calcarifer* fish scales group and the "ALDRICH" group.

Discussion

Synthetic hydroxyapatite is a mineral that can be derived from chemicals or natural materials commonly used for bone therapy or bone graft. Synthetic hydroxyapatite has the properties of osseointegration, osteoconduction, osteoinduction, and osteogenesis. Thus, it is said to meet the criteria as an ideal bone graft candidate. Synthetic hydroxyapatite has the chemical structure of $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$. The phosphate (PO_4)³⁻ and hydroxyl (-OH) contained in synthetic hydroxyapatite have important roles in the process of osteogenesis or bone repair.¹³ Phosphate (PO_4)³⁻ and hydroxyl (-OH) groups are functional groups of synthetic hydroxyapatites. Therefore, the presence of phosphate (PO_4)³⁻ and hydroxyl (-OH) groups in the sample can indicate the presence of hydroxyapatite in the sample.⁷

Based on the results of the FTIR spectrum, it is known that the *Lates calcarifer* scales contain phosphate and hydroxyl groups from the wave peaks in the resulting spectrum. The *Lates calcarifer* scales group had peaks present in the wavelength range of phosphate and hydroxyl groups which were the same as the "ALDRICH" control group, namely in the 850-995 cm⁻¹ and 990-1050 cm⁻¹ / 1100-1000 cm⁻¹ wavelength ranges, which indicated the presence of phosphate groups, and in the range of 3200-3570 cm⁻¹, which indicated the presence of a hydroxyl group. In the 850-995 cm⁻¹ wavelength range, both the *Lates calcarifer* scales group and the "ALDRICH" control group had peak figures at $\lambda = \sim 873$ cm⁻¹ and $\lambda = \sim 990$ cm⁻¹. In the *Lates calcarifer* group, the wavelength peak image was at $\lambda = \sim 873$ cm⁻¹ with its transmittance number = $\sim 66\%$ and wavelength peak image at $\lambda = \sim 990$ cm⁻¹ with transmittance number = $\sim 63\%$. Meanwhile, the control group "ALDRICH" had a slightly sharper peak image and lower transmittance number, in which at wavelength peak image $\lambda = \sim 873$ cm⁻¹ with its transmittance number = $\sim 50\%$ and at $\lambda = \sim 990$ cm⁻¹ with its transmittance number = $\sim 42\%$. In the 990-1050 cm⁻¹ / 1100-1000 cm⁻¹ wavelength range, both the fish scales group and the "ALDRICH" control group had a peak appearance at $\lambda = \sim 1050$ cm⁻¹. In the *Lates calcarifer* group, The wavelength peak image was at $\lambda = \sim 1050$ cm⁻¹ with its transmittance number = $\sim 39\%$, while the "ALDRICH" control group had a slightly sharper peak image and

lower transmittance number of $\sim 23\%$ compared to the *Lates calcarifer* fish scale group.

The difference in the peak image of the phosphate groups between the two groups was slightly different with insignificant transmittance numbers. The frequency that passes through an organic compound or sample (which is not absorbed) will be measured as a percent of transmittance number. The higher the transmittance number means that the fewer infrared waves are absorbed by the compound or sample. Meanwhile, the lower the transmittance number or the sharper the wavelength peak, the higher the absorption intensity of infrared waves.¹⁴ Thus, indicating that the content of chemical group constituents in a certain wavelength range will increase. Based on the results of the phosphate groups spectrum in the *Lates calcarifer* fish scales, they contained less phosphate than the "ALDRICH" group. The "ALDRICH" group contained $\pm 15\%$ more phosphate content than the *Lates calcarifer* fish scales. According to the Stanciu, et al theory, the sharper the peak of the phosphate group (PO_4)³⁻, the better the crystallinity growth of hydroxyapatite, which means that the better the hydroxyapatite is obtained.¹⁵ So that based on the image of the phosphate group peaks in the "ALDRICH" group, it can be said to have a slightly better hydroxyapatite content than the *Lates calcarifer* fish scales.

The *Lates calcarifer* fish scales group had peaks present in the wavelength range of the hydroxyl group, which was the same as the control group "ALDRICH", namely in the wavelength range of 3200-3570 cm⁻¹. The fish scales group had a peak image at $\lambda = \sim 3407$ cm⁻¹ with a transmittance number = $\sim 66\%$, while the control group "ALDRICH" had two peak images at $\lambda = \sim 3352$ cm⁻¹ with a transmittance number = $\sim 45\%$ and at $\lambda = \sim 3570$ cm⁻¹ with a transmittance number = $\sim 50\%$. Based on the results of the hydroxyl groups spectrum between the two groups, the peak image in the "ALDRICH" control group had a slightly sharper picture and a lower transmittance number compared to the *Lates calcarifer* fish scales. The "ALDRICH" group had two peaks in appearance while the *Lates calcarifer* fish scales group has only one peak. The sharper the peak of the hydroxyl group (-OH) shows a good level of crystallinity, which means that the more and better hydroxyapatite is obtained.¹⁶ So that based on the content and the

peak images of the hydroxyl group, the "ALDRICH" group had a better hydroxyapatite content because of more hydroxyl content that the absorption intensity of infrared waves was more than the *Lates calcarifer* fish scales group.

Conclusions

In conclusion, Based on the results of the analysis of the content of phosphate and hydroxyl groups using FTIR, it can be concluded that the *Lates calcarifer* scales can be used as a synthetic hydroxyapatite candidate because it contains hydroxyapatite as indicated by the presence of phosphate groups (PO_4^{3-}) and hydroxyl (-OH) which had the same wave range with synthetic hydroxyapatite "ALDRICH" with a similar amount or less than the control group "ALDRICH", albeit not significant. However, the hydroxyapatite content produced from the "ALDRICH" group was better than that of *Lates calcarifer* scales.

Limitations

This study has a limitation, namely the property test carried out on *Lates calcarifer* scales was only the FTIR method. Therefore, it is advisable to do further research on: The property test of *Lates calcarifer* scales as synthetic hydroxyapatite candidates tested using other methods, such as XRD, TEM, and others, The effectiveness of *Lates calcarifer* scales on the bone or as synthetic hydroxyapatite, The toxicity test of *Lates calcarifer* in the body.

Acknowledgements

The authors are grateful to the Ministry of Research, Technology and Higher Education, Indonesia, for the funding support thus this research could be conducted.

Declaration of Interest

The authors declare that there are no conflicts of interest.

Ethical policy and institutional review board statement

Ethical clearance had been obtained from the Ethics Commission of the Faculty of Dental Medicine, Airlangga University, Surabaya (No.279/ HRECC.FODM / VI / 2020) on 11 June, 2020.

References

1. Prahasanti C, Krismariono A, Takanamita R, et al. Enhancement of Osteogenesis Using a Combination of Hydroxyapatite and Stem Cells from Exfoliated Deciduous Teeth Chiquita. *J Int Dent Med Res* ISSN. 2020; 13(2): 508–12.
2. Supangat D, Cahyaningrum SE. Synthesis and Characterization of Hydroxyapatite of Crabs Shell (*Scylla Serrata*) by Wet Application Method. *UNESA J Chem*. 2017; 6(3): 143–9.
3. Szcześ A, Holysz L, Chibowski E. Synthesis of hydroxyapatite for biomedical applications. *Adv Colloid Interface Sci Journal*. 2017; 249: 321–30.
4. Technology Sector Material : Bioceramic Hydroxyapatite. Pusat Pelayanan Teknologi Badan Pengkajian dan Penerapan Teknologi. PUSYANTEK BBPT publication. 2018.
5. Windarto S, Hastuti S, Subandiyono S, Nugroho R, Sarjito S. Performa Pertumbuhan Ikan Kakap Putih (*Lates Calcarifer* Bloch, 1790) Yang Dibudidayakan Dengan Sistem Keramba Jaring Apung (KJA). *Sains Akuakultur Tropis*. 2019; 3(1): 56-7.
6. Romadhon, Darmanto Y, Kumiasih R. Karakteristik kolagen dari tulang, kulit, dan sisik ikan nila. *Jurnal Pengolahan Hasil Perikanan Indonesia*. 2019; 22(2): 403.
7. Harahap A, Helwani Z, Zultiniar, Yelmida. Sintesis Hidroksiapatit melalui Precipitated Calcium Carbonate (PCC) Cangkang Kerang Darah dengan Metode Hidrotermal pada Variasi pH dan Waktu Reaksi. *Jom FTEKNIK*. 2015; 2(2): 1-7.
8. Siregar C, Martono S, Rohman A. Application of Fourier transform infrared (FTIR) spectroscopy coupled with multivariate calibration for quantitative analysis of curcuminoid in tablet dosage form. *Journal of Applied Pharmaceutical Science*. 2018; 8(8): 151-6.
9. Causserand, C. & Aimar, P. Analysis of Chemical Composition. In: Causserand, C. & Aimar, P. *Characterization Of Filtration Membranes*. France: Elsevier: 2010: 328-31.
10. Guerrero-Pérez M, Patience G. Experimental methods in chemical engineering: Fourier transform infrared spectroscopy—FTIR. *The Canadian Journal of Chemical Engineering*. 2019; 98(1): 25-6.
11. Nandiyanto A, Oktiani R, Ragadhita R. How to Read and Interpret FTIR Spectroscopy of Organic Material. *Indonesian Journal of Science and Technology*. 2019; 4(1): 103.
12. Mohamed MA, Jaafar J, Ismail AF, Othman MHD, Rahman MA. Fourier Transform Infrared (FTIR) Spectroscopy. In: Hilal N, Ismail A, Matsuura T, Oatley-Radcliffe D. *Membrane Characterization*. 1st ed; 2017: 2-11.
13. Ardhiyanto H. Stimulasi Osteoblas oleh Hidroksiapatit Sebagai Material Bone Graft Pada Proses Penyembuhan Tulang. *Jurnal Kedokteran Gigi Universitas Jember*. 2014; 9(3): 162-3.
14. Dachriyanus. Spektrofotometer Inframerah. In: Dachriyanus. *Analisis Struktur Senyawa Organik Secara Spektroskopi*. Padang: Lembaga Pengembangan Teknologi Informasi dan Komunikasi (LPTIK) Universitas Andalas; 2004: 22-3.
15. Stanciu G, Sandulescu I, Savu B, et al. Investigation of the Hydroxyapatite Growth on Bioactive Glass Surface. *Journal of Biomedical & Pharmaceutical Engineering*. 2007; 1(1): 38.
16. Tua B, Amri A, Zultiniar. Sintesis dan Karakterisasi Hidroksiapatit dari Cangkang Kerang Darah dengan Proses Hidrotermal Variasi Suhu dan pH. *Jom FTEKNIK*. 2016; 3(2): 1-4.