

Biocompatibility of Portunus Pelagicus Hydroxyapatite Graft on Human Gingival Fibroblast Cell Culture

by Michael Josef K. Kamadjaja

Submission date: 04-Jun-2021 09:17AM (UTC+0800)

Submission ID: 1600001178

File name: droxyapatite_Graft_on_Human_Gingival_Fibroblast_Cell_Culture.pdf (955.64K)

Word count: 2713

Character count: 14516

4
ORIGINAL PAPER

doi: 10.5455/medarch.2019.73.378-381

MED ARCH. 2019 DEC; 73(6): 378-381

RECEIVED: OCT 09, 2019 | ACCEPTED: DEC 11, 2019

Corresponding author: Michael Josef Kridanto
Kamadjaja, DDS., MSc,
E-mail: michael-j-k-k@fkg.unair.ac.id

1
© 2019 Michael Josef Kridanto Kamadjaja, Janery
Fidelia Abraham, Harry Laksono

1
**Biocompatibility of Portunus
Pelagicus Hydroxyapatite Graft
on Human Gingival Fibroblast Cell
Culture**

Michael Josef Kridanto Kamadjaja¹, Janery Fidelia Abraham², Harry Laksono¹

ABSTRACT

Introduction: Crab shell (*Portunus pelagicus*) has the potential to be a source of hydroxyapatite biomaterials that used as bone grafts. Before clinical application, crab shell graft should be tested for its biocompatibility in vitro on human gingival fibroblast. **Aim:** This study aimed to determine the biocompatibility of *Portunus pelagicus* hydroxyapatite graft on human gingival fibroblast cell culture. **Methods:** Human gingival fibroblast cell cultures were divided into control group and treatment group with the addition of hydroxyapatite graft powder from *Portunus pelagicus* at a concentration of 100 ppm, 50 ppm, and 25 ppm. The synthesis process of hydroxyapatite was conducted by heating at 1000°C then characterizing the compound with SEM-EDX. All samples were incubated in α-MEM medium, then were given MTT material. The cultures on the plate were examined using ELISA reader. The results were analyzed using a Oneway Anova. **Results:** The percentage of living cells throughout all treatment group shown results that exceeded the LD50 parameter. The highest percentage of living cells was at 25 ppm concentration group. **Conclusion:** The hydroxyapatite graft powder from crab shells is biocompatible with human gingival fibroblast cell culture.

Keywords: Hydroxyapatites, Graft, Fibroblasts.

1. INTRODUCTION

The development of science and technology is not guaranteed the tooth resistance against disease or trauma completely, so there are still many cases of tooth loss. When tooth loss occurs, bone volume will decrease. Bone resorption due to tooth extraction may cause a problem in prosthodontics because it may lead to poor results of long-term treatment (1). Within 6 months, bone resorption occurs as much as 1.5-2 mm in vertical direction and 40%-50% in horizontal direction, and most cases occur in the first three months. If the treatment is not taken, the bone resorption can reach 40-60% of bone ridge volume in the first three years (2).

At present-day, there are various types of materials and techniques used for bone resorption treatment, including bone graft material, usage of guided tissue regeneration, application of growth factors to stimulate bone regeneration (3). Bone graft is used as scaffolds, matrix attachment and proliferation osteoblast (4). Bone graft material must have a biocompatibility property with living tissue, profitable for osteoconduction, osteo-

induction and has ability to support new bone formation. Graft biocompatibility is very crucial in order to prevent rejection by the host and not toxic to the body (5, 6).

The most ideal bone graft to use is an autograft that derived from the patient's own body. However, sometimes the process is not able to support, so that autograft is developed to allograft material. Yet, allografts often transmit infectious diseases, especially HIV and for that reason allograft is developed to xenograft material. The most commonly used xenograft is from bovine, but transmission of bovine spongiform encephalitis (BSE) is commonly occur. Various type of synthetic bone grafts was developed to minimize the risk of transmitting disease. Ideal conditions that need to be fulfilled by synthetic bone grafts are biocompatible, profitable for osteoconduction, osteoinduction and osteogenesis. Those three mechanisms are the most important for resorbable biomaterials that support tissue growth (6). However, alloplast particles cannot be counted on the site at the location of the embedded graft so that bone formation cannot be determined (7).

One type of bone graft, namely hydroxyapatite graft which can be produced from coral reef skeletons, bovine bones, chicken claws, shellfish shells and human cancellous bones (8). In Indonesia, natural raw materials, especially those derived from marine biota are easily found, relatively low-cost and the production process is simple. Among these raw materials are crab shells (*Portunus pelagicus*) which are uncommonly used, even turned into waste (9).

A crab shell contains large amounts of calcium carbonate, about 40% - 70% (9). Calcium carbonate is source of calcium that can be used as synthesis material of hydroxyapatite. Apatite crystals contain many carbon groups in carbonate shapes. Hydroxyapatite is a stable apatite crystal and implanted as bone replacement or filler. Hydroxyapatite biomaterials consist of bioactive components that are compatible with bones and teeth. This supports the use of crab shells as bone replacement alternative biomaterial based on the chemical composition. In addition, the development of crab shells as hydroxyapatite graft has not been carried out further and still requires biocompatibility test to be used on a wide scale (10).

In performing in vitro test of a new materials, fibroblasts are used. Fibroblasts are connective tissue cells that function as defense because they are able to differentiate as odontoblast and osteoblast cells and produce collagen fibers in healing process. The ability to grow fast in tissues and be able to live solitary is the reason why fibroblast cells are easily cultured into cell subjects (11). The biocompatibility test of hydroxyapatite graft produced from crab shells on human gingival fibroblast (HGF) cell cultures is required to determine whether the graft is ideal to be applied to the bone.

2. AIM

In the present study, we determine the biocompatibility of *Portunus pelagicus* hydroxyapatite graft on human gingival fibroblast cell culture.

3. METHODS

This is an experimental laboratory research with post-test only control group design. The treatment was carried out by giving hydroxyapatite graft powder from crab shell (*Portunus pelagicus*) on HGF cell culture. This study used 5 samples for each treatment group, those include the addition of hydroxyapatite graft crab shell at concentration of 100 ppm, 50 ppm and 25 ppm as well as cell control group and media control of 5 samples respectively. The sampling technique used is simple random sampling.

Processing of crab shells (*Portunus pelagicus*) for the synthesis of hydroxyapatite graft conducted at the Center for Biomaterials of Dr. Soetomo General National Hospital Surabaya. It was began by the washing process of crab shells using distilled water, chlorine and H₂O₂ then continued with the heating process of crab shells using furnace at 1000°C for 2 hours. Powder sifting process was performed with sifting machine until the particle size was less than 155µm and continued with the




Figure 1. SEM micrograph of hydroxyapatite crab shell samples at 500x magnification from two different fields of view

characterization of hydroxyapatite compounds using SEM-EDX.

The in vitro study was conducted at Stem Cell Research Development Center of Universitas Airlangga Surabaya. The isolation process of Human Gingival Fibroblast (HGF) cells was conducted from healthy gingival samples patients aged less than 30 years old. HGF cells are processed by splitting process which aim to multiply cells and replace α -MEM media. Before the treatment phase, cell preparations are processed by doing washing for several times using trypsin enzymes and α -MEM. Cells were divided into 96-well microplate as much as 100 µl with density 3-5x10³ and incubated for 24 hours at 37°C.

Hydroxyapatite graft powder was diluted with α -MEM media according to the concentration dose, at 100 ppm, 50 ppm and 25 ppm. Each of 5 samples were dripped by hydroxyapatite graft crab shell at concentration of 100 ppm, 50 ppm and 25 ppm. Incubation was carried out for 24 hours then microscopic observation was performed to observe whether cytotoxic effects had occurred. 25µl of MTT was dripped, incubated, then dripped with 10µl of DMSO. The results were analyzed with ELISA reader with wavelength of 620 nm and viability of fibroblast living cells were calculated. The data obtained were tested by Oneway Anova and Post-hoc Tukey HSD.

4. RESULTS

The results of SEM micrograph was shown on Figure 1. It showed fineness and homogeneity of hydroxyapatite structure. The analysis of the element characterization of the hydroxyapatite graft, the EDX test was conducted and the result shown in Figure 2. The analysis then described in table 1 and showed that the dominant atom in hydroxyapatite graft derived from *Portunus pelagicus* was O followed by Ca and P.

Optical density (OD) value of formazan hydroxyapatite graft powder from *Portunus pelagicus* was measured using spectrophotometer. The mean value of formazan optical density in 5 samples for each treatment group and percentage of living cells can be seen in Table 2. From the result of MTT assay, it indicated that the treatment at concentrations of 100 ppm and 50 ppm is capable to reduce the number of living cells to a certain extent. The results will be analyzed using the LD50 parameter to assess the biocompatibility of hydroxyapatite graft powder from crab shells from the entire concentration group.

Kolmogorov-Smirnov test results showed that all groups have a normality probability value greater than 0.05 ($p > 0.05$) which means that the data was normally distributed. Data analysis was continued by testing the




Figure 2. EDX spectrum of hydroxyapatite samples from Portunus pelagicus with three main elements, O, Ca, and P.

Element	Normalized Weight Calculation (wt.%)	Atom Calculation (at.%)	Standard deviation
O	67,59	83,54	6,9
Ca	29,16	14,39	0,7
P	3,25	2,08	0,1

Table 1. Calculation of normalized weight and calculation of atoms in Hydroxyapatite Graft derived from Portunus pelagicus.

Treatment Group	N	Optical Density Mean	Standard Deviation	Percentage of Living Cells
Hydroxyapatite graft 100ppm	5	0,0684	0,017785	89,8%
Hydroxyapatite graft 50ppm	5	0,0724	0,018366	93,27%
Hydroxyapatite graft 25ppm	5	0,0816	0,018366	101,2%
Cell Control	5	0,0802	0,014704	100%
Media Control	5	0,0358	0,000837	0%

Table 2. The mean value of optical density and the percentage of living cells for each treatment.

sample variance homogeneity using Levene's test. The homogeneity test results indicated the significance value of 0.987 which means the data was homogeneous ($p > 0.05$). Data was normally distributed and homogeneous so the data needs to be tested using the Oneway Anova test with Post-Hoc Tukey HSD. Oneway Anova test was conducted to find out the overall difference in the sample group. From the test results shown the value of sig. = 0.752 which means there is no significant difference in




Figure 3. Microscopic images of fibroblast cells after hydroxyapatite graft powder exposure at concentration; A) 100 ppm, B) 50 ppm, and C) 25 ppm with 20x magnification.

the whole group because it had not met the sig requirements ($p < 0.05$).

5. DISCUSSION

The results of SEM micrograph was shown on Figure 1. It showed fineness and homogeneity of hydroxyapatite structure. The analysis of the element characterization of the hydroxyapatite graft, the EDX test was conducted and the result shown in Figure 2. The analysis then described in Table 1 and showed that the dominant atom in hydroxyapatite graft derived from Portunus pelagicus was O followed by Ca and P.

Optical density (OD) value of formazan hydroxyapatite graft powder from Portunus pelagicus was measured using spectrophotometer. The mean value of formazan optical density in 5 samples for each treatment group and percentage of living cells can be seen in Table 2. From the result of MTT assay, it indicated that the treatment at concentrations of 100 ppm and 50 ppm is capable to reduce the number of living cells to a certain extent. The results will be analyzed using the LD50 parameter to assess the biocompatibility of hydroxyapatite graft powder from crab shells from the entire concentration group.

Kolmogorov-Smirnov test results showed that all groups have a normality probability value greater than 0.05 ($p > 0.05$) which means that the data was normally distributed. Data analysis was continued by testing the sample variance homogeneity using Levene's test. The homogeneity test results indicated the significance value of 0.987 which means the data was homogeneous ($p > 0.05$). Data was normally distributed and homogeneous so the data needs to be tested using the Oneway Anova test with Post-Hoc Tukey HSD. Oneway Anova test was conducted to find out the overall difference in the sample group. From the test results shown the value of sig. = 0.752 which means there is no significant difference in the whole group because it had not met the sig requirements ($p < 0.05$).

6. CONCLUSION

From the results of this study it can be concluded that hydroxyapatite graft powder from Portunus pelagicus has biocompatible properties on HGF cell culture and at the lowest concentration of 25 ppm has optimal biocompatibility compared to the other two concentrations.

- **Declaration of patient consent:** The authors certify that they have obtained all appropriate patient consent forms.
- **Authors contribution:** Each author gave substantial contribution to the conception or design of the work and in the acquisition, analysis and interpretation of data for the work. Each author had role in

3

drafting the work and revising it critically for important intellectual content. Each author gave final approval of the version to be published and they agree to be accountable for all aspects of the work in ensuring that questions related to the accuracy or integrity of any part of the work are appropriately investigated and resolved.

- **Conflict of interest:** There are no conflicts of interest.
- **Financial support and sponsorship:** Nil.

REFERENCES

1. Emam SH. A Textbook of Advanced Oral and Maxillofacial Surgery. USA: InTech, 2013:617-638.
2. Sheikh Z, Sima C, Glogauer M. Bone Replacement Materials and Techniques Used for Achieving Vertical Alveolar Bone Augmentation. *Materials*. 2015; 8(1): 2953-2993.
3. Hardhani PR, Lastianny SP, Herawati D. Pengaruh penambahan platelet-rich plasma pada cangkok tulang terhadap kadar osteocalcin cairan sulkus gingiva pada terapi poket infraboni. *Jurnal PDGI*. 2013; 62(3): 75-82.
4. Reynolds MA, Aichelmann-Reidy ME, Branch-Mays GL. Regeneration of periodontal tissue: bone replacement graft. *Dental Clinics of North America*. 2010; 54(1): 55-71.
5. Delee ZC, Delee J, Drez D, Miller MD. Delee and Drez's Orthopaedic Sports Medicine. Virginia: Elsevier/ Saunders. 2009. 51.
6. Ichsan MZ. Sintesis makroporus komposit kolagen - hidrok-siapatit sebagai kandidat bone graft. *Journal saintek*. 2012; 60(1): 1-6.
7. Hassan KS., Alagl AS. Immediate Dental Implants and Bone Graft, Implant Dentistry - The Most Promising Discipline of Dentistry. USA: InTech, 2011: 1.
8. Dumitrescu A. Chemicals in surgical periodontal therapy. Berlin: Springer. 2011: 73-144.
9. Raya I, Mayasari E, Yahya A, Syahrul M, Lantura AI. Synthesis and Characterizations of Calcium Hydroxyapatite Derived from Crabs Shells (*Portunus pelagicus*) and Its Potency in Safe-guard against to Dental Demineralizations. *International Journal of Biomaterial*. 2015; 1(1): 1-8.
10. Fujii E, Kawabata K, Nakazaki Y. Fabrication of hydroxyapatite with controlled morphology in a micro-reactor. *Journal of the Ceramic Society of Japan*. 2011; 119(1386): 116-119.
11. Freshney IR. Culture of Animal Cells: A Manual of Basic Technique and Specialized Applications. Canada: John Wiley and Sons. 2016: 513-521.
12. Pegg DE. Principles of cryopreservation. *Methods in Molecular Biology*. 2017; 368: 39-57.
13. Kartono GS, Widyastuti, Setiawan HW. Biokompatibilitas graft cangkang kerang darah terhadap kultur sel fibroblas. *Denta Journal Kedokteran Gigi*. 2014; 8(1): 1-8.
14. Putra ATW, Ade W, Hamidy MY. Tingkat Kepadatan Fibroblas pada Luka Sayat Mencit dengan Pemberian Gel Lidah Buaya (*Aloe chinensis Baker*). *Jurnal Universitas Riau*. 2013; 1: 8.
15. Kasaj A, Willerhausen B, Reichert C, Kasaj AG, Zafiroopoulos GG, Schmidt M. Human periodontal fibroblast response to a nanostructural hydroxyapatite bone replacement graft in vitro. *Archive of Oral Biology*. 2008; 53(7): 7-11.

Biocompatibility of Portunus Pelagicus Hydroxyapatite Graft on Human Gingival Fibroblast Cell Culture

ORIGINALITY REPORT

17%

SIMILARITY INDEX

15%

INTERNET SOURCES

6%

PUBLICATIONS

3%

STUDENT PAPERS

PRIMARY SOURCES

1	www.bibliomed.org Internet Source	3%
2	Submitted to Universitas Airlangga Student Paper	3%
3	repository.medri.uniri.hr Internet Source	3%
4	pubmed.ncbi.nlm.nih.gov Internet Source	2%
5	Anas M Fallatah, Areej J Bahrawi, Hussam M Babatin, Khalid M Nassibi, Yousef AlEdreesi, Hassan S Abduljabbar. "Pregnancy Outcomes among Obese Pregnant Women with Varying Levels of Vitamin D in King Abdulaziz University Hospital: A Single-center Retrospective Study", Cureus, 2019 Publication	1%
6	ejobios.org Internet Source	1%

7	Sheikh, Zeeshan, Corneliu Sima, and Michael Glogauer. "Bone Replacement Materials and Techniques Used for Achieving Vertical Alveolar Bone Augmentation", Materials, 2015. Publication	1 %
8	ejournal.poltekkes-smg.ac.id Internet Source	1 %
9	revista.uepb.edu.br Internet Source	1 %
10	zombiedoc.com Internet Source	1 %
11	de.scribd.com Internet Source	<1 %
12	www.hindawi.com Internet Source	<1 %

Exclude quotes Off
Exclude bibliography On

Exclude matches < 7 words

Biocompatibility of Portunus Pelagicus Hydroxyapatite Graft on Human Gingival Fibroblast Cell Culture

GRADEMARK REPORT

FINAL GRADE

/0

GENERAL COMMENTS

Instructor

PAGE 1

PAGE 2

PAGE 3

PAGE 4
