

ADVANCED PHARMACEUTICAL AND HERBAL NANOSCIENCE FOR TARGETED DRUG DELIVERY SYSTEMS PART II

Editors:
Swarnlata Saraf
Ram Kumar Sahu
Vivek Dave

Bentham Books



Advanced Pharmaceutical Herbal Nanoscience: Targeted Drug Delivery System

Part II

Edited by

Chief Editor:

Prof. (Dr.) Swarnlata Saraf

*Professor & Director, University Institute of Pharmacy,
Pt Ravishankar Shukla University,
Raipur-492010, Chhattisgarh, India*

Editor:

Dr. Ram Kumar Sahu

*Assistant Professor, Department of Pharmaceutical Science,
Sushruta School of Medical
and Paramedical Sciences,
Assam University (A Central University),
Silchar-788011, Assam, India*

&

Dr. Vivek Dave

*Associate Professor & Head, Department of
Pharmacy, School of Health Science,
Central University of South Bihar,
Bihar-824236, India*

**Advanced Pharmaceutical Herbal Nanoscience:
Targeted Drug Delivery System (Part II)**

Editors: Swarnlata Saraf, Ram Kumar Sahu and Vivek Dave

ISBN (Online): 978-981-5036-54-1

ISBN (Print): 978-981-5036-55-8

ISBN (Paperback): 978-981-5036-56-5

© 2022, Bentham Books imprint.

Published by Bentham Science Publishers Pte. Ltd. Singapore. All Rights Reserved.

For personal private use only
Not be distributed or uploaded to anyone or anywhere

BENTHAM SCIENCE PUBLISHERS LTD.

End User License Agreement (for non-institutional, personal use)

This is an agreement between you and Bentham Science Publishers Ltd. Please read this License Agreement carefully before using the ebook/echapter/ejournal (“**Work**”). Your use of the Work constitutes your agreement to the terms and conditions set forth in this License Agreement. If you do not agree to these terms and conditions then you should not use the Work.

Bentham Science Publishers agrees to grant you a non-exclusive, non-transferable limited license to use the Work subject to and in accordance with the following terms and conditions. This License Agreement is for non-library, personal use only. For a library / institutional / multi user license in respect of the Work, please contact: permission@benthamscience.net.

Usage Rules:

1. All rights reserved: The Work is the subject of copyright and Bentham Science Publishers either owns the Work (and the copyright in it) or is licensed to distribute the Work. You shall not copy, reproduce, modify, remove, delete, augment, add to, publish, transmit, sell, resell, create derivative works from, or in any way exploit the Work or make the Work available for others to do any of the same, in any form or by any means, in whole or in part, in each case without the prior written permission of Bentham Science Publishers, unless stated otherwise in this License Agreement.
2. You may download a copy of the Work on one occasion to one personal computer (including tablet, laptop, desktop, or other such devices). You may make one back-up copy of the Work to avoid losing it.
3. The unauthorised use or distribution of copyrighted or other proprietary content is illegal and could subject you to liability for substantial money damages. You will be liable for any damage resulting from your misuse of the Work or any violation of this License Agreement, including any infringement by you of copyrights or proprietary rights.

Disclaimer:

Bentham Science Publishers does not guarantee that the information in the Work is error-free, or warrant that it will meet your requirements or that access to the Work will be uninterrupted or error-free. The Work is provided "as is" without warranty of any kind, either express or implied or statutory, including, without limitation, implied warranties of merchantability and fitness for a particular purpose. The entire risk as to the results and performance of the Work is assumed by you. No responsibility is assumed by Bentham Science Publishers, its staff, editors and/or authors for any injury and/or damage to persons or property as a matter of products liability, negligence or otherwise, or from any use or operation of any methods, products instruction, advertisements or ideas contained in the Work.

Limitation of Liability:

In no event will Bentham Science Publishers, its staff, editors and/or authors, be liable for any damages, including, without limitation, special, incidental and/or consequential damages and/or damages for lost data and/or profits arising out of (whether directly or indirectly) the use or inability to use the Work. The entire liability of Bentham Science Publishers shall be limited to the amount actually paid by you for the Work.

General:

1. Any dispute or claim arising out of or in connection with this License Agreement or the Work (including non-contractual disputes or claims) will be governed by and construed in accordance with the laws of Singapore. Each party agrees that the courts of the state of Singapore shall have exclusive jurisdiction to settle any dispute or claim arising out of or in connection with this License Agreement or the Work (including non-contractual disputes or claims).
2. Your rights under this License Agreement will automatically terminate without notice and without the

need for a court order if at any point you breach any terms of this License Agreement. In no event will any delay or failure by Bentham Science Publishers in enforcing your compliance with this License Agreement constitute a waiver of any of its rights.

3. You acknowledge that you have read this License Agreement, and agree to be bound by its terms and conditions. To the extent that any other terms and conditions presented on any website of Bentham Science Publishers conflict with, or are inconsistent with, the terms and conditions set out in this License Agreement, you acknowledge that the terms and conditions set out in this License Agreement shall prevail.

Bentham Science Publishers Pte. Ltd.

80 Robinson Road #02-00

Singapore 068898

Singapore

Email: subscriptions@benthamscience.net



For personal private use only
Not be distributed or uploaded to anyone or anywhere

CONTENTS

FOREWORD	i
PREFACE	ii
LIST OF CONTRIBUTORS	iv
CHAPTER 1 PHARMACEUTICAL NANOSCIENCES AND THEIR APPLICATION IN THE DELIVERY OF VARIOUS PHYTOCONSTITUENTS	1
<i>Retno Widjowati and Andang Miatmoko</i>	
INTRODUCTION	2
PHYTOCONSTITUENTS IN HERBAL MEDICINE	3
Phenolic	3
Terpenoid	5
Alkaloid	6
Anthraquinone	7
NANOTECH FOR THE DELIVERY OF DIFFERENT PHYTOCONSTITUENTS	8
Liposome	9
Microemulsion	10
Solid Lipid Nanoparticles and Nanostructured Lipid Carriers	11
Inorganic Nanoparticles	13
Liquid Crystalline Systems	13
POLYMER NANOPARTICLES	14
Dendrimers	16
THERAPEUTICAL APPLICATION	17
Cancer	18
Rheumatoid	18
Nutraceutical Delivery	21
CONCLUSION	24
CONSENT FOR PUBLICATION	24
CONFLICT OF INTEREST	24
ACKNOWLEDGEMENTS	24
REFERENCES	24
CHAPTER 2 DESIGN OF COSMECEUTICAL DRUG DELIVERY SYSTEM: ROLE OF NANOTECHNOLOGY IN COSMECEUTICALS	33
<i>Vipin Kumar, Pankaj Bhatt, Mayank Kumar Malik and Arun Kumar</i>	33
INTRODUCTION	34
Merits of Nanocosmeceuticals	35
Demerits Of Nano Cosmeceuticals	35
NOVEL NANOCARRIERS IN COSMECEUTICALS	36
Niosomes	36
Liposomes	37
Nanocapsule	38
Lipid Nanoparticles And Lipid Nano-Carriers (SLN And NLC)	39
Nanogold and Nanosilver	40
Nanoemulsions	41
Nano Sphere	41
Cubosomes	43
MAJOR NANOCOSMECEUTICAL CLASS	44
Skincare	44
Haircare	44

Lip Care	45
Nail Care.....	45
NANOTECHNOLOGY IN HERBAL DRUGS- NANOPHYTOMEDICINE	45
Nanocurcumin.....	45
Green Nanotechnology (Cumin- Mediated Gold Nanoparticle).....	46
Ayurvedic Bhasma.....	46
Aloe Vera Extract In Nanoparticles	46
EMERGING CHALLENGES AND POTENTIAL SOLUTIONS	47
Cellular Toxicity Of Zinc Oxide And Titanium Dioxide Nanoparticles.....	47
Occupational Risks Of Nanoparticles	48
Potential Solutions	48
<i>Physical-Chemical Properties.....</i>	<i>49</i>
<i>Mathematical Modelling.....</i>	<i>49</i>
<i>Microscopic Techniques.....</i>	<i>49</i>
<i>In vitro methods.....</i>	<i>49</i>
FUTURE PROSPECT OF NANOTECHNOLOGY IN NANO COSMECEUTICALS.....	49
CONCLUSION.....	50
CONSENT FOR PUBLICATION.....	51
CONFLICT OF INTEREST.....	51
ACKNOWLEDGEMENTS	51
REFERENCES	51
CHAPTER 3 TRANSFERSOME: A NOVEL VESICULAR TRANSDERMAL DELIVERY SYSTEM	59
<i>Nagaraja Sreeharsha and Santosh Fattepur</i>	
INTRODUCTION	60
ADVANTAGES AND DISADVANTAGES.....	60
COMPOSITION AND ITS MECHANISM.....	62
TRANSFERSOMES PENETRATION MECHANISM	63
APPLICATION OF TRANSFERSOMES AS THE TRANSDERMAL DELIVERY SYSTEM	64
Delivery of Antioxidant	64
Delivery of Anticancer Drug.....	65
Delivery of Corticosteroids.....	65
Delivery of Anti-inflammatory Drugs.....	65
Delivery of Insulin	65
Delivery of Protein and Peptide	66
Delivery of Interferon	66
Delivery of Anesthetics.....	66
Delivery of NSAIDs	67
DELIVERY OF HERBAL DRUG	67
REGULATORY ASPECTS.....	67
LIMITATION OF TRANSFERSOMES	69
FUTURE PERSPECTIVE.....	69
CONCLUSION.....	69
CONSENT FOR PUBLICATION.....	70
CONFLICT OF INTEREST.....	70
ACKNOWLEDGEMENTS	70
REFERENCES	70
CHAPTER 4 SELF-NANO/MICRO EMULSIFIED DRUG DELIVERY SYSTEM	73
<i>Vishal Trivedi and Jiyauddin Khan</i>	

INTRODUCTION	73
HERBAL MEDICINE IS A NOVEL DRUG DELIVERY SYSTEM	74
HERBAL NANOMEDICINES OF SNEDDS AND SMEDDS	74
SELF EMULSIFICATION PROCESS	77
Self-Nano Emulsifying Drug Delivery System (SNEDDS)	77
Self-Micro Emulsifying Drug Delivery System (SMEDDS)	77
INGREDIENTS REQUIRED FOR THE FORMATION OF SELF-EMULSIFICATION	
DRUG DELIVERY SYSTEM	77
Excipients	77
Surfactants	78
Co-Surfactant	78
IMPORTANT OF SEDDS	79
MECHANISM OF SEDDS	79
DOSAGE FORMS FROM SEDDS	80
Dry Emulsions	80
Sustained and Controlled-release Tablets	80
Self-emulsifying Suppositories	80
Implants of Self-emulsifying.....	80
DRUG PROPERTIES AND CHARACTERIZATION OF SEDDS	81
For the Characterisation of SEDDS	81
BIOAVAILABILITY ENHANCEMENT OF DRUGS BY SEDDS	81
SNEDDS AND SMEDDS IMPROVED DISSOLUTION RATE AND BIOAVAILABILITY	
OF POORLY SOLUBLE DRUG	82
Surfactants' Effect	82
Lipids' Effect	82
P-glycoprotein Inhibition	83
SNEDDS AND SMEDDS DRUG DELIVERY SYSTEM FOR IMPROVING THE	
BIOAVAILABILITY/LYMPHATIC UPTAKE/LIVER UPTAKE/ PEPTIDE	83
ADVANTAGES OF SELF-EMULSIFYING DRUG DELIVERY	84
DISADVANTAGES OF SELF-EMULSIFYING DRUG DELIVERY SYSTEMS	84
EMERGING CHALLENGES AND POTENTIAL SOLUTIONS OF SNEDDS AND	
SMEDDS	84
MARKETED PRODUCTS OF SEDDS	85
FUTURE PROSPECTS	86
CONCLUSION	86
CONSENT FOR PUBLICATION	86
CONFLICT OF INTEREST	87
ACKNOWLEDGEMENTS	87
REFERENCES	87

CHAPTER 5 PHYTOSOMES 94

Ram Kumar Sahu and Vinod Nautiyal

INTRODUCTION	94
Phytosome/Herbosome/Pharmacosome/Liposome	95
Phytosome or Herbosome	95
Pharmacosomes	95
Liposomes.....	95
PHYTOSOME VS. LIPOSOME	95
PREREQUISITES FOR PHYTOSOME/HERBOSOME/LIPOSOME FORMATION	96
Selection of Active Phytoconstituents or Standardized Extract	96
Phospholipids.....	96

Not be shared or uploaded anywhere

Structure of Phospholipids	96
Glycerophospholipids	96
Sphingomyelins	97
PHYTO-PHOSPHOLIPID COMPLEX: PHYTOSOME TECHNOLOGY	97
PROPERTIES OF HERBOSOMES (PHYTOPHOSPHOLIPID COMPLEX).....	98
Physical Properties.....	98
Chemical Properties.....	98
Biological Properties.....	99
MERITS OF PHYTOPHOSPHOLIPID COMPLEXES (HERBOSOMES).....	99
PREPARATION OF HERBOSOMES	100
Phospholipids.....	100
Solvents	100
Phytoconstituents	101
METHODS OF PREPARATION OF HERBOSOMES.....	101
Anti-solvent Precipitation	102
Solvent Evaporation Method	102
Ether Injection Method	102
Rotary Evaporation Method.....	103
NOVEL METHODS FOR HERBOSOMES PREPARATION	103
DOSAGE FORMS OF HERBOSOMES	103
Capsules.....	103
Hard Gelatin Capsule	103
Soft Gelatin Capsule	104
Tablets	104
Topical Preparations	104
OPTIMIZATION OF HERBOSOMES.....	104
CHARACTERIZATION OF HERBOSOMES.....	105
Partition Coefficient and Solubility	105
Particle Size and Zeta Potential.....	105
Yield	105
Entrapment Efficiency	106
Crystallinity and Polymorphism	106
Stability of Vesicles	106
Transition Temperature.....	106
Measurement of Surface Tension Activity.....	106
Drug Release.....	107
Spectroscopic Confirmation of Herbosomes.....	107
Fourier Transform IR Spectroscopy.....	107
Proton NMR (1H NMR)	107
13C NMR	107
SEM/TEM	108
X-Ray Diffraction	108
MARKETED HERBOSOMES	108
LIMITATIONS OF HERBOSOMES.....	112
FUTURE PERSPECTIVES OF HERBOSOMES	112
CONCLUSION.....	113
CONSENT OF PUBLICATION	113
CONFLICT OF INTEREST	113
ACKNOWLEDGEMENTS	114
REFERENCES	114

CHAPTER 6 ROLE OF NANOMEDICINES IN OCULAR TARGETING DRUG DELIVERY SYSTEMS	116
<i>Claire Faye C. Zipagan and Erwin Martinez Faller</i>	
INTRODUCTION	116
THE HUMAN EYE	117
DISEASES OF THE HUMAN EYE	120
OCULAR DRUG ADMINISTRATIONS	121
BARRIERS OF THE EYES	123
Barriers in Intravitreal Injections	123
Barriers in Subretinal Injections	124
Barriers in Intravenous Administration	125
Barriers in Suprachoroidal Administration	125
Barriers Encountered After Transscleral Administration	125
NANOTECHNOLOGY	126
NANOTECHNOLOGY IN OCULAR DISEASES	127
NANOTECHNOLOGY IN THE DIAGNOSIS OF OCULAR DISEASE	128
NANOSYSTEMS FOR THE TREATMENT OF ANTERIOR OCULAR DISEASE	129
NANOSYSTEMS FOR THE TREATMENT OF POSTERIOR OCULAR DISEASE	130
NANOSYSTEMS FOR THE TREATMENT OF GLAUCOMA	131
EXOSOMES IN THE TREATMENT OF OCULAR DISEASES	132
EMERGING STRATEGIES IN OCULAR DRUG DELIVERY BASED ON NANOMEDICINE	133
Contact Lens	133
Hydrogels	134
Liposomes	135
Niosomes	135
Solid Lipid Nanoparticle (SLN)	136
Nanostructured Lipid Carrier (NLC)	136
Inorganic Nanoparticles	136
Polymeric Micelles	136
Nanosuspension	136
Nanoemulsions	136
Light-Responsive Nanoparticles	137
Mesoporous Silica Nanoparticles	137
FUTURE DIRECTIONS	137
CONCLUSION	138
CONSENT OF PUBLICATION	138
CONFLICT OF INTEREST	138
ACKNOWLEDGEMENTS	138
REFERENCES	138
CHAPTER 7 COLLOIDOSOME AS AN EFFICIENT NOVEL DRUG DELIVERY SYSTEM: AN UPDATE	141
<i>Payal Kesharwani, Ankit Jain, Smita Jain, Vivek Dave and Swapnil Sharma</i>	
INTRODUCTION	141
NATURAL POLYMERS FOR THE MANUFACTURING OF COLLOIDOSOMES	143
Chitosan	143
Alginate	144
Cellulose	144
Dextran	144
Gelatin	145

SYNTHESIS OF COLLOIDOSOMES.....	145
Emulsion Based Approach.....	145
Solvent Evaporation Method	147
Cross-linked Colloidosomes	148
Layer-by Layer	148
Thermal Annealing	149
Gel Trapping Technique	150
TYPES OF COLLOIDOSOMES.....	150
Patchy Colloidosomes.....	150
Aqueous Core Colloidosomes.....	151
Responsive Colloidosomes	152
Coated Colloidosomes	153
Hybrid Colloidosomes	153
STABILITY OF COLLOIDOSOMES	153
APPLICATION	155
Colloidosomes for Target Drug Delivery.....	155
Tumour Targeting	156
Brain Targeting.....	156
Colloidosomes as a Carrier of a Drug	157
<i>Delivery of Small Molecules.....</i>	<i>157</i>
<i>Biological Molecules.....</i>	<i>157</i>
Colloidosomes for Controlled and Sustained Release.....	157
Colloidosomes for Cosmetic and Dermatology	158
CONCLUSION AND FUTURE PROSPECTIVE	159
CONSENT FOR PUBLICATION	159
CONFLICT OF INTEREST	159
ACKNOWLEDGEMENTS	159
REFERENCES	160

CHAPTER 8 HERBAL NANOSCIENCE: CHALLENGES AND REGULATORY

PERSPECTIVE.....	166
<i>Vishal Soni, Priyanka Soni, Ritika Gururani and Jaya Dwivedi</i>	
INTRODUCTION	167
Advantages of Herbal Drugs.....	168
Drug Delivery Systems Based On Nanomedicines	168
Requirement For Nano based Delivery System for Herbal Remedies.....	168
Advantages of Novel Drug Delivery System	169
Regulatory Guidelines For Herbal Nanomedicines.....	170
Indian Regulations and Strategy	170
Quality Control Associated With Herbal Medicinal Products.....	171
European Regulations And Guidelines	172
Regulatory Challenges For Herbal Nanomedicines	174
Challenges Associated With The Regulatory Status Of Herbal-based Medicines.....	174
Challenges Associated With The Evaluation Of Safety And Efficacy	174
Challenges Associated With Quality Control Of Herbal-based Medicines	174
Challenges Associated With The Safety Evaluation Of Herbal Medicines	175
Regulations	175
Changes in Regulations Of Herbal Medicines Worldwide.....	175
Herbal Nanomedicines Already Approved For Clinical Use	177
Category 1: Indigenous Herbal Medicines.....	177
Category 2: Herbal Medicines In Medicine systems.....	177

Category 3: Modified Herbal Medicines	177
Category 4: Imported Products With Herbal Medicine Base	177
Emerging Challenges and Potential Solutions.....	178
Future Prospects.....	178
CONCLUSION.....	180
CONSENT FOR PUBLICATION.....	180
CONFLICT OF INTEREST.....	180
ACKNOWLEDGEMENTS	180
REFERENCES	180
CHAPTER 9 DENDRIMERS: A VERSATILE NANOPLATFORM FOR ADVANCED TARGETING AND BIOACTIVE(S) DELIVERY.....	185
<i>Priya Shrivastava1, Udit Agrawal, Rajeev Sharma and S.P. Vyas</i>	
INTRODUCTION	185
POTENTIAL APPLICATIONS OF DENDRIMERS	188
Dendrimers in Targeted Delivery of Bioactive(s)	188
Dendrimers in Oral Delivery of Bioactive(s)	189
Dendrimers in Ocular Delivery of Bioactive(s).....	190
Dendrimers in Microvascular Extravasation	191
Dendrimers in Intracellular Delivery of Bioactive(s).....	191
Dendrimers in Tuberculosis Therapy	192
Dendrimers in CNS Delivery of Bioactive(s).....	193
Dendrimers in Transdermal/topical Delivery of Bioactive(s).....	196
CONCLUSION.....	196
CONSENT FOR PUBLICATION.....	196
CONFLICT OF INTEREST.....	196
ACKNOWLEDGEMENTS	196
REFERENCES	197
CHAPTER 10 TARGETED DRUG DELIVERY SYSTEM TO CELL AND CELL ORGANELLES.....	202
<i>Kenny Shane P. Alojado and Erwin Martinez Faller</i>	
INTRODUCTION	202
CROSSING CELLULAR BARRIERS	203
Lipid-Based Drug Delivery System	204
CANCER RESEARCH AND CELLULAR DRUG DELIVERY SYSTEM	205
GOAL OF THE DRUG DELIVERY SYSTEM.....	208
EXTRACELLULAR VESICLE-BASED DRUG DELIVERY SYSTEM.....	208
IMPORTANCE OF EV-BASED DRUG DELIVERY SYSTEM.....	209
EXOSOMES AS NOVEL SHUTTLE DELIVERY	210
MITOCHONDRIA-TARGETED DRUG DELIVERY	212
MACROPHAGE DRUG DELIVERY	213
CARRIER-BASED DRUG DELIVERY SYSTEM.....	215
CONCLUSION.....	217
FUTURE DIRECTIONS.....	218
CONSENT OF PUBLICATION	218
CONFLICT OF INTEREST.....	218
ACKNOWLEDGEMENT	218
REFERENCES	218
CHAPTER 11 NANOTOXICOLOGY: CURRENT ISSUES AND FUTURE DIRECTIONS.....	220
<i>Maria Maichol P. Ababan and Erwin Martinez Faller</i>	

INTRODUCTION	220
Immune System	221
PHYSICOCHEMICAL IDENTIFICATION OF NANOMATERIALS	221
ROLE OF NANOPARTICLES IN CANCER DIAGNOSIS AND TREATMENT	221
KNOWING THE IMMUNE SYSTEM'S PART IN NANOPARTICLE DECOMPOSITION	222
UTILIZING NANOPARTICLES IN DIMINISHING TOXICITIES OF CONVENTIONAL	
MEDICINES	222
TOXICITY TESTING	223
CONCLUSION	223
FUTURE DIRECTIONS OF NANOTOXICOLOGY	224
CONSENT FOR PUBLICATION	224
CONFLICT OF INTEREST	224
ACKNOWLEDGEMENTS	224
REFERENCES	225
CHAPTER 12 LIPOSOMES FOR HERBAL DRUG DELIVERY	227
<i>Andang Miatmoko, Devy Maulidya Cahyani and Retno Widyowati</i>	
INTRODUCTION	227
Liposomes as Drug Carriers	232
Preparation of Liposomes	232
Manufacturing of Liposomes	237
1. Thin Film Hydration	238
2. Reverse Phase Evaporation	239
3. Ethanol Injection	240
The use of liposomes for herbal product delivery	240
1. Liposomes increase herbal drugs solubility	240
2. Liposomes improve the bioavailability and pharmacological effects of herbal drugs	244
The use of nanoliposomes for enhanced drug delivery	247
Long Circulating Liposomes	248
Ligand Targeting Liposomes	248
Factors Affecting the Encapsulation of Herbal Extract in Liposomes	250
CONCLUSION	251
Future Prospective	252
CONSENT FOR PUBLICATION	252
CONFLICT OF INTEREST	252
ACKNOWLEDGEMENTS	252
REFERENCES	252
CHAPTER 13 AI IN PHARMACY, HERBAL MEDICINE AND DRUG DELIVERY: A SCI-FI	
OR A REALITY	259
<i>Srija Sur, Prashansa Sharma and Vivek Dave</i>	
INTRODUCTION	259
HISTORY OF AI	261
IMPORTANCE OF ARTIFICIAL INTELLIGENCE	264
Advantages	265
RISK AND DISADVANTAGE OF AI	267
ROBOTS AND ARTIFICIAL INTELLIGENCE	270
POLICY OF AI	273
AI Policy of India	275
<i>Fairness, Ethics, and Human Rights</i>	276
<i>Encouraging AI Research</i>	277
<i>Other Laws which Directly or Indirectly Influence AI</i>	277

<i>Consumer Protection Law</i>	278
TOOLS OF ARTIFICIAL INTELLIGENCE	278
IBM Watson for Oncology	278
Erica Robot.....	279
TUG Robots.....	279
Robot Pharmacy.....	279
MEDi Robot.....	280
Magnetolectric Nanorobots	280
DNA Nanorobots	280
DRUG DISCOVERY AND DRUG DESIGN	281
QSAR Studies	281
Eve- the Scientist Robot.....	282
Insilico Medicines.....	282
Artificial Intelligence Related Start-ups.....	283
APPLICATION OF AI IN HEALTHCARE AND PHARMACY	283
Customised Treatment	283
CLINICAL TRIAL RESEARCH	283
DATA MANAGEMENT	284
Cancer Diagnosis	285
Epidemic Outbreak Prediction	285
Accessible Healthcare	285
The Future Aspect of AI	286
<i>Robotic Scientists</i>	286
<i>Automated Transport</i>	286
<i>Taking over Dangerous Jobs</i>	286
<i>Robotic Friend</i>	286
<i>Robots as Caretakers</i>	286
<i>Robots as a Pet</i>	287
<i>Robot-assisted Surgery</i>	287
<i>Artificial Intelligence on Herbal Medicine</i>	287
CONCLUSION	290
CONSENT OF PUBLICATION	290
CONFLICT OF INTEREST	290
ACKNOWLEDGEMENTS	290
REFERENCES	290
SUBJECT INDEX	294

Not be distributed or uploaded to anyone anywhere

FOREWORD



Prof. Sanjay Singh,
Vice Chancellor,
Babasaheb Bhimrao Ambedkar University
(A Central University),
Lucknow, Uttar Pradesh
India

Currently, various drug delivery systems are being developed to minimize drug degradation, prevent toxic effects, improve drug bioavailability, and increase drug accumulation at the disease target site. Nano based drug delivery offers significant advantages in terms of targeted drug delivery, transport, and release to achieve better therapeutic efficacy. This system is rapidly becoming one of the most important tools in the field of nanomedicine.

In the book titled "**Advance Pharmaceutical Herbal Nanoscience: Targeted Drug Delivery System Part II**," the author aims to provide a comprehensive overview of herbal nanoscience, including its production, evaluation, regulatory perspective and application. Herbal drugs are widely used worldwide, and their therapeutic efficacy depends on the nature of active constituents. The higher molecular weight and aqueous solubility of active ingredients, which cannot penetrate the lipid membranes of cells, lead to a decrease in bioavailability and efficacy. The combination of herbal medicine and nanotechnology has been widely recommended as nanostructured systems have the potential to overcome the above limitations. The nano-based delivery system improves the bioavailability of herbal medicines by delivering a sufficient amount of the drug to the target site of the disease.

In this book, an overview of recent advances in plant-based nanomedicine is presented. Each chapter attempts to describe the introduction, concept, progress, current status, and future prospects of plant-based nanomedicine. In addition, the book includes an overview of research in the field of plant-based nanoscience and some of the most fascinating findings from this study. The book also examined the difficulties and regulatory implications of plant-based nanoscience.

The authors of this book have succeeded in addressing the development that has been attempted in the area of novel plant-based drug delivery. This is a useful book and resource for undergraduate students, graduate students, researchers, and academicians who are exploring concepts for a nano-based drug delivery system and its performance.

PREFACE

The objective of the book entitled “**Advanced Pharmaceutical Herbal Nanoscience: Targeted Drug Delivery System**” is to offer an understanding of various herbal novel drug delivery systems, their preparations, characterization and exciting range of applications. Herbal nanoscience targeted drug delivery system demands a broad range of awareness in novel drug delivery systems. It is very important to have detailed knowledge and awareness of new technology or new process about the various herbal nanoscience products and their composition. The awareness of knowledge about the properties of various herbal constituents of a nanoformulation is also very important because it decides the determination of the formulation of the delivery systems and broadly ensures its properties. This book covers a broad spectrum of herbal nanoscience topics required to appropriately give formulation procedure, evaluation and applications of herbal drug delivery systems and correlate it with treating many diseases.

It expresses huge awareness and knowledge regarding advanced pharmaceutical, herbal nanoscience targeted drug delivery systems in the aspect of the application in drug delivery and herbal nanomedicine. In addition to this, the book covers all major topics like drug development issues, adaptation to clinical use, market prospects and industrial commercialization too, which come under advanced pharmaceutical nanoscience and nanotechnology application. Apart from the application section, it discusses in detail the safety, herbal nanotechnology, regulatory, targeting aspects and social scenario of pharmaceutical nanoscience. The book not only focuses on theoretical knowledge but also considers practical aspects. The book is quite beneficial for students and researchers across the globe who are indulged in the reading and investigation of advanced pharmaceutical, herbal nanoscience and related nanotechnology, thereby spreading awareness all over the globe and promoting anticipated trends in the field of nanoscience and nanotechnology. The major objective of this initiative is to bring all the fundamental concepts, target delivery, herbal bioactive, and nanomedicine, all in a common platform that will provide knowledge about all the possible advanced pharmaceutical, herbal nanoscience drug delivery systems. Some major chapters to be published in the book include nucleic acid-based therapeutic, electrosomes, aquasomes, phytosomes, guggulosome, niosomes, self nano/micro emulsified drug delivery system, the concept of targeted drug delivery system, application of herbal Bioactive and many more. This valuable resource will make the readers more aware of novel drug delivery systems as well as their promising applications in drug targeting and nanotheronostics, thereby improving the pharmaceutical world's situation.

The book's aim is to provide a single volume covering a detailed description of various herbal drug delivery systems, their principles and how these are put in use for the treatment of vivid diseases. The book has been divided into four sections. The first section deals with the fundamentals of advanced pharmaceutical nanoscience, whereas the second section deals with a detailed overview of the novel and efficient advanced pharmaceutical nanoscience delivery systems in the field of pharmaceutical science in which some major topics will be published in the book, which includes nucleic acid-based therapeutic, electrosomes, aquasomes, phytosomes, guggulosome, niosomes, self nano/micro emulsified drug, *etc.* This section is quite unique as it elaborately describes the major main beliefs and techniques of the preparations of the herbal drug delivery systems. This furnishes a quite unique and updated coverage of the essential areas that guide the underlying science behind these therapeutic delivery systems. The distinguished authors have emphasized on providing a complete insight into the advanced pharmaceutical nanoscience drug delivery systems with their convenient applications in the field of herbal nanoscience technology. The third section mainly involves diseases specific to advanced pharmaceutical nanoscience targeted drug delivery systems like cancer, infectious

diseases, brain diseases, *etc.* Finally, the fourth and the last section of the book provides the application of herbal bioactive in pharmaceutical, herbal nanoscience targeted drug delivery systems.

This advanced book has been designed keeping in mind the young and new researchers and scientists who are working dedicatedly in the field of health/medicine and the pharmaceutical sector. This book promises a detailed, informative description of advanced herbal and absolutely modern pharmaceutical dosage forms and drug delivery systems. The information furnished in the book is sure to serve society.



Dr. Swarnlata Saraf
Professor & Director University Institute of Pharmacy
Pt Ravishankar Shukla University
Raipur-492010, Chhattisgarh, India



Dr. Ram Kumar Sahu
Assistant Professor, Department of Pharmaceutical Science
Sushruta School of Medical and Paramedical Sciences
Assam University (A Central University)
Silchar-788011, Assam, India



Dr. Vivek Dave
Associate Professor & Head, Department of Pharmacy
School of Health Science Central University of South Bihar
Bihar -824236, India

List of Contributors

- Andang Miatmoko** Department of Pharmaceutical Science, Faculty of Pharmacy, Universitas Airlangga, Surabaya, 60115, Indonesia
- Ankit Jain** Department of Material Engineering, IISC, Bangalore, India
- Arun Kumar** Department of Chemistry, Department of Pharmaceutical Science, Gurukul Kangri (Deemed to be University), Haridwar, Uttarakhand, India
- Claire Faye C. Zipagan** Graduate School, Centro Escolar University, Manila, Philippines
Cognizant Technology Solutions, Taguig City, Philippines
Pharmacy Department, San Pedro College, Davao City, Philippines
- Devy Maulidya Cahyani** Department of Pharmaceutical Science, Faculty of Pharmacy, Universitas Airlangga, Surabaya, 60115, Indonesia
- Erwin Martinez Faller** School of Pharmacy, San Pedro College, Philippines/Graduate School, Centro Escolar University, Manila, Philippines
- Jaya Dwivedi** Department of Chemistry, Banasthali Vidyapith, Banasthali, P.O. Rajasthan-304022, India
- Jiyauddin Khan** School of Pharmacy, Management and Science University, 40100 Shah Alam, Selangor, Malaysia
- Kenny Shane P.** Alojado, Graduate School, Centro Escolar University, Manila, Philippines
- Maria Maichol P.** Ababan, Graduate School, Centro Escolar University, Manila, Philippines
- Mayank Kumar Malik** KIET School of Pharmacy, KIET Group of Institutions, Muradnagar, Ghaziabad, U.P, India
- Nagaraja Sreeharsha** Department of Pharmaceutical Sciences, College of Clinical Pharmacy, King Faisal University, Al-Ahsa-31982, Saudi Arabia
Department of Pharmaceutics, Vidya Siri College of Pharmacy, Off Sarjapura Road, Bengaluru - 560 035, Karnataka, India
- Pankaj Bhatt** Department of Pharmaceutical Science, Gurukul Kangri (Deemed to be University), Haridwar, Uttarakhand, India
- Payal Kesharwani** Department of Pharmacy, Banasthali Vidyapith, Banasthali, India
- Prashansa Sharma** Department of Home Science, Mahila Mahavidyalaya, Banaras Hindu University, India
- Priya Shrivastava** Drug Delivery Research Laboratory, Department of Pharmaceutical Sciences, Dr. H. S. Gour Vishwavidyalaya, Sagar, M.P., 470003, India
- Priyanka Soni** Department of Herbal Drug Research, B.R. Nahata College of Pharmacy, Research Centre, Mhow Neemuch Road, Mandsaur 458001, India
- Rajeev Sharma** Drug Delivery Research Laboratory, Department of Pharmaceutical Sciences, Dr. H. S. Gour Vishwavidyalaya, Sagar, M.P., 470003, India
- Ram Kumar Sahu** Department of Pharmaceutical Sciences, Sushruta School of Medical and Paramedical Sciences, Assam University (A Central University), Silchar-788011, Assam, India
- Retno Widjowati** Department of Pharmaceutical Science, Faculty of Pharmacy, Universitas Airlangga, Surabaya, 60115, Indonesia
Natural Product Drug Discovery and Development Research Group, Faculty of Pharmacy, Universitas Airlangga, Surabaya 60115, Indonesia

Ritika Gururani	Department of Pharmacy, Banasthali Vidyapith, Banasthali, P.O. Rajasthan-304022, India
S. P. Vyas	Drug Delivery Research Laboratory, Department of Pharmaceutical Sciences, Dr. H. S. Gour Vishwavidyalaya, Sagar, M.P., 470003, India
Santosh Fattepur	School of Pharmacy, Management and Science University, Seksyen 13, 40100 Shah Alam, Selangor, Malaysia
Smita Jain	Department of Pharmacy, Banasthali Vidyapith, Banasthali, India
Srija Sur	School of Pharmaceutical Technology, Adamas University, India
Swapnil Sharma	Department of Pharmacy, Banasthali Vidyapith, Banasthali, P.O. Rajasthan-304022, India
Udita Agrawal	Drug Delivery Research Laboratory, Department of Pharmaceutical Sciences, Dr. H. S. Gour Vishwavidyalaya, Sagar, M.P., 470003, India
Vipin Kumar	Department of Pharmaceutical Science, Gurukul Kangri (Deemed to be University), Haridwar, Uttarakhand, India
Vinod Nautiyal	Department of Pharmaceutical Sciences, Gurukul Kangri University Haridwar, Uttarakhand, India
Vishal Soni	Department of Herbal Drug Research, B.R. Nahata College of Pharmacy, Research Centre, Mhow Neemuch Road, Mandsaur 458 001, India
Vishal Trivedi	Department of Pharmacy, Madhav University, Abu Road, Pindwara, Rajasthan, India
Vivek Dave	Department of Pharmacy, School of Health Science Central University of South Bihar, Bihar -824236, India

For personal or research use only
Not be distributed or uploaded to any site or anywhere

- arthritis. *BioMed Res Int* 2013; 2013: 161943.
[<http://dx.doi.org/10.1155/2013/161943>] [PMID: 24062995]
- [114] Chen H, Chang X, Weng T, *et al.* A study of microemulsion systems for transdermal delivery of triptolide. *J Control Release* 2004; 98(3): 427-36.
[<http://dx.doi.org/10.1016/j.jconrel.2004.06.001>] [PMID: 15312998]
- [115] Aggarwal BB, Van Kuiken MEV, Iyer LH, Harikumar KB, Sung B. Molecular targets of nutraceuticals derived from dietary spices: potential role in suppression of inflammation and tumorigenesis. *Exp Biol Med* (Maywood) 2009; 234(8): 825-49.
[<http://dx.doi.org/10.3181/0902-MR-78>] [PMID: 19491364]
- [116] McClements DJ, Li F, Xiao H. The nutraceutical bioavailability classification scheme: classifying nutraceuticals according to factors limiting their oral bioavailability. *Annu Rev Food Sci Technol* 2015; 6: 299-327.
[<http://dx.doi.org/10.1146/annurev-food-032814-014043>] [PMID: 25705933]
- [117] Acosta E. Bioavailability of nanoparticles in nutrient and nutraceutical delivery. *Curr Opin Colloid Interface Sci* 2009; 14(1): 3-15.
[<http://dx.doi.org/10.1016/j.cocis.2008.01.002>]
- [118] Gopi S, Amalraj A, Haponiuk JT, Thomas S. Introduction of nanotechnology in herbal drugs and nutraceutical: A Review. *J Nanomedicine Biotherapeutic Discov* 2016; 6(2): 1-8.
[<http://dx.doi.org/10.4172/2155-983X.1000143>]

For personal private use only
Not be distributed or uploaded to anyone or anywhere

CHAPTER 12

Liposomes for Herbal Drug Delivery

Andang Miatmoko^{1,*}, Devy Maulidya Cahyani¹ and Retno Widyowati¹

¹ Department of Pharmaceutical Science, Faculty of Pharmacy, Universitas Airlangga, Surabaya, 60115, Indonesia

Abstract: This chapter evaluates liposomes used as delivery carriers for herbal products, which, due to poor permeability and solubility of extract components, has become a major issue in phytotherapy for treating illnesses and human health problems. Liposomes are vesicular formations with phospholipid bilayers that possess the capability to entrap both water-soluble and hydrophobic substances. However, there are several factors that should be considered with regard to herbal drugs, especially that the preparation technique should be appropriate to the solvent solubility of the plant extracts. In this regard, the ratio of phospholipids to extracts, pH stability, other liposomal components, and the ligand required to render liposome stability, circulation in the bloodstream for protracted periods, and targeted at specific organs should be investigated. The enhancement of phytochemical constituent stability within a context of environmental, physical, and chemical degradation, together with sustained or controlled drug release, can be achieved by incorporating extracts into liposomes. Moreover, the improved oral absorption of plant extracts by encapsulating them into liposomes indicates increased permeability and bioavailability *via* gastrointestinal tracts, thus enhancing pharmacological effects at low dose concentration as well as decreasing toxicity. However, thousands of constituents contained in plant extracts demonstrate various physicochemical characteristics that constitute significant challenges for liposomal delivery. Consequently, a comprehensive analysis of formulating and manufacturing aspects is required.

Keywords: Bioavailability, Human health, Illness, Liposomes, Phospholipids, Plant extracts, Solubility.

INTRODUCTION

Health problems involving chronic diseases such as cancer, diabetes, hypertension, stroke, cardiovascular disease, among others, are known to have a high prevalence [1]. They greatly affect people's quality of life, thus still constituting a major challenge that needs to be successfully addressed [2]. More-over, these diseases

* Corresponding author Andang Miatmoko: Department of Pharmaceutical Science, Faculty of Pharmacy, Universitas Airlangga, Surabaya, 60115, Indonesia; Email: andang-m@ff.unair.ac.id

are generally slow in progression, of considerable duration, and require medical therapy [3]. Therefore, identifying appropriate treatment strategies becomes the main concern in successfully addressing them by means of both medical and non-medical therapies involving either causative or symptomatic treatments.

Medical treatment includes the use of various pharmaceutical products. Therefore, a rapid expansion in the drug product list, in addition to designing effective delivery systems to target the disease sites, is required. However, the curative effect of drugs is not the only major concern since significant attention is also devoted to avoiding severe unintended side effects on normal tissues. Minimizing the side effects of medical therapy has encouraged numerous researchers to explore various ideas and strategies for drug delivery systems [4]. In addition, pharmacological therapy-related drug development is not limited to modern synthesized pharmaceuticals but is also strongly associated with natural and biological products offering great potential within the process of new drug discovery and development [5, 6].

Natural products are compounds produced by living organisms that usually produce various pharmacological effects. Plant extract usually contains many newchemical compounds with multiple structures that may have different biological roles [7]. Between 300,000 and 400,000 plant species are known to be used as primary raw materials in the development of new compounds as active pharmaceutical ingredients, which are proven to be effective as antioxidant, antimutagenic, anti-infectious, anti-inflammatory, anti-angiogenic, and anti-cancer drugs [8, 9].

On the other hand, not all compounds extracted or isolated from natural plants or other biological sources can be synthesized into medicine. The existence of extremely complex chemical structures which are exorbitantly expensive to synthesize on an industrial scale limits their development [7]. In addition, certain problems related to poor solubility and chemical instability also constitute major limitations on their clinical uses. Complex chemical structures and high molecular weight may also affect drug absorption, thereby requiring specific drug formulation strategies [10]. The main challenge for the formulation lies in poor bioavailability [11]. For example, the use of curcumin in the treatment of various diseases, such as cancer, has limited effectiveness due to its low water solubility, limited bioavailability, expeditious systemic metabolism, and rapid elimination [12]. It has long been accepted that solubility represents a determinant factor in the absorption of a drug and that permeability can be an important parameter for the penetration of the biological membrane by drug molecules and their entry into the blood circulation system or their diffusion into the target cells. Therefore, a modify-

cation is required to improve their physicochemical properties, increase their stability, enhance their pharmacokinetic profiles, and minimize the sideeffects of natural drug compounds.

Over the years, nanotechnology has been widely developed in various scientific fields for medical purposes [13]. Nanomedicine, which involves the use of nanoparticles, has been extensively used to diagnose, monitor, control, prevent, and cure diseases [14]. Lipid-based nanoparticles are commonly used to protect drugs from *in vivo* degradation, control drug release, modify biodistribution, target drug delivery to disease sites, and improve solubility and bioavailability [15]. Of all nanoparticles, liposomes constitute some of the most widely studied, with certain FDA-accepted formulations being used in chronic disease therapy, such as oncology, having the greatest impact on this field. Nano-sized vesicles, compatibility and degradability in a biological environment, ability to encapsulate water-soluble and lipid-soluble substances, low toxicity, and the immunogenicity of liposomes represent significant advantages for disease therapy [16].

The word 'Liposome' is derived from the two Greek words '*Lipos*' meaning 'fat' and '*Soma*' which translates as 'body' [17]. Liposomes have a spherical vesicle-shaped formation composed of phospholipids that resemble biological membranes and act as drug carriers. Liposomes have two compartments, lipophilic and aqueous phases, and can be formed when phospholipids interact with water with the result that liposomes are able to reduce unwanted drug side effects and can be used for targeted delivery systems by altering drug distribution within the body [18].

The structure of liposomes, which consists of a bilayer membrane, means that hydrophobic drugs demonstrating low water solubility can be trapped in the membrane bilayer. Meanwhile, high levels of hydrophilic compounds can also be loaded in the aqueous intraliposomal phase [19]. By encapsulating drugs inside liposomes, drug degradation related to the physiological environment and severe side effects in healthy tissues can be significantly minimized [20]. It is possible to make a drug carrier featuring the vesicular structures of liposomes with the ability to load hydrophilic and lipophilic drugs, protecting the encapsulated drugs from environmental degradation [21]. Liposomes can also possess non-toxic biomimetic characteristics capable of increasing cell penetration, thereby enhancing their therapeutic effect. Biomimetic liposomes are extremely stable, demonstrating superiority *vis-a-vis in vitro* targeting capabilities, and achieve 2.25times deeper penetration of the 3D tumor spheroid than that of their conventional counterparts [22].

As drug delivery carriers, liposomes have numerous advantages, which include increasing the efficacy and index of drug therapy, enhancing stability through encapsulation and biodistribution, and completing biodegradation in the body. Moreover, they are generally non-immunogenic in both systemic and non-systemic uses and significantly reduce the toxicity of encapsulated drugs, *e.g.*, amphotericin B and paclitaxel, by reducing drug exposure. Liposomes demonstrate flexibility in relation to specific ligand modification with the result that they can be targeted at specific tissues within the diseased site [23]. In addition, they can increase therapeutic efficacy and reduce toxic effects on normal cells through enhanced permeability and retention (EPR). This constitutes a passive and selective accumulation within tumor tissue because of increased permeability of tumor neovasculature and defective lymphatic drainage, thus increasing drug exposure to cancerous cells [24]. On the other hand, liposomes imbue hydrophobic drugs with hydrophilic properties that can reduce the frequency of dose administration [25]. Therefore, they offer numerous benefits in relation to increasing the bioavailability and the half-life of most drugs and delivering them to specific disease-target sites [21].

In liposomal preparation, phospholipid selection greatly influences the physicochemical and biological properties of liposomes. Phospholipids determine, to a large extent, the loading capabilities, drug-lipid molecular arrangement, membrane integrity, surface charge, steric resistance, and permeability of the lipid bilayer [26]. Moreover, they can also affect the interaction of liposomes with blood and tissue components during systemic administration [27]. Liposomes can undergo degradation or physical changes during manufacture or storage, through which the use of unsaturated lipids can cause possible oxidation. The partial substitution of phospholipids with cholesterol can decrease membrane fluidity and reduce the surface charge of the liposomes [28]. Liposomes are conventionally composed of phosphatidylcholine and cholesterol. However, after administration, these liposomes are predominantly recognized by the reticuloendothelial system (RES), which leads to rapid drug clearance and, ultimately, impairs drug-targeting efficiency. PEGylation involving the use of polyethylene glycol (PEG) can increase the hydrophilic properties of liposomes and provide a steric barrier to prevent serum opsonization, thus causing them to circulate for a protracted period in the body and improve drug accumulation in target tissues [27].

The ultimate goal of delivering drugs by means of liposomes is to achieve high drug levels at the target sites of, for example, tumor and inflammatory tissues. Selective drug accumulation can be accomplished by both active and passive targeting. High drug availability at target sites becomes an important factor in achieving a therapeutic effect. Therefore, a high drug concentration at the target site is imperative. Delivery systems with high drug loading, minimal leakage during

administration, and systemic blood circulation, which only involve complete release in the target cells, need to be produced. In this regard, liposomes differ from other controlled release systems in which drug release occurs both in plasma and at the site of administration [29]. To achieve this, a combination of lipids and cholesterol can be used [30].

From the outset of their development, liposomes undergo rapid development. Conventional liposomes, which are merely composed of phospholipids, are known to have low stability and high recognition by RES, causing faster drug excretion [27]. There are currently several types of liposomes that enhance drug delivery. Based on their composition and mechanism, they can be classified into five types, namely conventional liposome, pH-sensitive liposome, cationic liposome, long-circulating liposome (LCL), and immuno-liposome. The pH-sensitive liposome type is composed of dioleoyl-phosphatidyl-ethanolamine (DOPE), which has been designed for specific drug release by means of a rapid destabilization mechanism in response to an acidic pH environment, such as endosome [31]. The cationic liposome type is composed of cationic lipids and neutral-charged lipids (co-lipids), in which cationic lipid exhibits a positive charge triggering interaction with negatively charged nucleic acid, thus increasing nucleic acid stability during systemic blood circulation and improving cellular uptake [32, 33]. To inhibit the uptake of liposomes by RES causing rapid liposome elimination, the long-circulating liposomes can be generated by the addition of hydrophilic layers such as PEGylation on the liposomal surface, thus inhibiting protein adsorption [34]. The recent development of an immune-liposome, which recognizes tumor cells by means of antibodies, significantly enhances specific target cell internalization and intracellular drug release [35].

Several techniques have been developed to achieve liposome surface modification with different lipids or antibodies to overcome the problems associated with conventional liposome delivery. The use of PEG-lipid conjugates, target ligands, and multifunctional antibodies can be applied to liposome surface modification [36]. All of these correlate strongly with the physicochemical properties of lipids used in liposomes to determine the liposome-protein interaction in the body during administration [37].

In this chapter, the authors present an overview of the terminology used with liposomes, formulation, and multidimensional approaches to liposome production. There is also a summary of a number of liposome applications for herbal drug delivery.

Liposomes as Drug Carriers

Liposomes were the first drug carriers created in England in the 1960s by Bangham, who conducted research predominantly focused on phospholipids and blood clotting [38]. As seen from Figure 1, liposomes are vesicle-shaped drug carriers composed of phospholipids and cholesterol [39], which are able to encapsulate both water-soluble and lipid-soluble compounds [40]. Liposomes are of various sizes, ranging from nanometers to micrometers, which are generally between 25 nm and 2.5 μm [4]. When exposed to water, lipids will tend to self-assemble, thereby forming vesicles. The hydrophilic interaction between the two polar groups and the Van der Waals interaction between the hydrocarbon tails and with water (hydrophilic interaction and hydrophobic effect) leads to the formation of a lipid-based vesicular structure [40].




Fig. (1). The liposomal structure that enables penetration by both hydrophobic and/or hydrophilic drugs [38].

There have been numerous variations in the terminology relating to liposomes, such as ethosomes, transfersomes, and hexosomes. An ethosome, a lipid vesicle consisting of phospholipids, water, and a high concentration of ethanol, enables more efficient skin drug delivery in terms of both quantity and depth of penetration than a conventional liposome [41]. A transfersome is a highly elastic liposome composed of edge activators, *i.e.*, surfactants, enabling an improved penetration of transdermal drug delivery [42, 43]. On the other hand, a hexosome is a liposome with an internal hexagonal phase, providing superiority in formulation design, water solubility, and controlled-drug release of numerous substances [44].

Preparation of Liposomes

Liposomes are composed of phospholipid components, while other components such as cholesterol or PEG can be added. The characteristics of liposomes are highly dependent on the physicochemical properties of their constituent components.

1. Phospholipids are constituent components of the hydrophobic bilayer membrane.

Liposomes can be prepared with natural and/or synthetic phospholipids. Phospholipids are the main components of the cell membrane, which possess excellent amphiphilic and biocompatible properties [45]. This amphiphilic property invests phospholipids with self-assembly properties and enables them to act as emulsifying and wetting agents. When introduced into water, phospholipids can spontaneously produce different supermolecular structures depending on their specific properties and conditions; for example, they demonstrate a tendency to form liposomes [45].

Natural phospholipids are widely derived from plant sources, such as soybean, canola, sunflower, wheat germ, and from animal sources, for instance, egg yolk and milk [45, 47]. In contrast, various types of synthetic phospholipids can be obtained from natural lipids by modifying the hydrophobic and hydrophilic regions of phospholipid molecules [40]. Synthetic and natural phospholipids have respective advantages and disadvantages. While synthetic phospholipids demonstrate comparatively high stability and purity, they are relatively expensive compared to their natural counterparts. However, obtaining consistent purity is challenging and synthetic phospholipids are relatively unstable, resulting in their metabolization into lysophospholipids during the preparation process and storage [45].

Phospholipids are amphipathic molecules composed of hydrophilic and lipophilic groups on the head and tail, respectively. The structure of phospholipids (Fig. 2) generally consists of diglycerides, phosphate groups, *e.g.*, phosphoric acid molecules, and organic molecules such as choline. Diglycerides are glycerides consisting of two chains of fatty acids covalently bonded to a single glycerol molecule. The glycerol undergoes esterification at positions 1 and 2 with fatty and phosphoric acids at 3-position [46]. Glycerol ($C_2H_8O_3$) contains three hydroxyl groups (-OH), contributing to the solubility of phospholipid molecules in water, while fatty acid chains, whether saturated or unsaturated, possess hydrophobic properties. Thus, a phospholipid molecule has a hydrophobic tail consisting of two fatty acid chains and a hydrophilic head composed of glycerol and phosphate. A bilayer structure of liposome membrane will be spontaneously formed when the fatty acid chains of a phospholipid molecule encounter the fatty acid tail of another molecule with the polar head facing the water [47].

The physicochemical properties of each phospholipid are also related to the chain length of fatty acids, in which each phospholipid type has contrasting carbon atom numbers and saturation degrees, for example, hydrogenated soy phosphatidy-

choline (HSPC), distearoyl phosphatidylcholine (DSPC), dipalmitoyl phosphatidylcholine (DPPC), and dimyristoyl phosphatidylcholine (DMPC) [40]. For a stable liposome formulation, saturated phospholipids can be used, whereas this is rarely the case with unsaturated phospholipids. However, this selection is highly dependent on the physicochemical characteristics of the drug [48].




Fig. (2). The structure of phospholipids and their schematic representation in the formation of bilayer membranes of liposomes [47].

Based on the polar head group, phospholipids can be categorized as phosphatidylcholine (PC), phosphatidylethanolamine (PE), phosphatidylserine (PS), phosphatidylinositol (PI), phosphatidylglycerol (PG), and phosphatidic acid (PA), while PC and PE have been generally used in the production of liposomes [40].

Liposomes are classified into three types according to their charge potential; cationic, anionic, and neutral, in which these surface charges largely determine the systemic circulation time, distribution, cellular uptake, and elimination of liposomes within the body [49].

A cationic liposome is generally prepared with lipids that can induce a positive charge on the liposome surface, as indicated in Table 1. For the most part, negatively charged therapeutic agents can be incorporated into this liposome, forming stable complexes [49]. The general characteristics of cationic liposome include high water solubility and high cationic charge at physiological pH, thus promoting strong interaction with negatively charged cell membranes and improving cellular binding and uptakes [38], which strongly supports targeted drug delivery. In contrast, anionic liposome, composed of phospholipids with an anionic head group, can affect cell signaling, protein-lipid interactions, and membrane trafficking

[50, 51]. The charged lipids are initially used in RNA delivery as an application supporting successful gene delivery. On the other hand, cationic liposomes frequently have problems with systemic toxicity. The use of neutrally-charged phospholipids is generally applied to overcome toxicity problems with high drug delivery efficiency [49].

Table 1. Phospholipid types based on the types of liposomes [49].

No	Liposome Types	Phospholipids Used as the Lipid Component
1	Cationic Liposome	1, 2-dioleoyl-3-trimethylammoniumpropane (DOTAP)
		N- [1- (2,3-dioleoyloxy) propyl] -N, N, N-trimethyl-ammonium methyl sulfate
		Dioleoylphosphatidyl ethanolamine (DOPE)
		Oleic acid (OA)
		Dimethyldioctadecylammonium bromide
2	Anionic Liposome	Phosphatidylglycerol (PG)
		Phosphatidylinositol (PI)
		Phosphatidic acid (PA)
		Phosphatidylserine (PS)
3	Neutral Liposome	1,2-dioleoyl-sn-glycero-3-phosphatidylcholine (DOPC)

The most commonly employed phospholipid for preparing neutral liposome is phosphatidylcholine which consists of a hydrophilic group, *i.e.*, phosphocholine, together with a glycerol bridge and a hydrophobic region incorporating double acyl hydrocarbon chains [52]. Hydrogenated soy phosphatidylcholine (HSPC) is anionic synthetic phospholipid obtained from hydrogenated natural phospholipid, which is produced from egg yolk or soy by hydrogenation. HSPC has a molecular weight of 837.44 and a number of saturated chains of 16-18 with a transition temperature (T_c) of 52°C [40, 47]. Its several advantages comprise being odorless and unaffected by oxidation [40, 53]. Moreover, it is easier to hydrogenate soybean PC in producing HSPC than synthesize DSPC as synthetic lipids. In addition, rather than DPPC or DSPC, HSPC is most often used to ensure the stability of liposomes during systemic blood circulation.

In addition, the liposome bilayer membrane may contain other constituents such as cholesterol, hydrophilic lipids that are conjugated with lipids, and the water phase [38].

2. The hydrophilic aqueous core inside liposomes

The inner core of the liposome, surrounded by the polar head groups of the phospholipids, becomes the loading site for hydrophilic molecules. Therefore,

most hydrophilic drugs will tend to become entrapped in this aqueous core [55]. On the other hand, the lipophilic molecules will be enmeshed in the hydrophobic portion of the phospholipid bilayer [54].

Hydrophilic drug encapsulation can be passively induced by the hydration of a buffer or solution containing hydrophilic drugs [43]. Through this method, the drug can enter the liposomal aqueous core, although a limited amount of it will remain outside the liposome section. In addition, dehydration and rehydration methods can also be applied for DNA and protein encapsulation [56]. Drugs with good permeability coefficients that are reflected in their partition coefficient (Log P) can be efficiently loaded using an active method with the presence of pH or ammonia gradient. This loading method generally produces high encapsulation efficiency, which is, in most cases, at a level of >95% [48, 57].

3. Cholesterol as an additional component of the bilayer membrane

Cholesterol is generally used to enhance the physical stability of the membrane bilayer of liposomes, which reduces the water permeability of soluble molecules across the membrane bilayer [40], thus increasing liposome rigidity and stability [47]. Cholesterol plays a major role in the regulation, dynamics, and function of liposomal bilayer membranes by decreasing the free rotational force of the phospholipid hydrocarbon chain, thereby helping to reduce the loss of hydrophilic parts and stabilize the lipid bilayer [30]. In addition, without the addition of cholesterol, liposomes can interact rapidly with plasma proteins such as albumin, transferrin, and macroglobulin, causing physical instability of the liposomes and rapid elimination from the body. Cholesterol will occupy the gap produced by the phospholipids and render the structure more rigid, thus reducing the interaction between phospholipids and plasma proteins [58]. The use of cholesterol has also been reported to affect vesicle diameter in addition to efficient drug encapsulation [30].

4. PEG-conjugated lipids form a hydrophilic layer outside the liposomes

Targeted drug delivery systems represent a promising strategy for increasing selective drug delivery to unhealthy tissue or disease sites, thereby improving therapeutic efficacy and lowering toxicity. The use of hydrophilic polymer such as polyethylene glycol (PEG) is often associated with targeting specific cells, tissue, and even intracellular localization in organelles so as to prolong circulation time, increase drug bioavailability, and reduce unwanted side effects [59].

Liposomes are known to be very rapidly metabolized by the mononuclear phagocyte system (MPS). PEG has been used to improve drug stability and solubility, decrease toxicity, increase half-life, and reduce clearance and

immunogenicity of liposomes [60]. PEG can be attached to the liposomal membrane surface using numerous methods, the most frequent of which is to conjugate the polymer into the membrane *via* a PEG-conjugated lipid, such as 1,2-sn-distearoyl-glycero phosphoethanolamine methoxy-polyethylene glycol 2000 (DSPE-mPEG2000) (Fig. 3) [60].




Fig. (3). Modification of DPPC vesicles by S-PEG addition on the liposome surface induces high stability in the presence of Bovine Serum Albumin [61].

The effect of PEGylation on liposomes in increasing circulation time largely depends on the length of the PEG chain and the relative density of the total lipid constitution. In general, PEG featuring longer chains represents superior steric obstacles [62]. The lipid-PEG modification sterically inhibits the interaction between liposomes and MPS, which causes rapid clearance of liposomes from the blood. Santos *et al.*'s research shows that DSPE-mPEG2000 at a concentration of ≤ 5 mol% levels combined with the DSPC liposome results, with the effect of extending circulation time. However, at a level between 1 and 5 mol%, it will have a different effect. The addition of DSPE-mPEG2000 also prevents liposome aggregation, thus extending circulation time [63].

Manufacturing of Liposomes

The main objectives of ideal liposome manufacture are to achieve efficient drug encapsulation, small particle size, and high stability during long-term storage. In general, liposome manufacture includes the processes of lipid hydration, particle size reduction, and separation from free drugs. Approximately ten methods are usually adopted for the preparation of liposomes, including the thin-film hydration method, micro-emulsification, sonication, membrane extrusion, the freeze-thawed

method, the ether injection method, the ethanol injection method, the reverse-phase evaporation method, dehydration-rehydration, and the calcium-induced fusion method [64]. Method selection largely determines the unilamellarity, vesicle size, and stability of liposomes. In addition to the manufacturing method, there are two main drug loading methods into liposomes; passive loading and active loading.

Of all these manufacturing methods, thin-film hydration, reverse phase evaporation, and ethanol injection have become the most commonly used in the preparation of liposomes. The following are brief overviews of the various manufacturing methods for liposome manufacture:

1. Thin Film Hydration

The thin film hydration method is the most common and simplest liposome production technique, which involves dissolving phospholipids in organic solvents, such as dichloromethane, chloroform, ethanol, and chloroform-methanol [64] (Fig. 4). This is the simplest original method devised by Bangham, which, if compared to those of reverse-phase evaporation and ethanol injection, can produce liposomes with the optimum properties and stability [40].




Fig. (4). The schematic representation of liposome production using the thin film hydration method [65].

At the first stage, the organic solvents with volatile properties, especially chloroform, ether, or methanol, are used to dissolve lipids. The lipid will become a thin film layer on the bottom tube wall when the solvent is evaporated using a rotary vacuum evaporator [40]. Usually, an evaporation process completed in a vacuum at a temperature of 45-60°C will result in a homogeneous thin film layer. Nitrogen can also be used to remove the remaining solvent [64]. Furthermore, the dry, thin-film layer is hydrated under agitation with a hydration solution, such as

distilled water, phosphate buffer, phosphate buffered saline (PBS) at pH 7.4, or normal saline at a temperature above the transition temperature of the lipid used [38]. The hydration process usually varies from 1-2 hours in duration [64].

This thin layer method will produce a heterogeneous multilamellar vesicles (MLV) liposome that requires a further process to reduce its size. For example, sonication will produce small unilamellar vesicle (SUV) liposomes and/or extrusion with a polycarbonate membrane to produce homogenous size distribution among unilamellar liposomes [38].

2. Reverse Phase Evaporation

In the reverse-phase evaporation method, phospholipids are dissolved in diethyl ether/isopropyl ether or a mixture of diethyl ether and chloroform at a volume ratio of 1:1 or a mixture of chloroform-methanol at a ratio of 2:1 v/v. Phosphate buffer or citrate-disodium hydrogen phosphate buffer is subsequently added at the aqueous phase in order to increase the drug encapsulation efficiency of the liposomes. The organic phase must remain distinct from the water phase to ensure that an oil/water emulsion is formed. Liposome formation will occur during continuous rotational evaporation of organic solvents in a vacuum, as seen in Fig. (5). This method produces very high drug encapsulation. However, the possibility of remaining solvents and the difficulty of large-scale manufacturing constitute the main limitations of this method [64].




Fig. (5). A schematic representation of liposome preparation procedures involving the reverse phase evaporation method [65].

3. Ethanol Injection

In the ethanol injection method, lipids are first dissolved in ethanol, with the resulting solution being rapidly introduced into large quantities of preheated water or in a buffer to form SUV liposomes. The incorporation of drugs in liposome vesicles depends on their hydrophilic and/or hydrophobic properties. This method uses ethanol as a relatively harmless solvent, which can also be easily scaled up. In addition, no physical or chemical treatment exists that can cause lipid damage. However, the concentration of the vesicles obtained is extremely low, and there may be an azeotropic mixture with water rendering the removal of ethanol from the final product difficult [40, 64].

The use of Liposomes for Herbal Product Delivery

Liposomes have been used for many purposes, including drug delivery systems and cosmetics, among others. In this section, the use of liposomes is focused on a herbal drug delivery system since liposomes effectively enhance the drug solubility, bioavailability, and pharmacological activity of certain compounds.

1. Liposomes Increase Herbal Drugs Solubility

Liposomes can dissolve water-insoluble drugs by trapping them in the liposomal lipid membrane. Apart from increasing their solubility and biocompatibility, the liposome structure, which is similar to that of a biological membrane, can encourage its use in delivering drugs with poor permeability [65].

The use of liposomes has been applied to *Orthosiphon stamineus* (OS) extract formulation. *Orthosiphon stamineus* Benth. is a medicinal plant commonly used as an ingredient of various traditional drugs in the treatment of angiogenesis-related diseases, such as rheumatoid arthritis, tumor edema, obesity, diabetic retinopathy, and psoriasis [66]. The ethanol extract of OS contains many flavones, including sinensetin (SIN), eupatorine (EUP), and 3'-hydroxy-5, 6, 7, 4'-tetramethoxyflavone (TMF) as markers of pharmacological activity. However, these flavones exhibit low water solubility, which limits their clinical use [67]. Increasing the solubility of lipophilic flavones produced from OS extract can increase their bioavailability and pharmacological activity.

Liposomes have been prepared to increase the solubility and permeability of OS ethanolic extract, thereby enhancing their bioavailability. Aisha *et al.* reported the use of liposomes in preparing OS extract (OS-L) by the thin film hydration method, which involves dissolving phospholipids in chloroform.

The optimum ratio of phospholipids to extract is selected according to the increase in the solubility of the OS extract in water. The liposomes are prepared using crude soybean phospholipids prepared in ethanol (PH-Et) at various weight-to-weight ratios of the OS extract. The crude soybean lecithin contains $62 \pm 0.2\%$ acetone insoluble phosphatides, while PH-Et has a phosphatidylcholine (PC) fraction of 13.4%, as determined by column chromatography. The solubility of the non-formulated OS extract (OS-E), as measured by UV-vis spectrophotometry, is $956 \pm 34 \mu\text{g/ml}$. The results show a significant increase in the water solubility of the formulation prepared on phospholipids at extract ratios of 50:50, 150:50, and 100:50, as shown in Table 2. The formulation prepared at a weight ratio of 100:50 shows the greatest solubility improvement, albeit still limited. Consequently, the methanol is used to dissolve extract resulting in a significant increase in the water solubility of OS extract from $1,402 \pm 66 \mu\text{g/mL}$ in ethanol to $3,979 \pm 139 \mu\text{g/mL}$ in methanol ($P = 0.000$). The methanol used to dissolve extract has a similar boiling point to chloroform (65.0°C) as phospholipid solvent (61.2°C), resulting in a homogenous phospholipid-extract thin film. On the other hand, the higher boiling point of ethanol (78.4°C) compared to chloroform tends to produce phase separation and the precipitation of phospholipid from extract mixtures [67].

Table 2. The water solubility of OS extracts prepared at various phospholipid-extract ratios in liposomes [67].

Formula	Crude soybean phospholipids prepared in ethanol/PH-Et (mg)	OS Extract/ OS-E (mg)	Solubility in water ($\mu\text{g/mL}$)
F1	150.0	50.0	$1,296.5 \pm 18$
F2	100.0	50.0	$1,401.7 \pm 66$
F3	50.0	50.0	$1,188.8 \pm 169$
F4	25.0	50.0	$1,018.8 \pm 15$
F5	25.0	75.0	$1,072.6 \pm 6$

The interaction of the extracts with phospholipids results in changes in the infrared absorption spectrum. The most noticeable spectral change can be observed in the phospholipid polar group and may indicate the presence of hydrogen bonds between the polar phospholipid groups and the hydroxyl groups from the OS extract. Hydrogen bonds can also occur between the keto groups of flavonoids and the phospholipid oxygen groups. In addition, hydrophobic interactions occur between the flavone's methoxy group and the carbon chain in the tail portion of phospholipids [67].

The stability study shows that the OS extract liposomes are stable at pH 5.5 and 7.4, while at a lower pH of 1.6 (gastric pH), OS liposomes experience agglomeration and precipitation. Moreover, although the OS liposomes will clump, they will re-dissolve at pH 5.5 and 7.4, which represent the pH of the intestines. No precipitation occurs at pH 1.6 by using soybean phospholipids and the OS extract as a single compound [67].

The OS extract released from the liposome is evaluated by a dialysis bag that has a molecular weight cut-off (MWCO) of 8,200 using phosphate buffer pH 6.8 media at a stirring rate of 100 rpm and temperature of 37°C. The results show that a cumulative percentage release of OS extract loaded in liposomes is 62% after 24 hours. On the other hand, the cumulative release percentage of free OS extracts is 94%. These results indicate that OS extract is stably encapsulated in liposomes, probably due to OS extract and phospholipid interaction. Consequently, results related to the slow release of flavones contained in OS extracts include rosmarinic acid (RA), sinensetin (SIN), eupatorin (EUP), and 3'-hydroxy-5,6,7,4'-tetramethoxyflavone (TMF) [67].

A further evaluation carried out on the antioxidant effect on DPPH of the extract release indicated that the OS extract loaded in liposome demonstrates stronger antioxidant activity against DPPH with an IC_{50} value of 23.5 ± 1.1 µg/ml than that of non-formulated extracts, which have an IC_{50} value of 32.4 ± 0.5 µg/ml [67]. This is because OS extract is stably encapsulated in liposomes with a slow-release rate that enables it to maintain or increase the antioxidant activity.

A higher intestinal permeability of liposomal extracts compared to non-formulated extracts is obtained due to loading into liposomes, higher solubility, and the nano-sized vesicles that produce an increase in negative charge and enhance colloid stability. Previous studies have reported that anionic liposomes demonstrate superior colloid stability and absorption and an even higher cellular uptake rate than those of neutral and cationic liposomes. Based on the evaluation results related to the liposome formulation of the OS extract, it is clear that an increase in solubility, absorption, and antioxidant effects can intensify the pharmacological effects of the OS ethanol extract [67].

Liposome formulation to increase drug solubility has also been applied to silymarin extract. Silymarin has been known as the main flavonoid obtained from the extraction from the dried fruit of *S. marianum* and has been widely employed in the treatment of liver disease. Silybin constitutes the main and major active component of silymarin and plays a role in its pharmacological activity. Silymarin is known to be widely used in the treatment of liver disorders to reduce glutathione oxidation as a means of increasing glutathione levels in the liver, enhancing the stabilizing

effect of liver cell membranes, and the enhancement of hepatocyte protein synthesis [68]. However, the low solubility of silymarin in water produces low oral bioavailability of approximately 20-50%. Some degradations have also been reported due to the presence of gastric juice, which limits the use of silymarin [69, 70].

Based on Wang *et al.*'s research, it has been reported that silymarin prepared as pro-liposome improves encapsulation efficiency when the drug to phospholipids mass ratio or pH is increased [65]. Pro-liposomes form a dry and readily flowing powder that will convert to liposomes after hydration. Pro-liposomes offer several advantages over conventional liposomes, such as increased stability due to the dry-solid state forms during storage [65].

The pro-liposomal silymarin is prepared with soy lecithin, cholesterol, and sodium oleate dissolved in propylene glycol to produce a silymarin proliposome solution with a transparent light yellow color. The liposome is obtained by mixing proliposomes with water resulting in vesicles with multilayer membranestructures, as seen in Figure 6, with silymarin loading at a high entrapmentefficiency [71]. The hydrated pro-liposomes produce liposomal vesicles with small particle sizes, approximately 70 nm, and are homogeneous in terms of the distribution of their size. The use of sodium deoxycholate or sodium oleate in proliposomes can facilitate the formation of liposomes without any changes in their morphological structures and stable silymarin loading even after proliposome hydration [71].




Fig. (6). Transmission electron photomicroscopy of silymarin liposome (magnification 5x1000 times) [71].

It has also been reported that liposome is successfully used to load curcumin (CUR). Liposomes that are composed of lecithin, cholesterol, and CUR at a molar ratio of 60:15:1, respectively, and prepared by reverse-phase evaporation method generate a stable, homogeneous, and semitransparent liposome with an efficient encapsulation of 89.3% [12]. The liposomes successfully increase the stability of CUR at high temperatures and/or in acidic conditions.

Liposomes Improve the Bioavailability and Pharmacological Effects of Herbal Drugs

The main challenge to the development of an oral dosage form lies in managing poor drug bioavailability, which is known to be affected by several factors, including water solubility, permeability, dissolution rate, first-pass metabolism, and pre-systemic metabolism. However, poor water solubility and limited permeability are often associated with low oral bioavailability [11]. Liposomes are potentially effective drug carriers that can promote an improvement in the solubility of drugs in water, provide protection against degradation in the gastrointestinal environment, and ensure permeability through the epithelial cell membrane, thereby increasing the bioavailability of the drug [65]. In addition, liposomal drugs are known to be of low toxicity and offer improved pharmacological effects [72].

The use of liposomes has been successfully applied to increase the bioavailability of curcumin (CUR). CUR occurs as a yellow polyphenol compound derived from the turmeric plant and has been widely used in the treatment of various cancers affecting the lungs, cervix, prostate gland, breasts, bones, and liver, in addition to inflammatory diseases [12, 68, 72]. However, CUR has poor bioavailability resulting in its low blood level [74]. Therefore, a well-designed CUR formulation is necessary to improve its efficacy.

Several studies have reported that the encapsulation of CUR into liposomes improves its stability, bioavailability, targeting properties, and anticancer effectiveness. Several methods for the preparation of CUR liposomes have been reported, including thin-film, freeze-thawing, freeze-dried, solvent injection, and reversed-phase evaporation method [12].

Liposome preparation by the thin layer dispersion method increases the stability of CUR. According to the research conducted by Chen *et al.*, the use of N-trimethyl chitosan chloride (TMC) in the CUR liposomes composed of phosphatidylcholine, cholesterol, and D- α -tocopheryl polyethylene glycol 1000 succinate, increases the bioavailability of CUR. Another study by Gu *et al.* highlights that the preparation of liposomes coated with Carbopol is also reported to produce an increase in bio-

availability 2.22 times higher than that of CUR liposomes without coating.

Positively hybrid charged liposomes (PHL) prepared by thin layer hydration method, as reported in the study of Pamunuwa, Karunaratne, & Karunaratne(2016), significantly reduces the release of CUR from the liposomes compared to that of negatively hybrid charged liposomes (NHL). The use of stearylamine (SA) as an additional component of the lipid bilayer successfully produces a slow CUR release from liposomes. In another study, it is reported that the use of hydroxypropyl- β - or hydroxypropyl- γ -cyclodextrin (HP β CD or HP γ CD) complexes in liposomes by the thin layer hydration method results in an encapsulation efficiency 2.02 times higher than those without cyclodextrins. The use of HP β CD shows higher stability than HP γ CD. The formulation of CUR liposomes in cyclodextrin can significantly increase the solubility and stability of CUR [77].

CUR liposome formulation is also carried out using a lipid composition containing different characteristics of phospholipids, including neutrally charged phospholipids of varying rigidity, *i.e.*, soy phosphatidylcholine (SPC, a non-saturated phospholipid), dipalmitoylphosphatidylcholine (DPPC, a saturated phospholipid), negatively charged phospholipids, *i.e.*, dipalmitoyl phosphatidylglycerol (DPPG), and a mixture of these, *i.e.*, DPPC + DPPG (7:3 %_w), with 30% mole addition of cholesterol. The results show that the charges of lipid polar head and hydrophobicity related to saturated carbon chains of phospholipid tail greatly affect the particle size and the loading efficiency of liposomal CUR. The surface charges induced by environmental pH determine protonation of the phosphate portion of phospholipid molecules, thus affecting the hydrogen bonding between molecules leading to changes in particle size, the phospholipid liquid-crystalline stating transition temperature, and the instability of the liposomes. In acidic pH, SPC-based liposomes have the smallest vesicle size and most stable liposomes, whereas, in neutral and alkaline pH, DPPG demonstrates the highest degree of physical stability. However, the deprotonation of CUR hydroxyl groups occurring at alkaline pH causes lower entrapment efficiency for all phospholipids, specifically for DPPG, which produces repulsive interaction with CUR. The high hydrophobicity of neutral CUR form renders it highly loaded with acidic pH. The more rigid the phospholipids, *i.e.*, DPPC, with saturated hydrocarbon chains in their hydrophobic tail, the higher the entrapment efficiency and the lower the release of CUR from the liposome. The use of liposomes successfully induces a sustained and prolonged release of CUR [78].

Liposome formulation is further carried out using the freeze-thawing method, in which it has been reported that the use of 10% sucrose as a cryoprotectant can

protect liposomes from vesicle fusion and damage due to ice crystallization during the freezing process. Freeze-dried preparation itself is used to improve long-term liposome stability. The addition of sucrose demonstrates excellent maintenance of particle size as well as encapsulation efficiency, with almost 99% of CUR potentially being entrapped after rehydration [79].

Moreover, it has been reported that Hyaluronan and Eudagrite S100, both anionic polymers, can be employed as stable and effective coating substances for liposomes composed of SPC with rapid dissolution in the upper gastrointestinal tract [80]. The results show coating liposomes with these polymers produces vesicles of 220-287 nm, spherical in shape, and without any changes in dimension, even when exposed to a gastric bowel stimulated medium with high ionic strength. In addition, it produces an efficient encapsulation of CUR in the range of 78%-82%. Good water dispersion and homogeneous suspension without the presence of aggregates and precipitates being formed can be achieved. The combination of these two polymers can protect CUR from metabolism in the gastric environment. Biodistribution studies indicate that CUR levels in the liver and kidneys are low. On the other hand, there is a greater accumulation of CUR in the lower gastrointestinal tract, specifically the intestines and colon, while very low levels of CUR suspension are observed. The results show that these delivery carriers can be used to protect polyphenol compounds from the acidic gastric environment.

The solvent injection method can be performed using ethanol or ether. Through this method, phospholipids and hydrophobic drugs are dissolved together in an organic solvent as the oil phase, with the solution being rapidly injected into the water-soluble drug or aqueous phase while being stirred. Liposomes will be spontaneously formed when the organic solvent is removed. However, ether is used less frequently than ethanol because of its toxicity. CUR liposome composed of 1.0 mg of CUR with cholesterol: lecithin at a ratio of 1:3 and prepared using the ethanol injection method demonstrates high CUR encapsulation efficiency of up to 72% with a vesicle size of 830 nm [12]. Other research shows the use of propylene glycol liposome (PGL) as a CUR carrier prepared by the solvent injection method using ethanol produces a high CUR encapsulation efficiency of 92.74% without any aggregation or fusion, whereas conventional liposomes experience a degree of aggregation over time. It is also reported that CUR-PGL shows a gradual release up to a maximum of 46%. A 3-month stability evaluation shows that CUR-PGL has non-significant changes in the particle size, polydispersity index, and encapsulation efficiency, in contrast to the CUR liposome that experiences decreases in drug encapsulation. Therefore, the CUR-PGL formulation with the injection method is effective in increasing the efficiency of encapsulation and reducing the dosage and, inevitably, the side effects of CUR [81]. Another study by Li *et al.* on silica-

coated ethosome shows a high CUR encapsulation efficiency of 80.77%. The silica-coated CUR-ethosomes are stable and gradually release CUR. Moreover, these ethosomes produce 11.86 times higher CUR bioavailability than that of the CUR suspension [82]. An *in vivo* study of mice shows that the transporting of silymarin liposomes across the intestinal biological membrane is more efficient than that of silymarin solution [71]. These results highlight the successful use of liposomes to increase the bioavailability of natural products, thereby promoting their potential application in clinical contexts.

The Use of Nanoliposomes for Enhanced Drug Delivery

Nanoliposomes have many advantages, including controlled drug release, tumor targeting, low toxicity, high stability, extensive bioavailability, and reduced therapeutic dosages. Drug encapsulation in the nanoliposome system can be employed to improve the physicochemical stability of CUR. The use of chitosan in the formulation of CUR nanoparticles composed of CUR: Chitosan: Tripolyphosphate at a ratio of 3:24:8 w/w, respectively, produces high CUR nanoliposome stability when stored at 4°C, with no changes observed even up to ten months later. In addition, it results in greater *in vivo* bioavailability than the CUR suspension. This is because the use of chitosan can provide a positive charge, thereby extending the contact time of the drug with the absorption surface [83]. Shin *et al.* reported that the CUR nanoliposomes prepared using an ethanol injection method with chitosan coating have spherical morphology, as presented in Figure 7 and demonstrate improved physical stability with good mucoadhesive properties, thus enhancing bioavailability [84].




Fig. (7). Transmission electron microscopy (TEM) images of chitosan-coated CUR nanoliposomes with scales of (A) 20 nm and (B) 200 nm [84].

On the other hand, the use of nanoliposomes is unable to prevent CUR from hydrolysis at an alkaline pH of 12.0, during which it causes degradation of nanoliposomes as well as decomposition of CUR. When nanoliposome enters the circulation system, it can be rapidly phagocytized by monocyte-macrophages [85]. In addition, it can be easily and extensively accumulated in tissues with extensive vascularization in the liver, spleen, and kidneys. Consequently, the target specificity cannot be maximally achieved, thus reducing the effective dose delivered to the target sites. A modified liposome with PEG or ligand binding can prove as an effective strategy in solving this problem [12, 86, 87].

Long Circulating Liposomes

The conjugation of hydrophilic polymers, such as PEG, has been extensively used to obtain long-circulating liposomes through the formation of aqueous layers on the surface of liposomes. This polymer prevents plasma protein binding to liposomes through a steric protective layer, thereby reducing the excretion of liposomes by RES and prolonging systemic blood circulation. Long circulating liposomes are known to provide a homogeneous distribution without any aggregation. Therefore, the use of long-circulating PEGylated liposomes in the CUR liposomes results in greater stability [12].

Lin *et al.* reported that TEM analysis of liposome-PEG-polyethyleneimine (PEI) encapsulated CUR shows a coarse round shape in the presence of a hair-like surface, as shown in Fig. (8).




Fig. (8). Microstructures of the cationic liposome-PEG-PEI complex. (A) Schematic illustration of the structure of the cationic liposome-PEG-PEI complex. (B) TEM image showing the structure of the cationic liposome-PEG-PEI complex, consisting of the light circular area and dark corona on the surface [88].

Ligand Targeting Liposomes

Ligands can direct liposomes to bind specifically to receptors in the target cells. Therefore, the liposomes binding with ligands are generally used to enhance the therapeutic effect, produce synergies, reduce side effects, lower the dosage,

shorten the treatment period, and produce a specific targeting effect on the body with highly selective drug delivery. Encapsulation of CUR in liposomes with folic acid modification results in solubility and increased activity in tumors [12, 88].

In addition to the use of liposomes to increase the bioavailability and pharmacological effects of CUR, liposomes are also employed to enhance the pharmacological effects of *Cistanche tubulosa*. *Cistanche tubulosa* is a parasitic plant of the Orobanchaceae family that produces various pharmacological effects, including increasing immunity and endurance, nourishing the kidneys, treating impotence, and improving intelligence. Moreover, it also possesses anti-oxidant and anti-aging properties [90]. This plant contains phenylethanoid glycosides (CPhGs) as the main component that stimulates immunity. Despite their strong pharmacological effect, CPhGs have poor oral absorption [91] that severely limits their use for clinical and therapeutic applications.

Zhang *et al.* reported that liposomes composed of lecithin, DPPC, and cholesterol at a respective weight ratio of 1:2:2 are successfully prepared for encapsulating CPhGs. The liposomes have spherical shapes, uniform surface thickness, a homogenous particle size of 216.7 nm with a zeta potential of -55.6 mV, and efficient encapsulation of 38.46%. The release profile shows a release that is close to 100% after 24 hours. Moreover, CPhG liposomes greatly inhibit HSC viability and proliferation and increase the activity of concentration-dependent apoptotic cells with an IC_{50} value of 42.5 $\mu\text{g/mL}$.

Based on the evaluation results, 24 hours after exposure of CPhG liposomes to hepatic stellate cells (HSCs), and lactate dehydrogenase (LDH), an enzyme present in the cell cytosol, was released, thus indicating cell membrane damage. Moreover, the study also reported that CPhG liposomes induce apoptosis of hepatocytes, which intensifies with increasing doses of CPhGs liposomes. In addition, CPhG liposomes induce G1 phase cell cycle arrest. These results indicate that CPhG liposomes have a high potential for preventing and treating liver fibrosis by regulating cell proliferation, apoptosis, and cell cycle arrest [91].

The results also indicate that CPhG liposomes have a significant inhibitory effect on cell proliferation in HSCs. In addition, it has been found that p-PI3K and p-Akt levels consistently decrease in HSCs after 24 hours of CPhG liposome administration, indicating that the anti-proliferative effect of CPhG liposomes on HSCs is related to the deactivation of the PI3K/Akt pathway. CPhG liposomes at a concentration of 29.45 $\mu\text{g/mL}$ can reduce the expression level of phosphorylated PI3K protein and phosphorylated Akt ($p < 0.01$) [91].

The foregoing results indicate that the use of liposomes in CPhG liposome formulation significantly improves the inhibition activity of CPhGs for HSC

activation and reduces the progression of liver fibrosis by increasing apoptosis and regulating the cell cycle in HSC. This suggests that the liposome formulation in this study can be developed as an antifibrogenic agent for the treatment of liver fibrosis.

Factors Affecting the Encapsulation of Herbal Extract in Liposomes

In order to prepare liposomes with high encapsulation efficiency to improve solubility as well as bioavailability and pharmacological effects, there are certain critical parameters that should be identified.

1. The selection of phospholipids:

In the entrapping of hydrophobic substances, which will be located within the lipid bilayer membrane, the types of phospholipids will determine the entrapment efficiency. This is because the ordered structure of saturated phospholipid will limit the number of hydrophobic molecules located inside. In general, the less the crystalline structure of the lipid bilayer, the higher the loading capacity of the bilayer membrane since there is more space for hydrophobic molecules trapped inside. However, it will affect the molecular diffusion within the water, thus increasing drug release from liposomes [48, 92 - 94].

2. Extract to phospholipid ratio:

The drug and lipid ratio is a critical parameter that shows the capability of the liposomes to accommodate drug encapsulation, thus playing a critical role in the optimization process [95]. Most hydrophilic drugs will be trapped in the intraliposomal phase. Therefore, entrapment efficiency is significantly determined by the vesicular lipid volume capacity. In this case, the selection of phospholipids will also play a role in quantifying the capacity for entrapping drugs. Each phospholipid has a different surface area which determines the vesicle numbers in the dispersion media, thus affecting the volume of water available for loading drugs.

The ratio of extract to phospholipids affects the encapsulation for liposomalherbal preparation. The extract to phospholipid ratio in the OS liposome formulation greatly affects the extract solubility in the liposomes. The use of phospholipid:extract at a ratio of 100:50 w/w has the highest solubility, *i.e.*, 1,401.7 ± 66 µg/ml [67].

In silymarin liposome formulation, the mass ratio of silymarin to phospholipids also significantly influences drug encapsulation and loading efficiency. A significant increase in encapsulation efficiency from 31% to 42% is observed when the

drug-phospholipid ratio is increased from 1:5 to 1:10 ($P < 0.01$). However, no changes are obtained after increasing the ratio to 1:20 ($P > 0.05$) while the drug loading efficiency decreases.

3. pH of liposomes:

The encapsulation efficiency also changes with variations in pH. The silymarin liposomes are composed of 1 g of silymarin, 10 g of phospholipids, 5 g of cholesterol, and 0.5 g of sodium oleate and prepared with a silymarin- phospholipid at a ratio of 1:10. Adjusting the pH of liposomes to 5.0, 6.0, 7.0, and 9.0 increases their encapsulation efficiency, indicating that the larger the amount of silymarin, the more easily it is trapped when the liposomes are present in a more alkaline environment. This may be related to a chemical reaction between silymarin and phospholipids. Moreover, the improved transport of silymarin liposomes increases bioavailability up to a 1-fold increase in AUC ($P < 0.01$) [71].

4. Incubation temperature

In a drug loading process involving active loading, the fluidity of the bilayer membrane determines the ability of water-soluble solutes to permeate across the membrane and enter the intraliposomal phase. The presence of pH or ammonia gradient will drive the permeation or loading process to produce high levels of the drug inside the inner water phase, which sometimes results in high dense aggregates due to oversaturated internal drug concentration. Both the incubation period and temperature affect the gel to liquid crystalline state of phospholipids as the main component of the bilayer membrane and determine the solute transfer process from the exterior of the liposomes to their interior. This constitutes a major factor to be considered with regard to the loading of the active substances.

CONCLUSION

The compounds contained in plant extracts exhibit various physicochemical characteristics, which constitute a significant challenge for the liposome drug delivery system. The use of liposomes to develop natural products has several benefits, such as enhancing drug solubility and increasing the bioavailability and pharmacological effects of active substances. Based on the findings of research into the use of liposomes in herbal products, there is an increase in phytochemical stability in terms of physical and chemical degradation, with sustained or controlled drug release. Moreover, an increase in the oral absorption of plant extracts in the form of liposomes indicates increased bioavailability in the gastrointestinal tract, thereby increasing the pharmacological effect at low dose concentration and reducing toxicity.

FUTURE PROSPECTIVE

A comprehensive analysis from the formulation and manufacturing aspects to the composition of the liposome formula for the natural product drug delivery system and the appropriate manufacturing method is required. The various components contained in the plant extract, in addition to largely water-insoluble compounds, remain as challenges to the optimizing of liposomes preparation intended to improve solubility and permeability, thereby enhancing oral bioavailability. Liposomes could be beneficial, acting as potential drug delivery carriers, which enhance the biological activity of most hydrophilic and hydrophobic substances of herbal drugs due to their vesicular structures mimicking biological membranes.

CONSENT FOR PUBLICATION

Not applicable.

CONFLICT OF INTEREST

The authors declare no conflict of interest, financial or otherwise.

ACKNOWLEDGEMENTS

Declared none.

REFERENCES

- [1] Comlossy M. Chronic Disease Prevention and Management. National Conference of State Legislatures 2013.
- [2] Raghupathi W, Raghupathi V. An empirical study of chronic diseases in the united states: A visual analytics approach. *Int J Environ Res Public Health* 2018; 15(3): 10-2. [<http://dx.doi.org/10.3390/ijerph15030431>] [PMID: 29494555]
- [3] Megari K. Quality of life in chronic disease patients. *Health Psychol Res* 2013; 1(3): e27. [<http://dx.doi.org/10.4081/hpr.2013.932>] [PMID: 26973912]
- [4] Aqil F, Munagala R, Jeyabalan J, Vadhanam MV. Bioavailability of phytochemicals and its enhancement by drug delivery systems. *Cancer Lett* 2013; 334(1): 133-41. [<http://dx.doi.org/10.1016/j.canlet.2013.02.032>] [PMID: 23435377]
- [5] Newman DJ, Cragg GM. Natural Products as Sources of New Drugs from 1981 to 2014. *J Nat Prod* 2016; 79(3): 629-61. [<http://dx.doi.org/10.1021/acs.jnatprod.5b01055>] [PMID: 26852623]
- [6] Evens RP. Health Care and Industry Overview and Challanges. In: Evens RP, Ed. *Drug and biological development drug and biological development: From molecule to product and beyond*. New York: Springer 2007; pp. 1-31. [http://dx.doi.org/10.1007/978-0-387-69094-0_1]
- [7] Lahlou M. The Success of Natural Products in Drug Discovery. *Pharmacol Pharm* 2013; 04(03): 17-31. [<http://dx.doi.org/10.4236/pp.2013.43A003>]

- [8] Gurnani N, Mehta D, Gupta M, Mehta BK. Natural Products : Source of Potential Drugs. African J Basic Appl Sci 2014; 6(6): 171-86.
- [9] Ramana KV, Singhal SS, Reddy AB. Therapeutic potential of natural pharmacological agents in the treatment of human diseases. BioMed Res Int 2014; 2014: 573452. [http://dx.doi.org/10.1155/2014/573452] [PMID: 25610867]
- [10] Chen J, Li W, Yao H, Xu J. Insights into drug discovery from natural products through structural modification. Fitoterapia 2015; 103: 231-41. [http://dx.doi.org/10.1016/j.fitote.2015.04.012] [PMID: 25917513]
- [11] Krishnaiah YS. Pharmaceutical technologies for enhancing oral bioavailability of poorly solubledrugs. J Bioequivalence Bioavailab 2010; 02(02): 28-36. [http://dx.doi.org/10.4172/jbb.1000027]
- [12] Feng T, Wei Y, Lee RJ, Zhao L. Liposomal curcumin and its application in cancer. Int J Nanomedicine 2017; 12: 6027-44. [http://dx.doi.org/10.2147/IJN.S132434] [PMID: 28860764]
- [13] Jildeh NB, Matouq M. Nanotechnology in packing materials for food and drug stuff opportunities. J Environ Chem Eng 2020; 8(5): 104338. [http://dx.doi.org/10.1016/j.jece.2020.104338]
- [14] Tinkle S, McNeil SE, Mühlebach S, *et al.* Nanomedicines: addressing the scientific and regulatory gap. Ann N Y Acad Sci 2014; 1313(1): 35-56. [http://dx.doi.org/10.1111/nyas.12403] [PMID: 24673240]
- [15] Shah S, Dhawan V, Holm R, Nagarsenker MS, Perrie Y. Liposomes: Advancements and innovation in the manufacturing process. Adv Drug Deliv Rev 2020; 154-155: 102-22. [http://dx.doi.org/10.1016/j.addr.2020.07.002] [PMID: 32650041]
- [16] Yang F, Jin C, Jiang Y, *et al.* Liposome based delivery systems in pancreatic cancer treatment: from bench to bedside. Cancer Treat Rev 2011; 37(8): 633-42. [http://dx.doi.org/10.1016/j.ctrv.2011.01.006] [PMID: 21330062]
- [17] Çağdaş M, Sezer AD, Bucak S. Liposomes as potential drug carrier systems for drug delivery. In: Sezer AD, Ed. Application of nanotechnology in drug delivery. IntechOpen 2014; pp. 1-50.
- [18] Ramadon D, Mun'im A. Pemanfaatan Nanoteknologi dalam sistem penghantaran obat baru untuk produk bahan alam. Jurnal Ilmu Kefarmasian Indonesia 2016; 14(2): 118-27.
- [19] Olusanya TOB, Haj Ahmad RR, Ibegbu DM, Smith JR, Elkordy AA. Liposomal drug delivery systems and anticancer drugs. Molecules 2018; 23(4): 1-17. [http://dx.doi.org/10.3390/molecules23040907] [PMID: 29662019]
- [20] Moghimipour E, Handali S. Liposomes as drug delivery systems : properties and applications. Res J Pharm Biol Chem Sci 2013; 4(1): 169-85.
- [21] Pradhan B, Kumar N, Saha S, Roy A. Liposome: method of preparation, advantages, evaluation, and its application. J Appl Pharm Res 2015; 3(3): 1-8. [http://dx.doi.org/10.18231/j.joapr.2021.v9.i3.1-7]
- [22] Jia Y, Sheng Z, Hu D, *et al.* Highly penetrative liposome nanomedicine generated by a biomimetic strategy for enhanced cancer chemotherapy. Biomater Sci 2018; 6(6): 1546-55. [http://dx.doi.org/10.1039/C8BM00256H] [PMID: 29694474]
- [23] Akbarzadeh A, Rezaei-Sadabady R, Davaran S, *et al.* Liposome: classification, preparation, and applications. Nanoscale Res Lett 2013; 8(1): 102. [http://dx.doi.org/10.1186/1556-276X-8-102] [PMID: 23432972]
- [24] Yan W, Leung SSY, To KKW. Updates on the use of liposomes for active tumor targeting in cancer therapy. Nanomedicine (Lond) 2020; 15(3): 303-18. [http://dx.doi.org/10.2217/nmm-2019-0308] [PMID: 31802702]

- [25] Bulbake U, Doppalapudi S, Kommineni N, Khan W. Liposomal formulations in clinical use: An updated review. *Pharmaceutics* 2017; 9(2): 1-33. [http://dx.doi.org/10.3390/pharmaceutics9020012] [PMID: 28346375]
- [26] Kato N, Ishijima A, Inaba T, Nomura F, Takeda S, Takiguchi K. Effects of lipid composition and solution conditions on the mechanical properties of membrane vesicles. *Membranes (Basel)* 2015; 5(1): 22-47. [http://dx.doi.org/10.3390/membranes5010022] [PMID: 25611306]
- [27] Nunes SS, Fernandes RS, Cavalcante CH, *et al.* Influence of PEG coating on the biodistribution and tumor accumulation of pH-sensitive liposomes. *Drug Deliv Transl Res* 2019; 9(1): 123-30. [http://dx.doi.org/10.1007/s13346-018-0583-8] [PMID: 30187353]
- [28] Yandrapati RK. Effect of lipid composition on the physical properties of liposomes: a light scattering study. *Master Theses* 2012; p. 6864.
- [29] Gregoriadis G. Liposome technology: Entrapment of drugs and other materials into liposome. In: Gregoriadis G, Ed. Boca Raton: CRC Press 2007; pp. 1-383.
- [30] Eloy JO, Claro de Souza M, Petrilli R, Barcellos JPA, Lee RJ, Marchetti JM. Liposomes as carriers of hydrophilic small molecule drugs: strategies to enhance encapsulation and delivery. *Colloids Surf B Biointerfaces* 2014; 123: 345-63. [http://dx.doi.org/10.1016/j.colsurfb.2014.09.029] [PMID: 25280609]
- [31] Paliwal SR, Paliwal R, Vyas SP. A review of mechanistic insight and application of pH-sensitive liposomes in drug delivery. *Drug Deliv* 2015; 22(3): 231-42. [http://dx.doi.org/10.3109/10717544.2014.882469] [PMID: 24524308]
- [32] Simões S, Filipe A, Faneca H, *et al.* Cationic liposomes for gene delivery. *Expert Opin Drug Deliv* 2005; 2(2): 237-54. [http://dx.doi.org/10.1517/17425247.2.2.237] [PMID: 16296751]
- [33] Shim G, Kim MG, Park JY, Oh YK. Application of cationic liposomes for delivery of nucleic acids. *Asian J Pharm Sci* 2013; 8(2): 72-80. [http://dx.doi.org/10.1016/j.ajps.2013.07.009]
- [34] Wei X-Q, Ba K. Construction a long-circulating delivery system of liposomal curcumin by coating albumin. *ACS Omega* 2020; 5(27): 16502-9. [http://dx.doi.org/10.1021/acsomega.0c00930] [PMID: 32685814]
- [35] Zamboni WC. Carrier-mediated and artificial-cell targeted cancer drug delivery. In: Prakash S, Ed. *Artificial cells, cell engineering and therapy*. Cambridge: Woodhead Publishing Limited 2007; pp. 469-501. [http://dx.doi.org/10.1533/9781845693077.4.469]
- [36] Le NTT, Cao VD, Nguyen TNQ, Le TTH, Tran TT, Hoang Thi TT. Soy lecithin-derived liposomal delivery systems: Surface modification and current applications. *Int J Mol Sci* 2019; 20(19): E4706. [http://dx.doi.org/10.3390/ijms20194706] [PMID: 31547569]
- [37] Sharma A, Sharma US. Liposomes in drug delivery: progress and limitations. *Int J Pharm* 1997; 154(2): 123-40. [http://dx.doi.org/10.1016/S0378-5173(97)00135-X]
- [38] Laouini A, Bernard C, Jaafar-maalej C, Limayem-Blouza I, Sfar S, Charcosset C, *et al.* Preparation, characterization, and applications of liposomes : state of the art. *J Colloid Sci Biotechnol* 2012; 1(2): 147-68. [http://dx.doi.org/10.1166/jcsb.2012.1020]
- [39] Pal P, Pateriya K, Yadav PK. A comprehensive review on novel drug deliverz *via* unique property of liposome. *Eur J Biomed Pharm Sci* 2018; 5(02): 184-92.
- [40] Monteiro N, Martins A, Reis RL, Neves NM. Liposomes in tissue engineering and regenerative

- medicine. *J R Soc Interface* 2014; 11(101): 20140459. [http://dx.doi.org/10.1098/rsif.2014.0459] [PMID: 25401172]
- [41] Bragagni M, Mennini N, Maestrelli F, Cirri M, Mura P. Comparative study of liposomes, transfersomes and ethosomes as carriers for improving topical delivery of celecoxib. *Drug Deliv* 2012;19(7): 354-61. [http://dx.doi.org/10.3109/10717544.2012.724472] [PMID: 23043648]
- [42] Chaurasiya P, Ganju E, Upmanyu N, Ray SK, Jain P. Transfersomes : a novel technique for transdermal drug delivery. *J Drug Deliv Ther* 2019; 9(1): 279-85. [http://dx.doi.org/10.22270/jddt.v9i1.2198]
- [43] Miatmoko A, Kawano K, Hattori Y, Maitani Y, Yonemochi E. Evaluation of transfersome and protransfersome for percutaneous delivery of cisplatin in hairless mice. *J Pharmaceu Pharmacol* 2015; S(1): 1-7.
- [44] Rodrigues L, Schneider F, Zhang X, *et al.* Cellular uptake of self-assembled phytantriol-based hexosomes is independent of major endocytic machineries. *J Colloid Interface Sci* 2019; 553: 820-33. [http://dx.doi.org/10.1016/j.jcis.2019.06.045] [PMID: 31284226]
- [45] Li J, Wang X, Zhang T, *et al.* A review on phospholipids and their main applications in drug delivery systems. *Asian J Pharm Sci* 2015; 10(2): 81-98. [http://dx.doi.org/10.1016/j.ajps.2014.09.004]
- [46] van Hoogevest P, Wendel A. The use of natural and synthetic phospholipids as pharmaceutical excipients. *Eur J Lipid Sci Technol* 2014; 116(9): 1088-107. [http://dx.doi.org/10.1002/ejlt.201400219] [PMID: 25400504]
- [47] Khan I, Elhissi A, Shah M, Alhnan MA, Ahmed W. Liposome-based carrier systems and devices used for pulmonary drug delivery. In: Davim JP, Ed. *Biomaterials and medical tribology: Research and development*. Cambridge: Woodhead Publishing Limited 2013; pp. 395-443. [http://dx.doi.org/10.1533/9780857092205.395]
- [48] Miatmoko A, Salim RH, Zahro SM, Annuryanti F, Sari R, Hendradi E. Dual loading of primaquine and chloroquine into liposome. *Eur Pharm J* 2019; 66(2): 18-25. [http://dx.doi.org/10.2478/afpuc-2019-0009]
- [49] Obeid MA, Tate RJ, Mullen AB, Ferro VA. Lipid-based nanoparticles for cancer treatment. In: Grumezescu MA, Ed. *Lipid nanocarriers for drug targeting*. 3rd ed. Oxford: William Andrew Applied Science Publisher 2018; pp. 313-59. [http://dx.doi.org/10.1016/B978-0-12-813687-4.00008-6]
- [50] Wan C, Allen TM, Cullis PR. Lipid nanoparticle delivery systems for siRNA-based therapeutics. *Drug Deliv Transl Res* 2014; 4(1): 74-83. [http://dx.doi.org/10.1007/s13346-013-0161-z] [PMID: 25786618]
- [51] Draz MS, Fang BA, Zhang P, *et al.* Nanoparticle-mediated systemic delivery of siRNA for treatment of cancers and viral infections. *Theranostics* 2014; 4(9): 872-92. [http://dx.doi.org/10.7150/thno.9404] [PMID: 25057313]
- [52] Choudhury A. Liposome: a carrier for effective drug delivery. *J Appl Pharm Res* 2020; 8(1): 22-8. [http://dx.doi.org/10.18231/j.joapr.2019.v.8.i.1.003]
- [53] Schaffer T. Lecithin and phospholipids - the optimal choice for natural cosmetics. *Euro Cosmet* 2007; 9: 1-4.
- [54] Deb PK, Al-Attraqchi O, Chandrasekaran B, Paradkar A, Tekade RK. Protein/peptide drug delivery systems: Practical considerations in pharmaceutical product development. In: Tekade RK, Ed. *Basic fundamentals of drug delivery*. London: Academic Press 2018; pp. 651-84.
- [55] Bozzuto G, Molinari A. Liposomes as nanomedical devices. *Int J Nanomedicine* 2015; 10: 975-99. [http://dx.doi.org/10.2147/IJN.S68861] [PMID: 25678787]

- [56] Alavi M, Karimi N, Safaei M. Application of various types of liposomes in drug delivery systems. *Adv Pharm Bull* 2017; 7(1): 3-9. [http://dx.doi.org/10.15171/apb.2017.002] [PMID: 28507932]
- [57] Miatmoko A, Kawano K, Yoda H, Yonemochi E, Hattori Y. Tumor delivery of liposomal doxorubicin prepared with poly-L-glutamic acid as a drug-trapping agent. *J Liposome Res* 2017; 27(2): 99-107. [http://dx.doi.org/10.3109/08982104.2016.1166511] [PMID: 26982164]
- [58] Shashi K, Satinder K, Bharat P. A complete review on : liposomes. *Int Reserach J Pharm* 2012; 3(7): 10-6.
- [59] Wang R, Xiao R, Zeng Z, Xu L, Wang J. Application of poly(ethylene glycol)-distearoylphosphatidylethanolamine (PEG-DSPE) block copolymers and their derivatives as nanomaterials in drug delivery. *Int J Nanomedicine* 2012; 7: 4185-98. [PMID: 22904628]
- [60] Immordino ML, Dosio F, Cattel L. Stealth liposomes: review of the basic science, rationale, and clinical applications, existing and potential. *Int J Nanomedicine* 2006; 1(3): 297-315. [PMID: 17717971]
- [61] Park Y, Franses EI. Effect of a PEGylated lipid on the dispersion stability and dynamic surface tension of aqueous DPPC and on the interactions with albumin. *Langmuir* 2010; 26(10): 6932-42. [http://dx.doi.org/10.1021/la904183e] [PMID: 20121171]
- [62] Nag OK, Awasthi V. Surface engineering of liposomes for stealth behavior. *Pharmaceutics* 2013; 5(4): 542-69. [http://dx.doi.org/10.3390/pharmaceutics5040542] [PMID: 24300562]
- [63] Dos Santos N, Allen C, Doppen AM, *et al.* Influence of poly(ethylene glycol) grafting density and polymer length on liposomes: relating plasma circulation lifetimes to protein binding. *Biochim Biophys Acta* 2007; 1768(6): 1367-77. [http://dx.doi.org/10.1016/j.bbame.2006.12.013] [PMID: 17400180]
- [64] Popovska O, Simonovska J, Kavrakovski Z, Rafajlovska V. An overview: methods for preparation and characterization of liposomes as drug delivery systems. *Int J Pharm Phytopharm Res* 2013; 3(2): 13- 20.
- [65] Lee MK. Liposomes for enhanced bioavailability of water-insoluble drugs: *In vivo* evidence and recent approaches. *Pharmaceutics* 2020; 12(3): E264. [http://dx.doi.org/10.3390/pharmaceutics12030264] [PMID: 32183185]
- [66] Ahamed MBK, Aisha AFA, Nassar ZD, *et al.* Cat's whiskers tea (*Orthosiphon stamineus*) extract inhibits growth of colon tumor in nude mice and angiogenesis in endothelial cells *via* suppressing VEGFR phosphorylation. *Nutr Cancer* 2012; 64(1): 89-99. [http://dx.doi.org/10.1080/01635581.2012.630160] [PMID: 22136553]
- [67] Aisha AFA, Majid AMSA, Ismail Z. Preparation and characterization of nano liposomes of *Orthosiphon stamineus* ethanolic extract in soybean phospholipids. *BMC Biotechnol* 2014; 14(1): 23. [http://dx.doi.org/10.1186/1472-6750-14-23] [PMID: 24674107]
- [68] Ghosh A, Ghosh T, Jain S. Silymarin- a review on the pharmacodynamics and bioavailability enhancement approaches. *J Pharm Sci Technol* 2010; 2(10): 348-55.
- [69] Tomeh MA, Hadianamrei R, Zhao X. A review of curcumin and its derivatives as anticancer agents. *Int J Mol Sci* 2019; 20(5): E1033. [http://dx.doi.org/10.3390/ijms20051033] [PMID: 30818786]
- [70] Li X, Yuan Q, Huang Y, Zhou Y, Liu Y. Development of silymarin self-microemulsifying drug delivery system with enhanced oral bioavailability. *AAPS PharmSciTech* 2010; 11(2): 672-8. [http://dx.doi.org/10.1208/s12249-010-9432-x] [PMID: 20405254]
- [71] Wang M, Xie T, Chang Z, *et al.* A new type of liquid silymarin proliposome containing bile salts: Its

- preparation and improved hepatoprotective effects. PLoS One 2015; 10(12): e0143625. [http://dx.doi.org/10.1371/journal.pone.0143625] [PMID: 26674103]
- [72] Beltrán-Gracia E, López-Camacho A, Higuera-Ciapara I, Velázquez-Fernández JB, Vallejo-Cardona AA. Nanomedicine review: Clinical developments in liposomal applications. Cancer Nanotechnol 2019; 10(11): 1-40. [http://dx.doi.org/10.1186/s12645-019-0055-y]
- [73] Shehzad A, Wahid F, Lee YS. Curcumin in cancer chemoprevention: molecular targets, pharmacokinetics, bioavailability, and clinical trials. Arch Pharm (Weinheim) 2010; 343(9): 489-99. [http://dx.doi.org/10.1002/ardp.200900319] [PMID: 20726007]
- [74] Lopresti AL. The problem of curcumin and its bioavailability: could its gastrointestinal influence contribute to its overall health-enhancing effects? Adv Nutr 2018; 9(1): 41-50. [http://dx.doi.org/10.1093/advances/nmx011] [PMID: 29438458]
- [75] Chen H, Wu J, Sun M, *et al.* N-trimethyl chitosan chloride-coated liposomes for the oral delivery of curcumin. J Liposome Res 2012; 22(2): 100-9. [http://dx.doi.org/10.3109/08982104.2011.621127] [PMID: 22007962]
- [76] Pamunuwa G, Karunaratne V, Karunaratne DN. Effect of lipid composition on *in vitro* release and skin deposition of curcumin encapsulated liposomes. J Nanomater 2016.
- [77] Matloob AH, Mourtas S, Klepetsanis P, Antimisaris SG. Increasing the stability of curcumin in serum with liposomes or hybrid drug-in-cyclodextrin-in-liposome systems: a comparative study. Int J Pharm 2014; 476(1-2): 108-15. [http://dx.doi.org/10.1016/j.ijpharm.2014.09.041] [PMID: 25269006]
- [78] Roy B, Guha P, Bhattarai R, *et al.* Influence of lipid composition, pH, and temperature on physicochemical properties of liposomes with curcumin as model drug. J Oleo Sci 2016; 65(5): 399-411. [http://dx.doi.org/10.5650/jos.ess15229] [PMID: 27150333]
- [79] Jangle RD, Thorat BN. Effect of freeze-thawing study on curcumin liposome for obtaining better freeze-dried product. Dry Technol 2013; 31(9): 966-74. [http://dx.doi.org/10.1080/07373937.2013.769003]
- [80] Catalan-Latorre A, Ravaghi M, Manca ML, *et al.* Freeze-dried eudragit-hyaluronan multicompartiment liposomes to improve the intestinal bioavailability of curcumin. Eur J Pharm Biopharm 2016; 107: 49-55. [http://dx.doi.org/10.1016/j.ejpb.2016.06.016] [PMID: 27349806]
- [81] Zhao YZ, Lu CT, Zhang Y, *et al.* Selection of high efficient transdermal lipid vesicle for curcumin skin delivery. Int J Pharm 2013; 454(1): 302-9. [http://dx.doi.org/10.1016/j.ijpharm.2013.06.052] [PMID: 23830940]
- [82] Li C, Deng L, Zhang Y, Su T-T, Jiang Y, Chen Z-B. [Silica-coated ethosome as a novel oral delivery system for enhanced oral bioavailability of curcumin]. Yao Xue Xue Bao 2012; 47(11): 1541-7. [PMID: 23387090]
- [83] Sun W, Zou Y, Guo Y, *et al.* Construction and characterization of curcumin nanoparticles system. J Nanopart Res 2014; 16(3): 2317. [http://dx.doi.org/10.1007/s11051-014-2317-2]
- [84] Shin GH, Chung SK, Kim JT, Joung HJ, Park HJ. Preparation of chitosan-coated nanoliposomes for improving the mucoadhesive property of curcumin using the ethanol injection method. J Agric Food Chem 2013; 61(46): 11119-26. [http://dx.doi.org/10.1021/jf4035404] [PMID: 24175657]
- [85] Brayner R. The toxicological impact of nanoparticles. Nano Today 2008; 3(8): 48-55. [http://dx.doi.org/10.1016/S1748-0132(08)70015-X]
- [86] Hattori Y, Shibuya K, Kojima K, *et al.* Zoledronic acid enhances antitumor efficacy of liposomal

- doxorubicin. *Int J Oncol* 2015; 47(1): 211-9.
[<http://dx.doi.org/10.3892/ijo.2015.2991>] [PMID: 25955490]
- [87] Barenholz Y. Doxil®--the first FDA-approved nano-drug: lessons learned. *J Control Release* 2012; 160(2): 117-34.
[<http://dx.doi.org/10.1016/j.jconrel.2012.03.020>] [PMID: 22484195]
- [88] Lin YL, Liu YK, Tsai NM, *et al.* A Lipo-PEG-PEI complex for encapsulating curcumin that enhances its antitumor effects on curcumin-sensitive and curcumin-resistance cells. *Nanomedicine* 2012; 8(3): 318-27.
[<http://dx.doi.org/10.1016/j.nano.2011.06.011>] [PMID: 21704596]
- [89] Lu Y, Ding N, Yang C, Huang L, Liu J, Xiang G. Preparation and *in vitro* evaluation of a folate-linked liposomal curcumin formulation. *J Liposome Res* 2012; 22(2): 110-9.
[<http://dx.doi.org/10.3109/08982104.2011.627514>] [PMID: 22372871]
- [90] Fu C, Li J, Aipire A, *et al.* *Cistanche tubulosa* phenylethanoid glycosides induce apoptosis in Eca-109 cells *via* the mitochondria-dependent pathway. *Oncol Lett* 2019; 17(1): 303-13.
[PMID: 30655768]
- [91] Zhang S-L, Ma L, Zhao J, *et al.* The phenylethanol glycoside liposome inhibits PDGF-induced HSC activation *via* regulation of the FAK/PI3K/Akt signaling pathway. *Molecules* 2019; 24(18): 1-18.
[<http://dx.doi.org/10.3390/molecules24183282>] [PMID: 31505837]
- [92] Basso LGM, Rodrigues RZ, Naal RMZG, Costa-Filho AJ. Effects of the antimalarial drug primaquine on the dynamic structure of lipid model membranes. *Biochim Biophys Acta* 2011; 1808(1): 55-64.
[<http://dx.doi.org/10.1016/j.bbamm.2010.08.009>] [PMID: 20713019]
- [93] Ezer N, Sahin I, Kazanci N. Alliin interacts with DMPC model membranes to modify the membrane dynamics: FTIR and DSC Studies. *Vib Spectrosc* 2017; 89: 1-8.
[<http://dx.doi.org/10.1016/j.vibspec.2016.12.006>]
- [94] Huang CS, Lyu SC, Chen JY, Hu ML. The anti-metastatic efficacy of β -ionone and the possible mechanisms of action in human hepatocarcinoma SK-Hep-1 cells. *Br J Nutr* 2012; 107(5): 631-8.
[<http://dx.doi.org/10.1017/S0007114511003473>] [PMID: 21787455]
- [95] Chountoulesi M, Naziris N, Pippa N, Demetzos C. The significance of drug-to-lipid ratio to the development of optimized liposomal formulation. *J Liposome Res* 2018; 28(3): 249-58.
[<http://dx.doi.org/10.1080/08982104.2017.1343836>] [PMID: 28627268]

SUBJECT INDEX

A

- Absorption 10, 12, 14, 21, 74, 76, 77, 82, 83, 98, 99, 100, 213, 214, 216, 242
 enhanced systemic 99
 intestinal lumen 99
- Acid (s) 2, 5, 11, 15, 17, 19, 38, 64, 65, 68, 109, 124, 131, 133, 144, 152, 156, 187, 191, 209, 211, 217, 233, 234, 235
 arachidonic (AA) 19
 asiatic 19, 109
 dithiodibutyric 152, 156
 drugs mefenamic 65
 fluorescent deoxyribonucleic 144
 gambogic 19
 gingoic 109
 glutaric 191
 glycolic 15
 Glycyrrhizin 17
 hyaluronic 38, 64, 124, 131
 lactic-co-glycolic 217
 nucleic 2, 133, 187, 209, 211
 oleanolic (OA) 5, 235
 oleic 11, 68, 85, 152, 235
 phosphatidic 234, 235
 phosphoric 233
- Action 111, 113, 208
 enzymatic 208
 hypoglycemic 111
 hypolipidemic 113
- Activity 7, 17, 67, 221, 282
 antihypertensive 17
 anti-malarial 282
 anti-tumor 7
 hypoglycemic 67
 leukocyte procoagulant 221
- Adenosine triphosphate 212
- Adenoviruses 209
- Adsorption 146, 149, 231
 inhibiting protein 231
- Agents 42, 80, 143, 166, 203
 anionic surfactant mildness 42
 anti-inflammatory 143
 chemotherapeutic 80, 166, 203
 immunotherapeutic 166
- AI-powered diagnostic systems 285
- Alkaloids 3, 6, 7, 19, 75
 bis-benzylisoquinoline 7
- Allergic eye diseases 136
- Amphiphilic block copolymers (ABCs) 215
- Anaesthesia 61, 66, 124
 transferrin 66
- Anaesthetics 61
- Analysis 48, 49, 190
 microscopic 49
 photocoagulated eyes 190
 transmission electron microscopy 48
- Angiogenesis 188
- Antibodies 88, 131, 155, 187, 188, 231
 monoclonal 188
- Anticancer drug, liposomal 209
- Anti-inflammatory 11, 19
 effects 19
 test 11
- Antioxidant 3, 4, 7, 11, 16, 17, 19, 21, 22, 37, 38, 40, 64, 65, 82, 109, 110, 111, 113, 242
 action 111
 activity 11, 16, 17, 22, 82, 242
 efficacy 113
 nature 40
 systemic 111
- Anti-proliferative effects 66, 249
- Antisense oligonucleotides 223
- Anti-solvent technique 103
- Anti-tumor agents 5
- Anti- VEGF oligonucleotide 190
- Apoptosis 47, 249, 280
 triggering 280
- Applications 2, 179, 185, 196, 231, 249
 biomedical 185, 196
 biomedicine 179
 liposome 231
 therapeutic 2, 249
- Arthritis 18, 19, 20, 240
 rheumatoid 18, 240
- Artificial intelligence in herbal medicine 289

Artificial neural networks (ANNs) 265, 285
 Atherosclerosis 110
 Autoimmune inflammatory disease 18

B

Bacillus thuringiensis 147
 Betaxolol hydrochloride (BH) 135
 Bioactive 191
 anticancer 191
 antiviral 191
 Bioavailability profile 10, 51
 Biogenesis mechanism 211
 Biological 37, 44, 47, 65, 86, 94, 96, 100, 168,
 172, 221, 228, 229, 240, 252, 281, 282
 activity 47, 65, 86, 96, 168, 172, 252, 282
 hypothesis 281
 membranes 37, 44, 94, 100, 221, 228, 229,
 240, 252
 Biomimetic liposomes 229
 Block copolymers, amphiphilic 215
 Blood 2, 156, 191, 193, 194, 195, 203, 205,
 210, 221, 228, 232, 266
 brain barrier (BBB) 2, 156, 193, 194, 195,
 203, 205, 210
 circulation system 228
 circulatory system 191
 clotting 221, 232
 coagulation 221
 disorders 266
 Bovine serum albumin (BSA) 216, 237
 Brain 132, 193, 194, 195, 221, 265
 -computer interface (BCIs) 265
 diseases 132, 193, 194, 195
 MR imaging mimicking 221
 parenchyma 195

C

Camellia sinensis 110
 Cancer 7, 15, 17, 18, 179, 202, 205, 209, 220,
 221, 227, 228, 265, 266, 278, 279
 bladder 7
 breast 265, 279
 chemotherapy 205
 colon 265, 266
 lung 15
 pancreatic 209
 Cardiovascular disease 3, 132, 168, 227

Central nervous system (CNS) 193
 Chemopreventive treatment 15
 Chemotherapeutic medications 208
 Chemotherapy 18, 205, 280
 Chitosan 43, 131, 136, 143, 146, 247
 folate-linked 131
 Cholesterol esterification 205
 Choline transporter 194
 Chronic diseases 21, 227
 Cirrhosis 100, 111
 protected in liver 100
 Coating 10, 149, 137, 151, 157, 158, 245, 246
 fatty 158
 liposomes 246
 polymer-based 137
 symmetric 151
 Collagen, restoring skin 44
 Collagenase synthesis 47
 Colloidosome architectures 159
 Colloidosomes 151, 152, 156
 enzyme amylase encapsulating 151
 plasmonic 152, 156
 Column chromatography 241
 Computers 259, 262, 263, 264, 265, 279
 conventional 264
 Concentration 19, 20, 22, 60, 62, 63, 66, 67,
 69, 78, 123, 126, 188, 189, 194, 202,
 205, 223, 224
 drug-carrier device's 205
 therapeutic 194, 202
 transdermal 63
 Contamination 175, 217
 bacterial 217
 Cornea inflammation 129
 Corneal 3, 129, 130
 injury 3, 129
 neovascularization 130
 Cosmetic 34, 38, 43, 44, 76, 142
 elements 44
 industries 34, 43, 76, 142
 related products 38
 skincare masks 43
 Creams 37, 38, 40, 46, 100, 104
 anti-ageing 37, 40
 Crohn's disease 205
 Crystals 108, 151
 fabricating photonic 151
 Curcuma longa 15, 19
 Cytochrome C (CC) 216
 Cytotoxicity assay 190

D

- Deaths 13, 124, 205, 212
 - apoptotic cell 212
- Degradation 1, 4, 11, 41, 69, 74, 75, 77, 85,
120, 211, 213, 229, 243, 244, 248
 - age-related macular 120
 - environmental 229
 - lysosomal 211
 - oxidative 69
 - process 75
- Delivery systems 1, 2, 47, 68, 73, 76, 84, 112,
125, 131, 168, 169, 215, 217, 230, 251
 - biomimetic antibiotic 217
 - drug nanoparticle 2
 - herbal-based drug 168
 - liposomal 215
 - liposome drug 251
 - nanotechnology-based drug 47
 - phytosomal drug 112
 - self-emulsifying drug 73, 76, 84
 - transfersome-based drug 68
- Dendrimer (s) 16, 17, 190, 192, 193
 - cationic phosphorus 17
 - in tuberculosis therapy 192
 - lipophilic amino acid 190
 - non-PEGylated 193
 - release 16
- Dermatitis 47, 109, 110
- Detrimental effects 223
- Devices 36, 146, 148, 168, 186, 206, 224, 276
 - aphoto-regulated memory 148
 - conventional bioactive delivery 186
 - drug delivery nanocarrier 206
 - microcapillary 146
- Dexamethasone 137
- Diabetes 227, 265, 268
- Diabetic retinopathy 120, 128, 276
- Digestion 22, 76, 77
 - of nanoemulsion 22
 - process 76, 77
- Digestive processes 44
- Diseases 1, 2, 3, 94, 120, 121, 123, 128, 136,
138, 192, 195, 205, 221, 229, 240, 266,
281, 285, 288, 289
 - angiogenesis-related 240
 - cerebral 195
 - corneal 121
 - inflammatory-moderated 136
 - intestinal 205
 - iris 121
 - metastatic 221
 - therapy 229
- Disinfection 40, 272
 - skin wound 40
- Disorders 19, 45, 50, 94, 129, 172, 214
 - inflammatory 19
 - nail-related 45
- Dispersed monomer method 15
- DNA 13, 35, 43, 61, 133, 144, 187, 196, 211,
233, 236, 280
 - damages 13
 - nanorobots 280
 - oligonucleotides 196
 - toxicity 223
- DOX inacidulous lysosomes 195
- Drug(s) 5, 17, 18, 68, 69, 73, 83, 84, 131, 141,
142, 143, 153, 157, 178, 185, 207, 214,
229, 232, 236, 244, 250, 265, 281, 282,
283, 284, 286
 - carriers, lipid-based protein-integrated 207
 - cytotoxic 18
 - developing anti-cancer 282
 - deliverance system 68
 - delivery vehicles 69, 153
 - discovery process 265, 282, 283, 284, 286
 - dissolution process 73
 - fabricated silver-coated colloidosomes
 - encapsulating anticancer 157
 - hydrophilic 84, 131, 141, 142, 143, 232,
236, 250
 - insoluble encapsulation 5
 - liposomal 244
 - macrophage-mediated 214
 - protein 83
 - screening process 281
 - side effects 229
 - toxicity 17, 185
 - transportation system 178
- Drug accumulation 169, 208, 230
 - required target-based 169
 - tumor tissue 208
- Drug concentrations 81, 83, 120, 121
 - therapeutic 121
- Drug delivery 70, 118, 119, 120, 121, 125,
127, 141, 155, 156, 158, 167, 168, 177,
194, 208, 218, 232, 259, 280
 - cell-targeting 218
 - efficient skin 232
 - lipid-based 158, 208

Subject Index

sustained 141
transdermal 70, 232
Drug development 99, 228, 259, 281, 288
therapy-related 228
Drug distribution 211, 215, 217, 229
systemic 217
Drug distribution 203, 212
methods 212
process 203
systems 203
Drug loading 84, 210, 250, 251
efficiency 251
process 251
Drug release 17, 33, 39, 82, 107, 132, 137,
143, 156, 207, 231
pH-sensitive 143
sustainable 132
Drug therapy 18, 230
conventional 18
Drug-to-cell 207
membrane transformation 207
transformation, reduced 207
Dry eye disease (DED) 136
Dual-targeting dendrimer nanoparticles 195
Dyspnea 6, 222
Dysregulated macrophage activity 214

E

Early-stage diseases, slow-progressing 123
Echinacea phytosome 110
Ecotoxicological effect 48
Edible oil and lipids 77
Efficiency 10, 12, 33, 43, 47, 59, 186, 230,
280
drug-targeting 230
therapeutic 186
Efficient self-micro emulsifying system 77
Electron microscopy 13, 40
cryofracture 13
Electrospinning 43
Electrostatic layer-by-layer deposition method
149
Emulsification 73, 81, 151
microfluidic 151
Emulsification 12, 22
diffusion 22
sonification method 12
Emulsifying 12, 233
Emulsion 12, 145, 147

Advanced Pharmaceutical Herbal Nanoscience, Part II 297

based approach 145
based technique 147
evaporation/sonification 12
Emulsions 77, 142, 145, 150, 152
continuous phase containing water-in-oil 142
inverse water-in-oil 150
oil-in-water 145, 152
systems 77
Encapsulate 143, 154, 156, 186, 229, 232
Encapsulated products, stable 148
Encapsulation 3, 4, 5, 8, 11, 16, 146, 147, 149,
150, 153, 157, 244, 246, 250
biomolecule 146
liposomal 8
polyphenol 3
Encapsulation 10, 141, 149, 249, 250
of CUR in liposomes 249
of herbal drugs 141
of herbal extract in liposomes 250
system 10
Endocytosis 131, 194, 195, 216
carrier-mediated mannose 194
caveolin-mediated 195
scavenger-mediated 216
Endophthalmitis 123
Endothelial cells 83, 119, 194
Engineering designing intelligence 280
Environment 95, 244
gastrointestinal 244
lipophilic membrane 95
Environmental 48
nanotechnology 48
risks of nanoparticles 48
Enzymes 43, 50, 144, 152, 156, 212, 249
metabolic 212
Epidermal keratinocytes 47
Epidermis 12, 36, 37, 63
Epigallocatechin 110
Epithelium 117, 118, 125
monolayer retinal pigment 125
non-pigmented 118
Escherichia Coli 157
Esculicide phytosome 109
Ethanol 8, 85, 238, 240, 247
and oleic acid 85
injection method 8, 238, 240, 247
Ethoxylated surfactants 11
Ethyl ximenynate 111
European medicines agency (EMA) 166
Evaporation 63, 80, 148, 150, 238, 239

process 238
 reverse phase 238, 239
 rotary 80
 EV separation 210
 Exosomal intercellular trade 211
 Exosome(s) 116, 132, 133, 209, 210, 211, 212
 biogenesis 210, 211
 fusion 211
 high-resolution subcellular 211
 Extracellular vesicles (EVs) 133, 208, 209, 210
 Eye 135, 136, 276
 infections 135, 136
 problems, common 276
 Eyesight, restoring 120

F

Facial 279, 270
 expressions, human-like 279
 predictive expressions 270
 FACS analysis 191
 Factors 18, 35, 36, 75, 77, 104, 105, 107, 119, 122, 123, 133, 174, 175, 191, 192, 206, 211, 223, 224
 anti-angiogenic 133
 anti-vascular endothelial growth 123
 environmental 18
 epidermal growth 206
 hepatocyte growth 211
 Failure 157, 190, 283
 traditional system expressedits 157
 Fatty acids 154, 233
 functionalized 154
 Fibrin-binding peptide 194
 Flow cytometry 47, 191
 Fluid 82, 83, 84, 101
 gastrointestinal 84, 101
 intestinal 82, 83
 Fluorescein angiography 128, 133
 Folic acid stability 22
 Force 61, 153, 236
 free rotational 236
 osmotic 61
 repulsive 153
 Formula, gelatin nanoparticle 7
 Formulation 22, 74, 83, 86, 191, 194
 dendrimer-based 191
 dendrimers-based 194
 lipid-based 74, 83, 86

 nutraceutical 22
 Fourier transform infrared 193
 spectrophotometry technique 193
 Freeze-fracture electron microscopy 81
 Freezing-thaw process 9

G

Gaps 204, 236
 Gas chromatography (GC) 172
 mass spectrometry 172
 Gastric juice 243
 Gastroenterology 261
 Gastrointestinal tract 76, 227, 251
 dissolution inthe 76
 Gd-perfluorocarbon nanoparticulate 128
 Gelatin 42, 145, 217
 nanoparticles 217
 nanosphere 42
 particles, formulated monodispersed 145
 Gel trapping technique 150
 Gene(s) 130, 131, 155, 156, 187, 193, 196, 224, 283, 288
 mutations 224
 ontology 288
 non-viral polymeric 130
 transfection 187
 Generative adversarial network (GAN) 282
 Ginseng Phytosome 110
 GI tract absorption 80
 Glaucoma 116, 121, 130, 131, 132
 treating 131
 treatment of 131, 132
 Glaucoma therapy 135, 137
 Glaucomatous retinal degeneration 120
 Glucuronides 20
 Glycerides 39, 78, 233
 polyglycolyzed 78
 Glycerol monomethacrylate 148
 Glycerophospholipids 96, 97
 Glyceryl monostearate 11, 12
 Glycosaminoglycans 19, 124
 Glycosides 95, 109, 249, 111
 natural 109
 phenylethanoid 249
 Gold 40, 46
 nanophytomedicine 46
 particles and gold nanoparticles 40
 Green 19, 46, 110, 131, 137
 fluorescent protein (GFP) 131, 137

nanotechnology 46
 tea extract (GTE) 19
 tea Phytosome 110
 Growth 34, 190, 194, 195, 206, 263, 290
 accelerated 206
 of artificial intelligence 263

H

Haemoglobin 137
 Hair 18, 33, 34, 35, 37, 38, 40, 41, 42, 44, 110
 care products 44
 conditioning 34
 cream 37
 damage 33, 34
 follicles 18
 loss repairing shampoo 35
 repair shampoo 37
 sun protection 41
 Health, human 22, 227
 Healthcare 172, 265
 global 172
 outcomes 265
 Hema tological toxicity 6
 Hemolytic toxicity study 189
 Hepatic stellate cells (HSCs) 249, 250
 Hepatocytes 249
 Hepatoprotection 100
 Hepatotoxicity 21
 Herbal 166, 170, 171, 172, 173, 174, 176, 177, 178, 197, 289
 based medicines 170, 171, 172, 173, 174, 176, 177
 healthcare products 178
 medicinal products (HMPC) 166, 171, 174, 180
 multicomponent 289
 nanomedicine development 179
 Herbal drugs 67, 73, 74, 75, 86, 141, 143, 167, 168, 171, 172, 174, 176, 177
 anti-inflammatory 67
 arehydrophobic 86
 transporting 167
 Herbal medicines 1, 2, 3, 8, 9, 73, 74, 75, 170, 171, 175, 176, 177, 180, 287
 aggregate Chinese 287
 in medicine systems 177
 High 100, 106, 107, 154, 172
 colloidal stability 154
 density lipoprotein (HDL) 100

performance liquid chromatography (HPLC) 106, 107, 172
 High-pressure homogenization (HPH) 11, 39, 64, 65
 technique 64, 65
 High-screening techniques 206
 HIV 85
 proteases 85
 treatment 85
 Homeostasis 118, 125
 Homoeopathy 172
 Hormones 69, 206, 207
 steroid 206
 HPH method 11
 Human phenotype ontology 288
 Hyaluronidase-engineered exosomes 209
 Hydrated pro-liposomes 243
 Hydrogels 20, 130, 134
 nanosphere-based 20
 pH-sensitive 130, 134
 Hydrolysis 101, 145, 248
 Hydrophilic 9, 11, 13, 35, 36, 37, 43, 74, 76, 78, 79, 99, 117, 118, 134, 236
 drug encapsulation 236
 Hydrophilicity 10
 Hydrophilic 83, 117, 235
 lipids 235
 molecules 83, 117, 235
 Hydrophobic 13, 18, 75, 83, 84, 126, 131, 150, 207, 208, 232, 233, 240
 bilayer membrane 233
 medications 207
 properties 233, 240
 silica nanoparticles 150
 Hydrophobic drugs 86, 207, 229, 230, 246
 liposomes imbue 230
 Hydrophobicity 245
 Hydrotaxis theory 69
 Hyperglycemic effect 65
 Hypotension 222
 Hypothesized cell-embedded substrate 206
 Hypoxic-ischemic encephalopathy 195

I

IBM 285
 watson genomics 285
 watson health 285
 Imbalance-related neurological diseases 205
 Immunoglobulin G (IgG) 152, 156, 216

- Industries, cosmeceutical 33
Infections 192, 211, 271, 272
 nematode 211
 pathogenic 211
 transmissible 192
Inflammation 3, 18, 42, 47, 111, 129, 190
 conjunctive 129
 synovial 18
Inflammatory diseases 214, 244
 pulmonary 214
Influence herbal medicinal research 179
Information, comprehensive toxicity 224
Ingredients, naturally-produced 23
 phytochemicals used as 23
Injection method 246
 prepared using the ethanol 246
Inner limiting membrane (ILM) 124
Instrumental techniques 105
Intelligence 259, 263
 natural 259
Intelligent 260, 268
 machines 260, 268
Intelligent robots 263, 267, 269, 274
 developing artificial 267
Interaction 21, 23, 98, 122, 149, 150, 151,
 152, 178, 179, 191, 192, 205, 206, 207,
 212, 221, 223, 231, 234, 236, 237
 electrostatic 122, 149, 152, 212
 liposome-protein 231
 protein-lipid 234
 protein-protein 207
 stoichiometric 98
Interface 10, 78, 142, 145, 147, 148, 152, 153,
 154, 158, 265
 brain-computer 265
 oil-in-water 148
 water-air 147
Interfacial tension 78, 153
Intra-articular resveratrol injection 19
Intraocular haemorrhage 123
- K**
- Keratin treatment 44
Ketoprofen transfersome 67
- L**
- Lactate dehydrogenase 249
Laws 171, 175, 176, 263, 277, 278
 consumer protection 278
Layer 149, 151
 by layer methods of preparation of
 colloidosomes 149
 by-layer techniques 151
LC techniques 76
Leishmaniasis 215
Lentiviruses 209
Ligand 194, 248
 anchored dendrimeric systems 194
 targeting liposomes 248
Light microscopy 13, 81
Lipid 9, 22, 39, 75, 76, 79, 136, 204, 207, 209,
 211, 215, 245
 based drug delivery systems (LBDDS) 75,
 76, 204
 composition 211, 245
 film hydration method 215
 free nanoformulation 22
 membrane 9
 nanoparticles 39, 136, 209
 transporter 207
 vehicles 79
Lipophilic 9, 43, 74, 77, 83, 84, 85, 132, 207,
 229
 bilayer 43
 drugs 9, 43, 74, 77, 83, 84, 85, 132, 229
 hormones 207
Lipophilicity 101, 105
Lipophilic 22, 73, 75
 natures 73, 75
 nutraceuticals 22
 plant extracts 22
Lipoproteins 82
Liposomal 23, 215, 237
 membrane surface 237
 therapy 215
Liposome(s) 4, 9, 10, 37, 60, 68, 97, 158, 208,
 227, 229, 230, 231, 232, 233, 234, 235,
 236, 237, 238, 240, 242, 243, 244, 245,
 248, 249, 250, 251
 anionic 234, 235, 242
 bilayer membrane 235
 can produce 238
 cationic 231, 234, 235, 242
 conventional 60, 231, 232, 243
 elastic 68, 232
 fabricating 158
 formulation 242, 245, 250

- immunogenicity of 229, 237
 - membrane 233
 - PEG-polyethyleneimine 248
 - pH-sensitive PEGylated 208
 - preparation 37, 244
 - production technique 238
 - propylene glycol 246
 - stability 227, 238
 - technology 97
 - transport processes 60
 - Lipoxygenase 19
 - Liquids 13, 14, 41, 74, 142, 151, 172
 - chromatography, high-performance 172
 - crystalline systems 13, 14
 - crystal systems 14
 - isotropic 13
 - non-miscible 41
 - phase deposition (LPD) 151
 - Liquid crystal 13
 - lyotropic 13
 - thermotropic 13
 - Liver 242, 243, 250
 - cell membranes 243
 - disease 242
 - disorders 242
 - fibrosis 250
 - Long-circulating liposome (LCL) 231, 248
 - Low 205, 273
 - cost flying wireless 273
 - density lipoproteins (LDL) 205
 - Lymphatic transport promotion 74
 - Lyotropic liquid crystals (LLCs) 13
 - Lysophospholipids 233
- M**
- Machine(s) 263, 265, 266, 268, 279, 280, 281, 288, 289
 - learning techniques 288, 289
 - artificial 265
 - Magnetic resonance imaging (MRI) 128, 191, 280
 - Malnourishment 268
 - Mannosylated dendrimer 191, 192
 - Manufacturing of liposomes 237
 - Mechanical tensions 124
 - Mechanisms 62, 63, 64, 74, 78, 81, 116, 120, 133, 137, 138, 188, 203, 215, 231
 - pegylation 188
 - rapid destabilization 231
 - reticuloendothelial 215
 - sustained release 138
 - Mediators, inflammatory 19
 - Medications 9, 18, 43, 44, 116, 117, 131, 138, 176, 203, 211, 203, 207, 208, 217, 218, 272, 273, 279, 283
 - anti-cancer 18
 - delivery system 203
 - distribution applications 211
 - lipophilic 9
 - plant-based 166
 - prolonging 203
 - Medicinal products 171, 208
 - herbal-based 171
 - Medicines 169, 170, 172, 173, 175, 176, 177, 218, 221, 223, 260, 261, 273, 276, 280, 289
 - and engineering designing intelligence 280
 - ayurvedic 172
 - botanical 170
 - Membrane permeability 94, 99, 101
 - Mesoporous silica nanoparticles (MSNs) 137
 - Metabolism 3, 4, 20, 40, 74, 83, 94, 178, 207, 244, 246
 - pre-absorptive 74
 - pre-systemic 244
 - rapid 3, 4, 20
 - vitalizing skin 40
 - Metallic nanophytomedicine 46
 - Metal nanoparticles 13, 126
 - transition 13
 - Metal-organic framework 142
 - Methods 80, 113, 148, 158, 224, 236, 287
 - analytical 224
 - compression 80
 - conventional 113, 287
 - cross-linking 148
 - for producing colloidosome microcapsules 158
 - rehydration 236
 - Methylcellulose 146
 - Microcapsules 74, 141, 142, 149, 152, 153, 155, 156, 157, 158
 - hybrid 153
 - Microemulsion(s) 6, 12, 192
 - liquid-crystalline systems 192
 - method 12
 - system 6
 - Microparticles 153, 158, 211, 214
 - doxorubicin-encapsulated chito-mimed 214

Microscopic techniques 49
Mitochondrial electron transfer system 212
Mitochondria-targeted drug delivery 212
Modification, oxidative 5
Modified cellulosenanocrystals 144
Modified double emulsion technique 157
Molecular 192, 156, 242
 dynamics simulations 192
 sensor 156
 weight cut-off (MWCO) 242
Mononuclear 209, 236, 237
 phagocyte system (MPS) 236, 237
 phagocytic systems 209
Mutations 76, 212
 mitochondrial DNA 212
Mycobacterium tuberculosis 192

N

Nano delivery systems 166
Nanoemulsion delivery systems 22
Nano-emulsion processes 75
Nanoliposomes for enhanced drug delivery 247
Nanomedicine technology 222
Nanoparticle 2, 17, 222
 decomposition 222
 drug formulation development 17
 techniques 2
Nanostructured lipid carrier (NLCs) 11, 12, 17, 35, 39, 40, 136, 155
Nanotechnology-based 117, 128, 137
 systems 128
 techniques 117, 137
Natural language processing (NLP) 259, 265, 285
Neurodegeneration 121
Neurons 124, 157, 193
 dopaminergic 157
Neurotoxicity 47
Neurotraumatic dopamine 157
Neutral liposome 235
Neutron diffraction 13
Nigella sativa 5
Niosomes 36, 37, 44, 45, 50, 127, 135, 137, 215
 developed 36
 encapsulated 215
NMR analysis 107
Northwestern spy-bird systems 272

NSCs, neural stem cells 47
Nucleobase transporter 194
Nucleosomes 50

O

Occupational risks of nanoparticles 48
Ocular 116, 133, 136, 137
 drug delivery 133, 136
 illnesses 116
 nanosystems 137
Ocular diseases 116, 117, 120, 127, 128, 132, 133, 134, 137, 138
 management of 117, 120, 127, 134
 treatment of 116, 132, 137, 138
Oil 13, 73, 77, 78, 79, 151, 141, 154
 and water interfaces 78, 79
 neem 141, 154
 non-ionic triglyceride 73
 polyethylene glycol castor 222
 vegetable 13, 77, 151
Oncologists 278, 279
Optical coherence tomography (OCT) 128, 133
Oral 4, 12, 17, 22, 46, 82, 86, 189, 251
 absorption 189, 251
 bioavailability 4, 12, 17, 22, 46, 82, 86
Organs 133, 192, 203, 209, 216, 223, 227
 macrophage-rich 216
Origem hair recycling shampoo 35
Osteoarthritis 19, 110
Other analytical methods 223
Oxidative phosphorylation 212
Oxide-inflammatory cascade 20

P

Pathways 49, 60, 75, 83, 133, 193, 195, 206, 208, 220
 biochemical 220
 intracellular lipid 60
 lymphatic 75, 208
 nasal 193
 open paracellular 83
 receptor-mediated endocytic 206
Peptide fibrillation 17
Percolating techniques 75
Permeability 78, 80, 81, 95, 96, 141, 142, 149, 156, 157, 159, 189, 190, 228, 244

Subject Index

transepithelial 189, 190
Phagocytosis 213
Phospholipid complexation technique 95
Phospholipids 95, 96, 97, 98, 99, 100, 101, 102, 106, 112, 227, 230, 232, 233, 234, 235, 236, 241, 245, 250, 251
 neutrally-charged 235
 synthetic 95, 233, 235
Phytochemicals 8, 10, 46, 96
 embedded active 8
 plant-based 46
Phytoconstituents and phospholipids 102, 112
Phytoextracts 102, 104, 105, 107
 bioavailability of 103, 113
Phytophospholipid complexation 103, 107
Phytophospholipid complexes 98, 99, 112
Plants 5, 6, 7, 9, 10, 11, 12, 14, 15, 48, 95, 97, 98, 99, 174, 178, 228, 244, 249
 and phytoconstituents 9, 14
 natural 228
 parasitic 249
 therapeutic 174
 turmeric 244
 water treatment 48
Plasmalogens 97, 211
Plasma membrane 210, 211
PLGA nanoparticles 151
Polymer 4, 15
 based nano formulations 4
 deposition methods 15
 nanoparticle method 15
Polymersomes, biodegradable chimeric 216
Polyphenols 3, 4, 5, 19, 23, 94, 101
 natural 19
Polyprenylated xanthone 19
Polypropylenimine 192
Polysaccharides, homopolymer 144
Predicting large-scale disasters 273
Preparation 6, 36, 37, 38, 39, 42, 73, 75, 94, 100, 103, 112, 135, 146, 147, 149, 178, 230
 botanical 178
 liposomal 135, 230
 liposome nanocarrier 6
Process 45, 46, 47, 75, 76, 77, 81, 82, 83, 85, 86, 104, 105, 206, 211, 283
 chromatographic 206
 endocytic 206
Producing colloidosome microcapsules 158

Advanced Pharmaceutical Herbal Nanoscience, Part II 303

Products 42, 44, 45, 47, 48, 94, 96, 98, 167, 176, 178, 228, 247, 251
 lip 45
 nanocosmeceutical 44
 nanomaterial 48
 nanotherapeutic 47
 natural 94, 96, 167, 176, 178, 228, 247, 251
 skincare 98
 skin-related 42
Progress of nanomedicine technology 222
Proliposomes 243
Proniosomes 20, 36
Properties 3, 4, 5, 11, 40, 46, 48, 50, 73, 75, 97, 154, 205, 217, 233, 249
 ageing 50
 amphiphilic 233
 anti-aging 249
 anti-bacterial 40
 anti-carcinogenic 4
 antitumor 46
 anti-ulcer 5
 bactericidal 48
 cell mimicking 217
 gastroprotective 97
 hepatoprotective 3
 immunomodulatory 5
 immunosuppressive 11
 isotropic thermodynamic 73
 lipophilic 75
 magnetic 154
 metastasis 205
Propylene glycol liposome (PGL) 246
Prospect of nanotechnology 49
Protease inhibitors 124
Proteins 50, 66, 83, 131, 132, 133, 137, 141, 142, 143, 155, 156, 187, 204, 206, 207, 209, 211, 212, 213, 283
 conjugation 50
 cytosolic 211
 endocytic 213
 endosomal-sorting complex
 monoubiquitinated membrane 211
 green fluorescent 131, 137
 import machinery 212
 leukocytic-derived natural 66
Psoriasis 6, 240
Pycnogenol phytosome 110

Q

Quantitative structure-activity relationship (QSAR) 281
Quantum dots (QD) 2, 45, 129, 280

R

Rabbit Immunoglobulin 152, 156
RA 19, 20
 pharmacotherapy 19
 therapy 19, 20
RBC membrane-coating technique 217
Reactions 42, 86, 105, 154, 214, 222, 251, 280
 adverse 222
 adverse drug 280
 alcoholic dispersion polymerization 148
 allergic 86, 214, 222
 chemical 251
 hypersensitivity 222
 one-step ligand exchange 154
 phytoconstituents phospholipid 105
 sensitization 42
Reactive oxygen species (ROS) 19, 212
Receptor(s) 194, 213
 macrophage mannose 213
 mediated transcytosis 194
Receptor proteins 207
 transition-facilitating 207
Red blood cells (RBCs) 193, 217
Reflux condenser 102
Regulations 20, 132, 166, 167, 170, 171, 173, 174, 175, 176, 180, 275, 277
 herbal drug 167
 immune 132
 stringent privacy 277
Regulatory proteins 209
Relationship 5, 46, 221, 282, 283, 288, 289
 geometric 5
Release 14, 17, 23, 43, 46, 127, 132, 148, 149, 150, 151, 152, 156, 157, 158, 159, 210, 211
 bioactive materials 23
 enzyme-triggered 132
 photo-triggered protein 148
 stimuli-responsive 127
Retina diseases 122
Retinal 120, 123, 125
 diseases 120, 123

 pigment epithelium (RPE) 125
Retinoblastoma 130, 131, 137
Retroviruses 209
Reversed-phase evaporation method 244
Reverse-phase evaporation method 238, 239, 244
Rheumatism 6, 19
Rheumatoid arthritis (RA) 18, 19, 20, 21, 240, 242
Robotic technology 279
Rotary evaporation method 103

S

Safety evaluation of herbal medicines 175
Scaffolds, promising 187
Secretion pathways 211
Security purposes camera 271
Self 73, 74, 75, 76, 77, 78, 79, 80, 81, 82, 83, 84, 85, 86
 emulsifying drug delivery 84
 emulsifying drug delivery system (SEDDS) 73, 75, 76, 78, 79, 80, 81, 83, 85
 emulsifying process 77
 micro emulsification drug delivery systems (SMEDDS) 73, 74, 75, 77, 78, 82, 83, 84, 86
 micro emulsification process 77
 nano emulsifying drug delivery system (SNEDDS) 74, 75, 76, 77, 82, 83, 84, 85, 86
Serum albumin 66, 216, 237
 bovine 216, 237
Silica 126, 150, 154
 nanoparticles 126, 154
 sol-gel reaction of 150
Silymarin proliposome solution 243
Simulation technique 192
Skin 20, 34, 38, 39, 40, 41, 42, 43, 68, 109, 283
 disorders 109
 dryness 34
 elasticity 40
 hydrating 39
 inflammation 40
 irritation 42
 lesions 283
 luminosity 38
 obstructions 68
 permeation 20

Subject Index

regeneration 43
retention 20
Small 9, 10, 81, 239
angle neutron scattering 81
angle X-ray scattering 81
unilamellar vesicle (SUVs) 9, 10, 239
Solid lipid nanoparticles (SLNs) 1, 2, 6, 8, 11,
12, 17, 20, 21, 24, 39, 40, 75, 76, 136
Solubility properties 77, 220
Solvent evaporation 11, 102, 105, 147
emulsification techniques 11
method 102, 147
technique 105, 147
Soya phospholipids 100
Soybean phospholipids 242
Soy phosphatidylcholine 245
SPC-based liposomes 245
Spectroscopic techniques 98, 107, 223
Spectroscopy 81, 107
photon correlation 81
Sphingomyelins 96, 97
Splenocytes 213
Spray drying technique 147
Stability 1, 2, 12, 13, 14, 20, 22, 23, 24, 65,
106, 112, 147, 153, 154, 251
phytochemical 251
Stabilizing gold nanophytomedicine 46
Stable colloidosomes 145, 150, 159
fabricated 145
Stratum corneum (SC) 36, 47, 59, 62, 63, 64,
67, 69, 204
Stress 60, 286
dependent changes 60
Stroke 195, 227
ischemic 195
Subcutaneous tissue 60
Subretinal Injections 124
Supercritical fluid 103, 113
methods 103
process 113
techniques 103
Surgery 145, 205, 211, 259, 270, 271, 287
gynaecological 271
Synthesis 145, 211, 243
hepatocyte protein 243
System 10, 11, 13, 14, 16, 17, 80, 82, 83, 85,
128, 129, 150, 153, 204, 216, 217, 220,
221, 224, 230, 247, 266, 271, 277, 282
algorithm 277
cytoplasm 216

Advanced Pharmaceutical Herbal Nanoscience, Part II 305

elementary 80
immune 220, 221, 224
lipid-based 85
lymphatic 83
nanoliposome 247
reticuloendothelial 217, 230
robotic 282

T

Target herbal medicine 169
Technologies 8, 34, 44, 46, 107, 113, 117, 126,
185, 223, 259, 260, 264, 265, 272, 273,
274, 275, 276, 278, 289
based novel drug delivery 185
engineering 126
fast-advancing 117
flourishing 223
herbosomal 113
herbosome 107, 113
Thebiodegradable polymers 146
Therapies 8, 21, 66, 69, 86, 127, 130, 131,
136, 195, 206, 281
allopathic 21
brain diseases 195
photodynamic 8, 131
Thermal annealing method 149, 150
Thermodynamics theory 79
Thermotropic liquid crystals (TLC) 13, 172
Thin-film 65, 237
dispersion method 65
hydration method 237
Thin-layer 171
chromatography 171
Tissues 18, 188, 123, 124, 125, 127, 130, 133,
202, 203, 204, 205, 208, 209, 218, 223,
230
cancerous 188
choroidal 125
damaged 202
inflamed 18
inflammatory 230
tumor 230
Tools, electromagnetic 45
Toxicity 189, 216
gastrointestinal 189
hemolytic 216
Toxicological reactions 127
Tract 203
Traditional chinese medicine (TCM) 176, 287

Transdermal delivery system 64
Transferosome 62
Transferrin 194, 195, 206, 236
Transfersome technology 69
Transition temperature 106, 239
Translocate protons 212
Transmission electron
 microscopy 243, 247
 photomicroscopy 243
Transport 23, 60, 125, 133, 137, 143, 145,
 190, 195, 204, 211, 220, 276, 279
 elastic 60
 protective 23
 transepithelial 190
Transporting 99, 167, 212, 247
 electrons 212
 herbal 167
Tuberculosis therapy 192
Tumors 6, 17, 18, 129, 179, 188, 194, 195,
 208, 230, 247, 249
 imaging 129
 therapy 18
Tumor's microbiome 208
Turing test 263

U

Ultrasonography 128
Ultrasound sensitivity 156

V

Vapour phase deposition (VPD) 151
Vehicles 39, 69, 75, 76, 104, 152, 158, 204,
 214, 268
 non-polar 204
 semisynthetic oil 104
Vessels 83, 119, 128, 205
 angiogenic 128
 intestinal lymphatic 83

W

Waals forces 23, 145
 producing Vander 145
World health organization (WHO) 68, 166,
 170, 172, 177



Swarnlata Saraf

Dr. Swarnlata Saraf graduated from the Indian Institute of Technology, BHU, Varanasi and received her Ph.D. from Dr. H. S. Gour University Sagar, India. She guided 40 Master's Degrees and 19 Ph.D. students. She wrote 6 books and numerous chapters in edited books, filed patents and contributed to more than 200 scientific publications. She served as an editorial board member, reviewer of research journals and books. She served as an expert of national and international research projects and its screening committee. According to Google Scholar, she bears 9200 citations, H-index 47 and i-10 index 170 and has received national awards from various professional bodies. She handled research projects funded by national public agencies (India). As per a recently released database by Stanford University, she is among the top 2% of World Scientists. Her areas of interest are pharmaceuticals, nanotechnology, herbal drug delivery, and cosmetic technology. She has widely travelled abroad like USA, UK, Switzerland, Singapore, UAE and many more for official, professional and academic activities.



Ram Kumar Sahu

Dr Ram Sahu is a result oriented, high energy, hands-on proficient with a successful record of achievements. He has completed his Ph.D. from Banasthali University, Jaipur (Rajasthan), India and M Pharm from Dr. M. G. R. Medical University, Chennai, India. Currently, he is an assistant professor at the Department of Pharmaceutical Sciences, Assam University (A Central Government University), Silchar (AS), India. He also holds the position of associate professor at Pharmacy Department, Pt. Deendayal Upadhyay Memorial Health Sciences and Ayush University of Chhattisgarh, Raipur (CG) and Columbia Institute of Pharmacy, Raipur. He had more than 15 years of teaching experience along with research experience. He delivered guest lectures at various Universities of Malaysia, Thailand, Philippines and Indonesia. Dr. Sahu's research work highlights novel drug delivery system, isolation and characterization of active constituents, formulation and standardization of herbal drugs, screening and evaluation of various pharmacological activities of samples. He has made innovative, outstanding and original contributions both in education and research in the area of natural products. Under his supervision, 03 Ph.D. scholars and 26 PG students have been awarded. Dr. Sahu was appointed as co-supervisor for M Pharm students in the MSU University Malaysia. He has received many awards from international and Indian conferences. He is an editorial board member and reviewer of various national and international peer-reviewed journals. Dr. Sahu has been an invited speaker and panellist at various international and Indian conferences.



Vivek Dave

Vivek Dave, presently working in the capacity of Associate Professor at Central University South Bihar, Gaya, Bihar has commendable experience and skills coupled with sound theoretical knowledge. Besides his past experiences with many pharmacy colleges, he also worked for more than 8 years at the Banasthali University, Rajasthan soon after pursuing his Ph.D. from Banasthali University itself. During his Ph.D., he worked on the design and evaluation of aceclofenac and esmolol HCl containing ocular drug delivery system. He did his Masters in Pharmaceutics on Aceclofenac ethosomes for enhanced transdermal drug delivery system. His expertise in working with the formulation and development of novel drug delivery systems like PEGylated liposome, ethosomes, nanoparticle, quantum dots has shaped the leading scientific high impact research and book publications of international repute. Currently, he is working on nano-formulation for therapeutic managements of various diseases like Alzheimer's, inflammation, and cancer, etc. He has been the recipient of several awards in various conferences, seminars and conventions, including a prestigious award, "Best Sustainability Award" on Smart Shoe sole in the 2019's International Conference on Future Healthcare and Economic Development from Medical Device Innovation Center (MDIC), National Cheng Kung University, Taiwan. Dr. Dave is also acting as a regular reviewer of journals of national and international repute of different publishing houses, namely Wiley, Springer, Elsevier, BMC, etc.