

BONE FORMATION IN RAT'S CALVARIAL DEFECT AFTER APPLICATION OF DEMINERALIZED FREEZE DRIED BOVINE CORTICAL BONE MEMBRANE

by David Kamadjaja

Submission date: 23-Jan-2019 11:54AM (UTC+0800)

Submission ID: 1067334836

File name: Bone_formation_Asian_Journal_of_Microbiol-Desember_2018.pdf (553.96K)

Word count: 1788

Character count: 9708

BONE FORMATION IN RAT'S CALVARIAL DEFECT AFTER APPLICATION OF DEMINERALIZED FREEZE DRIED BOVINE CORTICAL BONE MEMBRANE

GANENDRA ANUGRAHA¹, DAVID B. KAMADJAJA^{1,2}, R. SOESANTO¹ AND ACHMAD HARIJADI¹

¹Department of Oral and Maxillofacial Surgery, Faculty of Dental Medicine, Universitas Airlangga, Jawa Timur, Indonesia

²Stem Cell Research and Development Center, Universitas Airlangga, Jawa Timur, Indonesia

¹⁰(Received 25 September, 2018; accepted 15 November, 2018)

Key word: Bovine cortical bone membrane, Guided bone regeneration, Bone formation

Abstract– Bovine pericardium collagen membrane (BPCM) had been widely used in guided bone regeneration (GBR) for alveolar bone augmentation. However, it is associated with prolonged biodegradation. A newly developed Demineralized Freeze-Dried Bovine Cortical Bone Membrane (DFDBCMB) assumed to be rich in osteogenic growth factors was found to be biocompatible. Its osteogenic capacity yet to be proven. This study evaluated bone defects healing in rats' calvarial critical sized defect after the application of DFDBCMB and BPCM. Critical sized defect was made on calvaria bone of 30 Wistar rats. The samples were divided into 3 groups, each contains of 10 rats. The defects were then covered by DFDBCMB and BPCM in the first two groups, the control group was left to heal without membrane application. Samples were collected at 4 and 8 weeks from each group. Degree of bone healing was examined using histology examination with HE staining using bone healing score. Data was analyzed statistically with the Kruskal-Wallis test and Mann Whitney accordingly. The degree of bone healing was significantly higher in DFDBCMB groups compared to BPCM groups both in 4 and 8 weeks observation. DFDBCMB has higher capacity for bone defect healing compared to BPCM in rat's calvaria defect.

INTRODUCTION

Alveolar augmentation is a surgical procedure to improve the shape and size of the alveolar bone in preparation for receiving and maintaining a dental prosthesis and implant placement (Pellegrini, *et al.*, 2013). Whereas Guide Bone Regeneration (GBR) is a technique where bone growth is obtained by maintaining space and preventing soft tissue growth into the area which will be developed using a resorbable or nonresorbable barrier membrane and giving bone graft inside the defect (Donos *et al.*, 2002). The initial types of graft material are autogenous, allograft, xenograft, and alloplastic (Newman, 2002). Autogenous is obtained from the patient itself and has the ability to form new bone in osteogenesis, osteinduction and osteoconduction (Tedyasihto, 2010).

Demineralized freeze dried bovine cortical bone membrane (DFDBCMB) has several advantages

including containing collagen that is intact so that it is expected to produce more growth factors. In addition, DFDBCMB also has no difficulty in biodegradation, thus allowing a better membrane degradation process which will support the osseointegration process of new bone with surrounding tissue and will induce better bone healing than Bovine Pericardium Collagen Membrane (BPCM).

To determine the effectiveness of using DFDBCMB in the GBR method, it is necessary to know the degree of bone healing.

MATERIALS AND METHODS

Preparation of surgical procedure

As an animal, 30 Wistar rats aged 10 - 12 weeks were used with a weight of 120 - 140 g, which were adjusted for a week. Rats were kept each in a cage

*Corresponding author's email: david-b-k@fkg.unair.ac.id

measuring 30 x 30 x 10 cm for each treatment group consisting of 5 rats. All animals are given a normal diet and drinking water during the study period.

The procedure begins with intramuscular injection of ketamine HCl (20 mg / kg body weight). After the anesthetic has worked, the area of the dorsum region is shaved and povidone iodine disinfection is 10%. Skin incisions were performed on the rat's head in the medial section, and then mucoperiosteal flap retraction was performed until calvaria bone was obtained. Medial suture was identified in calvaria rats. The defect was made on the right lateral side of the medial suture using a bur of 5 mm in diameter as thick as 0.8 mm. The membrane was applied over the defect until the defect is completely covered by the membrane. Then suturing the incision wound on the skin with silk thread 3.0.

In the 4th and 8th weeks after the membrane application, each 5 rats from the treatment and control groups were sacrificed for the research tissue specimen retrieval procedure. The mouse is decapitated without removing the skin tissue above the defect. The specimens processed to obtain histology slides under routine procedure.

Histology Examination

In this study, an examination of the degree of bone healing was carried out by using indicators score of connective tissue formation, woven bone, bone

trabeculae and formation of adult bones. The four indicators were observed at week 4 and week 8.

Table 1. Bone Healing Score

Score	Callus Proportion			
	Fibrous Tissue	Woven Bone	Trabeculae Bone	Adult Bones
1	++++	+	+	-
2	++	++	++	-
3	+	+++	+++	-
4	+/-	++++/++	++++/+	+/+++

Score 1: healing zone is dominated by fibrous tissue with / without a little woven bone and with / without bone trabeculae, no adult bone is found

Score 2: healing zone consists of a small amount of fibrous tissue, and has begun to form woven bones and trabecular bones, no adult bones

Score 3: healing zone consists of a little fibrous tissue, lots of woven bones and trabecular bone, adult bones have not been found

Score 4: fibrous tissue begins to disappear, the proportion of woven bones and trabecular bone is higher, adult bones have been found

The data from histological examination result is analyzed statistically with the Kruskal-Wallis test and followed by the Mann Whitney test accordingly. Significant difference is determined when p value is < 0.05.




Fig. 1. Microscopy of defect healing in the fourth week and eight week after implantation of membrane. (A) Implantation of DFDBCMB, (B) BPCM and (C) without membrane. It appears that there are already woven bone tissue with little lamellae (1-2 lamellae (→)), bone vitality is confirmed by the presence of osteocytes (→). Note: osteoblasts (→), new bone (TB), old bone (TL), connective tissue (→), inflammatory cell (→), fibrous tissue (→), bone membrane (→), pericard membrane (→), erythrocyte (E).

RESULTS

Based on the results of observations and measurement of the value of the variable degree of bone healing by histology examination divided into 3 research groups: (1) the treatment group (DFDBCMB); (2) treatment group (BPCM); (3) negative control group (without membrane), with each study sample that has been observed in the 4th and 8th weeks, obtained results. In this study, the total healing zone area, fibrous tissue area and reinforcement area within the healing zone were calculated. On histomorphometric calculation at week 4th and 8th. The total area of fibrous tissue of DFDBCMB treatment group was narrower.

The data described in figure 2 showed that the degree of bone healing in DFDBCMB groups is higher than BPCM and control groups both in fourth and eighth week. Statistical analysis with Kruskal-Wallis test revealed significant difference ($p < 0.05$) among groups in both observation times. Mann-Whitney U-test confirmed that there are significant difference ($p < 0.05$) in bone healing degree between DFDBCMB group and BPCM as well as control group in fourth week. Significant difference in bone healing degree in eight weeks is only found between DFDBCMB and control group ($p < 0.05$).




Fig. 2. The average of The Degree of Bone Healing in DFDBCMB, BPCM and control groups in fourth and eighth week post implantation

DISCUSSION

The observation in this study consisted of 2 periods, 4 weeks and 8 weeks. This is done to assess the dynamic processes that occur so that they can see the changes that occur during the healing process. The 4th week observation time is based on the bone formation phase, where there is a mineralization process, woven bone formation, osteoclasts convert callus to lamellar bone and woven bone. Lamellar and woven bone in this study were counted as reinforcement areas (Bouxsein, 2010).

The degree of bone healing was carried out by using indicators scale of connective tissue formation, woven bone, bone trabeculae and formation of adult bones (McAllister *et al.*, 2007). The four indicators were observed at week 4 and week 8. The higher score showed the better degree of bone healing in the calvaria rat defect. If the composition in the calvaria bone defect is dominated by connective tissue, it indicates that the healing of bone defects has not yet formed bone that covers the defect. Whereas if the calvaria bone defect has begun to form bone and some adult bones begin to form, this indicates that the bone defect has undergone a healing process and the defect has begun to be covered by bone (Kalfas, 2001).

In addition to the irregular collagen fibers, there are other characteristics for primary bone tissue, namely the lack of mineral content so that it is easily penetrated by X-rays and more osteocytes when compared to secondary bone tissue. Primary bone tissue will eventually undergo remodeling into a secondary (lamellar bone) that is physically stronger and resilient. Therefore in healthy adult bones there is only lamella (Nieminen, *et al.*, 2006).

The result of the study determines that DFDBCMB has the potential to be applied as a membrane in the GBR procedure. This is because DFDBCMB indicates that the number of adult osteoblasts in the bone defect area is obtained and osteogenesis process occurs better in the defect applied by DFDBCMB membrane. This shows that DFDBCMB membranes have good osteoinduction properties that increase the process of osteogenesis after subcutaneous implantation in animals testing the Wistar Rattus norvegicus strain.

CONCLUSION

From this study, it was found that Demineralized Freeze-Dried Bovine Cortical Bone Membrane has high osteogenic capacity compared to bovine pericardial membrane. Therefore, it is potential to be applied as a membrane in the Guide Bone Regeneration procedure.

REFERENCES

- Donos, N., Kostopoulos, L. and Karring, T. 2002. Augmentation of the rat jaw with autogenic cortico-cancellous bone grafts and guided tissue regeneration. *Clin Oral Implants Res.* 13 : 192-202.

- Kalfas, I.H. 2001. The principles of bone healing. *Neurosurg focus* 10 : 1-10.
- McAllister, B.S. and Haghghat, K., 2007. Bone augmentation techniques. *J. Periodontal*. 78:377-96.
- Nieminen, T., Kallela, Keranan, J., Hiidenheimo, I., Kainulainen, N., Wuolijok, E. and Rantala, I. 2006. *In vivo* and *in vitro* degradation of a novel bioactive guided tissue regeneration membrane', *Int. J. Oral Maxillofac. Surg.* 35 : 727-732.
- Newman, M.G., Takei, H.H. and Carranza, F.A. 2002. *Clinical Periodontology*, 9th ed., W. B. Saunders Company, Philadelphia.
- Pellegrini, G., Pagni, G. and Rasperini, G. 2013. Surgical Approaches Based on Biological Objectives: GTR versus GBR Techniques. *International Journal of Dentistry*, University of Milan, Italy.
- Tedyasihto, B. 2010. *Buku Ajar Implantologi Mulut: Teori & Praktek*, EGC, Jakarta.



BONE FORMATION IN RAT'S CALVARIAL DEFECT AFTER APPLICATION OF DEMINERALIZED FREEZE DRIED BOVINE CORTICAL BONE MEMBRANE

ORIGINALITY REPORT

9%

SIMILARITY INDEX

7%

INTERNET SOURCES

3%

PUBLICATIONS

2%

STUDENT PAPERS

PRIMARY SOURCES

1

doaj.org

Internet Source

2%

2

Brugnami, Federico, and Cristiano Caleffi. "Prosthetically driven Implant Placement. How to achieve the appropriate implant site development", The Keio Journal of Medicine, 2005.

Publication

1%

3

ejournal-s1.undip.ac.id

Internet Source

1%

4

Alexander Patera Nugraha, Ida Bagus Narmada, Diah Savitri Ernawati, Aristika Dinaryanti et al. "Osteogenic potential of gingival stromal progenitor cells cultured in platelet rich fibrin is predicted by core-binding factor subunit- α 1/Sox9 expression ratio (in vitro)", F1000Research, 2018

Publication

1%

5	Submitted to iGroup Student Paper	1%
6	www.envirobiotechjournals.com Internet Source	1%
7	jpaap.napier.ac.uk Internet Source	1%
8	cdeworld.com Internet Source	1%
9	repository.unair.ac.id Internet Source	1%
10	www.frontiersin.org Internet Source	<1%
11	"ABSTRACTS", Clinical Oral Implants Research, 8/2006 Publication	<1%

Exclude quotes Off

Exclude matches Off

Exclude bibliography On

BONE FORMATION IN RAT'S CALVARIAL DEFECT AFTER APPLICATION OF DEMINERALIZED FREEZE DRIED BOVINE CORTICAL BONE MEMBRANE

GRADEMARK REPORT

FINAL GRADE

/0

GENERAL COMMENTS

Instructor

PAGE 1

PAGE 2

PAGE 3

PAGE 4
